

SELECTION & SPECIFICATION DATA

Generic Type	Polyamide Epoxy with corrosion inhibitor, (zinc phosphate)
Description	A high performance, surface tolerant, high build, corrosion resistant epoxy mastic. It has outstanding adhesion to metal substrates along with most aged coatings and offers maximum protection against severe weather conditions, corrosion, moisture penetration and general industrial environments. It wets and penetrates firm rust and tight crevices and resists further rust deterioration. Use it on tank exteriors, structural steel, piping, process equipment, bridges & water towers. Carbomastic 94 may also be used on barges, vessels and other marine applications. An optional micaceous iron oxide, (MIO), additive can be purchased separately and may be used per its Product Data Sheet to further enhance the coatings's performance.
Features	<ul style="list-style-type: none"> • Surface tolerant epoxy mastic • Excellent corrosion protection • Low VOC • Custom colors available via RTS • Excellent wetting properties and adhesion • High solids, low stress over existing coatings • High film build, up to 7 mils DFT per coat • Class A Flame Spread and Smoke Development • Excellent durability • Good flexibility and impact resistance • Outstanding abrasion resistance • Good chemical resistance • Long pot life • Long maximum re-coat, up to 1 year • Approved topcoat over many Carboline Fireproofing Materials
Color	RTS capable, refer to Carboline color chart.
Finish	Semi-Gloss
Primer	Self priming. May be used over zinc-rich primers or other epoxies.
Dry Film Thickness	5 - 7 mils (127 - 178 microns) per coat 5 mils for most applications; 7 mils for more aggressive exposures.
Solids Content	By Volume 86% +/- 2%
Theoretical Coverage Rate	1379 ft ² /gal at 1.0 mils (33.9 m ² /l at 25 microns) 276 ft ² /gal at 5.0 mils (6.8 m ² /l at 125 microns) 197 ft ² /gal at 7.0 mils (4.8 m ² /l at 175 microns) Allow for loss in mixing and application.
VOC Values	As Supplied : 1.0 lbs/gal (120 g/l)
Dry Temp. Resistance	Continuous: 200°F (93°C) Non-Continuous: 250°F (121°C)
Topcoats	May be coated with Acrylics, Epoxies, or Polyurethanes depending on exposure and need.

Carbomastic 94

PRODUCT DATA SHEET



SUBSTRATES & SURFACE PREPARATION

General | Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.

Steel | SSPC-SP 2, SP 3, SP 7, or Waterjet Cleaning of Metals per WJ-1 through WJ-4 are acceptable methods. Use a minimum of NACE No. 3/SSPC-SP 6 with a 2.0-3.0 mil (50-75 micron) surface profile for maximum protection.

Galvanized Steel | Prepare in accordance with SSPC-SP 16, latest edition.

Previously Painted Surfaces | Clean and lightly sand or abrade to roughen and degloss the surface. Existing coatings must attain a minimum 3A rating in accordance with ASTM D3359 "X-Scribe" adhesion test.

MIXING & THINNING

Mixing | Thoroughly mix each component using mechanical agitation. Pour the activator, part B, into part A (mixing ratio by volume: 1 part activator, part B, to 1 part base, part A) and mix well using mechanical agitation.

Thinning | Mixed Carbomastic 94 may be thinned to a maximum of 25 fluid ounces per gallon with Thinner 248. Use of solvents other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.

Pot Life | Maximum 4 hours at 77 °F (25 °C). In order to maintain application properties, mix (activate) only what can be applied in 4 hours. Allow 15 minutes induction time at 77 °F (25 °C).

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Spray Application (General) | Apply using airless spray. Use a 50% overlap with each pass when spraying to eliminate holidays and pinholes.

Airless Spray | Material Hose: 3/8" I.D. (min.)
Tip Size: 0.019-0.023"
Output PSI: 3000 minimum
High Pressure Filter: 30 Mesh

Brush | Natural bristle or nylon/polyester

Roller | 1/4-3/8" woven, solvent resistant core for smooth surfaces, 3/4- 1 1/4" nap for rough surfaces.

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	50°F (10°C)	50°F (10°C)	50°F (10°C)	0%
Maximum	90°F (32°C)	110°F (43°C)	110°F (43°C)	100%

CURING SCHEDULE

Surface Temp.	Dry to Touch	Dry to Recoat	Dry to Topcoat	Dry to Handle
50°F (10°C)	10 Hours	20 Hours	40 Hours	20 Hours
60°F (16°C)	6 Hours	12 Hours	24 Hours	12 Hours
75°F (24°C)	3 Hours	6 Hours	12 Hours	6 Hours
90°F (32°C)	1.5 Hours	3 Hours	6 Hours	3 Hours

Expect longer dry times in periods of higher humidity or lower temperatures or when applying thicker films. These dry times are for exterior exposures at recommended film thickness with good ventilation. The temperature of the substrate during coating application must be at least 5 °F above the dew point of the air. * Note: Dry to recoat is 6 hours or within 1 year.

CLEANUP & SAFETY

Cleanup | Clean up all tools and equipment promptly with Thinner 2.

Safety | Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions. Use adequate ventilation. Keep container closed when not in use.

PACKAGING, HANDLING & STORAGE

Shelf Life | Part A: 36 months
Part B: 36 months

*Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.

Storage Temperature & Humidity | 40-110 °F (4-43 °C)
0-100% Relative Humidity

Storage | Store Indoors.

Shipping Weight (Approximate) | 2-Gal Kit - 29 lbs
10-Gal Kit - 139 lbs

Flash Point (Setaflash) | Part A - 89 °F (32 °C)
Part B - 105 °F (41 °C)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.