

SELECTION & SPECIFICATION DATA

Generic Type	Proprietary cross-linking epoxy-acrylic gloss finish
Description	Fast cure iso-cyanate-free epoxy-acrylic gloss coating for industrial and marine and off-shore applications where use of polyurethane coatings is banned or undesirable.
Features	<ul style="list-style-type: none"> • Isocyanate free • Early through-curing • User friendly wet edge characteristics - cuts over-spray 'flashing' • Excellent colour and gloss** retention • Lead and chrome-free colour range • Excellent gloss retention • Good chemical resistance • Good chalk resistance • Excellent durability • Excellent aged self re-coat
Colour	<p>NZ & AU: White & most BS and AS shades</p> <p>NZ only: Black and Golden Yellow LF</p> <p>AU only: Silver Aluminium (satin finish) and Blast Grey 1 (low sheen finish)</p>
Gloss	<p>Typical Gloss - 83+ Gloss Units*</p> <p>* Gloss level may be colour dependent (see notes to AU only colours above)</p>
Primer	Apply over the specified Carboline® intermediate or primer coat Refer to Carboline Technical Service or relevant Coating Specification
Film Build	40 – 60 microns – 50 microns DFT optimum Do NOT attempt to overbuild this product
Solid(s) Content	44% by volume
Coverage Rate	<p>11.2 square metres per litre at 40 µm DFT 9.0 square metres per litre at 50 µm DFT 7.5 square metres per litre at 60 µm DFT</p> <p>Optimum WFT/DFT: 111 µm wet to obtain 50 µm dry Do NOT attempt to overbuild this product</p>
VOC Value(s)	490 grams per litre (mixed) - EPA Method 24
Dry Temp. Resistance	<p>Continuous: 90°C (194°F) Non-Continuous: 121°C (250°F)</p> <p>Discolouration may be observed above 93°C</p>
Limitations	<ul style="list-style-type: none"> • Colour may change as temperature approaches 121°C, but the film will remain intact • As noted in "Film Build" and "Coverage Rate" above; this product should not be over-built as over application will retard through-cure and may cause finish wrinkling.

Carboguard 2929 Gloss Finish

PRODUCT DATA SHEET



SELECTION & SPECIFICATION DATA

Chemical Resistance Tables

ASTM D1308 – 24 hour Spot Test Under Watch-Glass at 21°C

- 10% Ammonia (aqueous): No effect
- Ammonia – concentrated: No effect
- 10% Sodium Hydroxide: Slight fine blistering, slight discolouration
- 35% Sodium Hydroxide: Very slight discolouration, no blisters
- Tap Water: No effect
- 5% Sodium Chloride: No effect
- 10% Hydrochloric Acid: No effect
- 10% Acetic Acid: Severe blistering & wrinkling
- 10% Nitric Acid: Heavy blistering & discolouration
- 5% Sulphuric Acid: Slight fine blistering
- 10% Sulphuric Acid: Moderate fine blistering
- 10% Phosphoric Acid: Moderate fine blistering

SUBSTRATES & SURFACE PREPARATION

General

Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. For all surfaces prime with specific Carboline primer as recommended by your Carboline sales representative. Refer to the specific primer's Product Data Sheet for detailed requirements of the specified primer.

Steel

Power tool clean or abrasive blast to the standard required for the specified primer, taking into account the required performance and the exposure conditions.

Galvanized Steel

Prime with specific Carboline primer as recommended by your Carboline Sales Representative. Refer to the specific primer's Product Data Sheet for substrate preparation requirements.

Previously Painted Surfaces

Lightly sand or abrade to roughen and degloss the surface. Existing paint must attain a minimum 3B rating in accordance with ASTM D3359 "X-Scribe" adhesion test.

PERFORMANCE DATA

Test Method	System	Results
Abrasion Resistance ASTM D4060		Very good
Adhesion ASTM D4541	1 ct Cg 690 / 1 ct Cg 2929	Excellent
Elongation ASTM D522 Method B	1 ct Cg 690 / 1 ct Cg 2929	Very good
Gloss		83+ Gloss Units
Gloss Retention QUV Exposure	Cg 2929 Gloss White	96% Gloss Retention after 3000 hours QUV-A
Humidity Resistance ASTM D2247	1 c Cg 690 / 1 ct Cg 2929	Very good

MIXING & THINNING

Mixing | Mix each component separately, then combine and mix to the correct 4:1 proportions.

MIXING & THINNING

Thinning	<ul style="list-style-type: none"> • Spray: Up to 20% with #25 • Brush: Up to 20% with #25 • Roller: Up to 20% with #25 <p>Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.</p>
Ratio	<ul style="list-style-type: none"> • 4:1 by volume (Part A : Part B) • <u>5 litre kit</u>: Part A 4 litres, Part B 1 litre • <u>1¼ litre kit</u>: Part A 1 litres, Part B ¼ litre
Pot Life	4 hours at 24°C (5 litre kit)
Induction Time	10 minutes at 25°C; longer if colder

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

General	Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.
Conventional Spray	Pressure pot equipped with dual regulators, 9.5 mm (3/8") I.D. minimum material hose, 1.8 mm (.070") I.D. fluid tip and appropriate air cap. Hold gun 300-350 mm from the surface and at a right angle to the surface.
Airless Spray	<p>Pump Ratio: 30:1 Volume Output: 10 l/minute min. Material Hose: 9.5 mm min. (3/8") I.D. Tip Size: .013-.017" Output Press.: 2100-2400 psi Filter Size: 60 mesh *Teflon packings are recommended and available from pump manufacturer.</p>
Brush & Roller (General)	<p>Recommended for touch-ups only Multiple coats may be required to obtain desired appearance and adequate hiding. Avoid excessive rebrushing or re-rolling. For best results, tie-in within 10 minutes at 24°C.</p> <ul style="list-style-type: none"> • Brush: Use a medium, natural bristle brush. • Roller Use a short nap roller cover with a phenolic core

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	10°C (50°F)	5°C (41°F)	2°C (36°F)	0%
Maximum	38°C (100°F)	45°C (113°F)	35°C (95°F)	90%
Optimum	20°C (68°F)	20°C (68°F)	20°C (68°F)	50%

Industry standards are for substrate temperatures to be above the dew point. Special thinning and application techniques may be required above or below normal conditions.

Carboguard 2929 Gloss Finish

PRODUCT DATA SHEET



CURING SCHEDULE

Curing Details	<ul style="list-style-type: none">• 10°C: 12 hours to handle; 24 hours to recoat*; 14 days final cure• 16°C: 10 hours to handle; 24 hours to recoat*; 10 days final cure• 24°C: 8 hours to handle; 24 hours to recoat*; 7 days final cure• 32°C: 4 hours to handle; 12 hours to recoat*; 5 days final cure
	<p>These times are based on a 50 micron dry film thickness. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure.</p> <p>*Maximum recoat times are indefinite. Surface must be clean and dry. As part of good painting practice it is recommended to test for adhesion by wiping the surface with Thinner #25. If the film shows a slight "tack" the surface is suitable for recoating without extensive surface preparation such as abrading</p>

CLEANUP & SAFETY

Cleanup	Use Thinner #2, #12 or acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.
Safety	Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Hypersensitive persons should wear protective clothing, gloves and use protective cream on face, hands and all exposed areas.
Ventilation	When used as a tank lining or in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapour concentration from reaching the lower explosion limit for the solvents used.
Caution	This product contains flammable solvents. Keep away from sparks and open flames.

PACKAGING, HANDLING & STORAGE

Shelf Life	Part A: 24 months @ 24°C Part B: 24 months @ 24°C *Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.
Storage Temperature & Humidity	4-38°C 0-95%
Flash Point (Setaflash)	Mix: 27°C
Storage	Store indoors and KEEP DRY
Packaging	1¼ litre & 5 litre kits

WARRANTY

Manufactured and / or distributed in Australia & New Zealand by Altex Coatings under license to Carboline Company. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Altex Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ALTEX COATINGS OR CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. Altex Terms and Conditions of Trade, available at www.altexcoatings.com, apply in respect of all coating products and materials supplied, including samples.