

Selection & Specification Data

| | |
|----------------------------------|---|
| Generic Type | Waterborne Acrylic |
| Description | Specialized high solids filler used for sealing/filling masonry surfaces subject to both aggressive and mild environments. Unique formulation allows for topcoating with conventional or high-performance finishes. May be used as a block-filler where LEED-compliant flats and non-flat primers and finishes are required. |
| Features | <ul style="list-style-type: none"> ▪ High solids with excellent filling properties ▪ Dry heat resistance to 200°F ▪ Wet heat resistance to 120°F ▪ Block filler for alkyds, acrylics and epoxies ▪ Single component ▪ Low odor; low VOC ▪ Suitable for use in USDA inspected facilities ▪ Applicable for LEED projects as a block filler (not considered a thin-film paint) |
| Gloss | Not applicable (block filler) |
| Color | White (S800) |
| Topcoats | Topcoat with flat or non-flat primers or finishes such as acrylics, epoxies, polyesters depending on service |
| Dry Film Thickness | 12.0 mils (300 microns) Second coat may be required on rough or extremely porous surfaces to attain pinhole-free surface. |
| Solids Content | By Volume: 54% ± 2% |
| Theoretical Coverage Rate | 72 ft ² @ 12 mils (1.8 m ² /l @ 300 microns) Allow for loss in mixing, application and rough or porous surfaces. |
| VOC Values | As supplied: 0.5 lbs/gal (60 g/l) These are nominal values. EPA Method 24: 0.8 lbs/gal (96 g/l) |
| Dry Temp. Resistance | Continuous: 170°F (76°C) Non-Continuous: 200°F (93°C) Slight discoloration is observed above 170°F (76°C). |
| Limitations | <ul style="list-style-type: none"> ▪ Do not apply to surfaces that will exceed 160°F (71°C) in service. ▪ Do not use on floors or in immersion service. ▪ Do not apply to damp or wet surfaces. |

Substrates & Surface Preparation

| | |
|-----------------|---|
| General | Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. |
| CMU | Mortar joints should be thoroughly cured for a minimum of 15 days at 75°F (24°C) and 50% relative humidity or equivalent. |
| Concrete | Concrete must be cured 28 days at 75°F (24°C) and 50% relative humidity or equivalent. Laitance, form oils, curing agents, and surface hardeners must be removed by suitable method before coating application. |

Sanitile 100

Application Equipment

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

General guidelines:

Spray Application (General) The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco. Backrolling is required for all spray applications to ensure adequate filling of surface irregularities.

Pressure Pot Unit: Bottom outlet with dual regulators
Material Hose: 25' of 3/4" I.D. min.
Air Hose: 25' of 1 1/2" I.D. min.
Spray Gun: Heavy duty mastic type
Fluid Tip: .125"
Air Cap: .125" Round

Low Pressure Pneumatic Unit: 10:1 min. with evenflo regulator
Material Hose: 50' of 1" I.D. min.
Air Hose: 50' of 1/2" I.D. min.
Spray Gun: Heavy duty mastic type
Fluid Tip: .125"
Air Cap: .125" Round
Teflon packings are recommended and are available from the manufacturer.

Roller Use 9"-12" roller with a phenolic core. The roller nap will depend on the texture of the substrate to be coated. Apply with full strokes and avoid re-rolling.

Mixing & Thinning

Mixing Power mix until uniform in consistency. Avoid excessive air entrapment.

Thinning Normally not required. May be thinned up to 6 oz/gal with clean potable water for spray application. Material is ready to apply as supplied. Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.

Cleanup & Safety

Cleanup Use potable water, followed with a solvent flush to dry equipment. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

Safety Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Use adequate ventilation and wear gloves or use protective cream on face and hands if hypersensitive. Keep container closed when not in use.

Application Conditions

| Condition | Material | Surface | Ambient | Humidity |
|-----------|------------------------|------------------------|------------------------|----------|
| Normal | 55°-90°F (13°-32°C) | 55°-90°F (13°-32°C) | 55°-95°F (13°-35°C) | 40-60% |
| Minimum | 50°F (10°C) | 50°F (10°C) | 50°F (10°C) | 0% |
| Maximum | 95°F (35°C) | 95°F (35°C) | 95°F (35°C) | 85% |

Do not apply when the surface temperature is less than 5°F (3°C) above the dew point. Do not apply if temperatures are expected to drop below 45°F (10°C) within 24 hours of application. Water base products are sensitive to moisture during cure. Do not apply to frozen block or any masonry surface that has not completely thawed and avoid application in direct sunlight if possible. Special application techniques may be required above or below normal application conditions.

Curing Schedule

| Surface Temp. & 50% Relative Humidity | Dry to Touch | Dry to Recoat/ Topcoat with Water Base | Dry to Topcoat with Solvent Base |
|---------------------------------------|--------------|--|----------------------------------|
| 75°F (24°C) | 0.5 Hour | 18 Hours | 48 Hours |

These times are based on a 12.0 mil (300 micron) dry film thickness. Higher film thicknesses, insufficient ventilation, high humidity or cooler temperatures will require longer cure times.

*Sanitile 100 may be recoated with itself in 60 min. at 75°F.

Packaging, Handling & Storage

Shipping Weight (Approximate) 1's 16 lbs (7 kg) 5's 76 lbs (35 kg)

Flash Point (Setflash) >200°F (93°C)

Storage (General) Store Indoors. **Keep from Freezing**

Storage Temperature & Humidity 40° -110°F (4°-43°C)
0-90% Relative Humidity

Shelf Life 24 months at 75°F (24°C)

***Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.**



350 Hanley Industrial Court, St. Louis, MO 63144-1599
314/644-1000 314/644-4617 (fax) www.carboline.com

An **RPM** Company

December 2007 replaces April 2003

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Carboline® and Sanitile® are registered trademarks of Carboline Company.