

SELECTION & SPECIFICATION DATA

Generic Type	A petrolatum marine tape
Description	<p>Carbowrap Marine Tape is a non-woven bonded synthetic fabric, fully impregnated and coated with natural petroleum based compounds and inert fillers. It is chemically inert, does not polymerize or oxidize, retains water resistance and dielectric properties over an indefinite period, and contains a highly effective anti-bacterial agent to protect the substrate from microbial corrosion activities. This tape is designed for application underwater, near the splash zone, or on substrates in a corrosive marine environment. Carbowrap Marine Tape is part of the Carbowrap system developed for the protection of metal surfaces in severe environments and difficult to protect applications.</p> <p>The Carbowrap System is designed to be applied over hand or power wire brushed surfaces for above ground, buried, and underwater applications. The typical system involves priming the surface with a paste (Carbowrap Marine Paste), profiling around irregular shapes with a mastic compound (Carbowrap Mastic), and wrapping with a petroleum tape (Carbowrap Tape A, B, C or Marine Tape). An optional overwrap tape (Carbowrap Overwrap) is used for additional mechanical or electrical resistance.</p> <p>*Please consult the data sheets of the additional system products for additional information and instructions.</p>
Features	<ul style="list-style-type: none"> • Contain no VOC's • Resists harsh chemical exposures • Will not crack or harden over time • Application in any weather • Provides an impermeable protective layer • No special tools required for application • Complies with AWWA C217 specification • Provides excellent protection against chemical splash or fume attack • Tensile Strength: 45 lbs/in • Water Vapor Permeability: 0.12 g/m² per 24 hours • Service Temperature: 131 °F (55 °C)
Primer	<ul style="list-style-type: none"> • Carbowrap Marine Paste • Carbowrap Mastic on irregular surfaces (optional)
Typical Uses	<p>Carbowrap Tape System is used for the protection of: piping, valves, pumps, connectors, flanges, bolt heads or any other difficult to protect object. The system is also used in applications where surface preparation is minimal or inadequate for coatings; or where the weather or ambient conditions are such that other methods are not practical.</p>
Recommended Thickness	50.0 mils (1270 microns)
Protection Mechanism	<p>The Carbowrap system is very simple in its approach to corrosion control and application for long term service. These petrolatum-based products will totally encapsulate an object such as a pipe or pipe flange and seal it off from atmospheric moisture and oxygen, thereby preventing corrosion of the metal substrate. The petrolatum material is inherently acid and caustic resistance, and has outstanding moisture resistance. The system remains flexible indefinitely and as long as the wrap is not broken exposing the metal substrate, it will continue to perform for extended periods of time.</p>
Topcoats	Carbowrap Overwrap Tape (optional - for additional protection)

Carbowrap Marine Tape

PRODUCT DATA SHEET



SUBSTRATES & SURFACE PREPARATION

General	<p>Remove all contaminants such as dirt, oil, scale, and excessive moisture. Remove all loose paint, rust, or other residue by hand or power tool in accordance with SSPC - SP2 or 3.</p> <p>All surfaces should be evenly coated with Paste to fill any voids or surface irregularities and to ensure good contact of the tape.</p> <p>*See separate application instructions</p>
----------------	--

APPLICATION PROCEDURES

Application	<p>The Carbowrap Tape system is applied over minimally prepared steel surfaces (see Substrates and Surface Preparation).</p> <ol style="list-style-type: none">1. The paste is first applied using a stiff brush or hand applied using protective gloves over the entire surface to be protected.2. The Carbowrap Profiling Mastic may be used as needed to contour irregular geometries and fill voids that might result in air gaps when the tape is applied. The mastic is packaged as a "block" of material that can be hand-molded and shaped to fit the item being protected (flanges, valves, etc).3. The Carbowrap Tape is then applied using a wrapping technique around the substrate (pipe, flange, etc) using a 55% overlap. The edges of the overlap are to be smoothed over to provide a smooth transition and final appearance. The tape may be cut to varying lengths as needed to completely encapsulate the item being protected.4. The Carbowrap Overwrap Tape is then applied (optional) to provide an additional barrier to provide a more pleasing appearance, for color, for ease of cleaning (prevents dirt build-up) or to help seal-in the petrolatum material from coming in contact with personnel. (Note: The petrolatum remains soft and has a grease-like feel).
--------------------	--

PACKAGING, HANDLING & STORAGE

Packaging	<u>2" x 33' Roll</u> <ul style="list-style-type: none">• # Rolls per Carton: 36• Approx. Weight: 60 lbs
	<u>3" x 33' Roll</u> <ul style="list-style-type: none">• # Rolls per Carton: 24• Approx. Weight: 60 lbs
	<u>4" x 33' Roll</u> <ul style="list-style-type: none">• # Rolls per Carton: 18• Approx. Weight: 60 lbs
	<u>6" x 33' Roll</u> <ul style="list-style-type: none">• # Rolls per Carton: 12• Approx. Weight: 60 lbs

Shelf Life	<p>36 months at 75 °F (24 °C)</p> <p>Indefinite when kept at recommended storage conditions and in original unopened containers.</p>
-------------------	--

Flash Point (Setaflash)	464 °F (240 °C)
--------------------------------	-----------------



Carbowrap Marine Tape

PRODUCT DATA SHEET

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.