

SELECTION & SPECIFICATION DATA

Generic Type	Epoxy
Description	A two component, 100% solids product to minimize shrinkage and for laminating with fiberglass for a 62 mil lining system. A chemical resistant epoxy coating with exceptional adhesion to various substrates. Excellent resistance to petroleum products, alkalies, salts, organic solvents and gases.
Typical Uses	As a resin binder for reinforcing fiberglass mat or chopped fiberglass to produce a protective coating and lining, where excellent chemical resistance is required for the protection of interior tank bottoms exposed to sour crude, gasoline, military fuel, salt water and other petroleum products. Also, for the protection of exterior tank roofs under severe chemical exposures.
Color	Blue (0100)
Finish	Gloss
Dry Film Thickness	62 mils (1575 microns) with fiberglass
Solids Content	By Volume 100% +/- 2%
Coverage Rate	With Glass: 25 ft ² /gal (0.61 m ² /l)
Theoretical Coverage Rate	1604 ft ² /gal at 1.0 mils (39.4 m ² /l at 25 microns) 26 ft ² /gal at 62.0 mils (0.6 m ² /l at 1550 microns) Allow for loss in mixing and application.
VOC Values	As Supplied : 0 Calculated
Dry Temp. Resistance	Continuous: 250°F (121°C)
Temperature Resistance (Immersion)	190°F (88°C)
Topcoats	Alkyds, Epoxies, Polyurethane (Inorganic Zinc is not recommended)

SUBSTRATES & SURFACE PREPARATION

General | Near White Sandblast SSPC-SP10-63.

PERFORMANCE DATA

Test Method	Results
Adhesive Strength (lbs x 10 ³)	1.6-2.7
Compressive Strength (psi x 10 ³)	50-90
Flexure Strength (psi x 10 ³)	45-80
Hardness (Rockwell M)	105-120
Shear Strength (psi x 10 ³)	17-22
Tensile Strength (psi x 10 ³)	33-50

American Coatings TL-1

PRODUCT DATA SHEET



MIXING & THINNING

Thinning	DO NOT THIN
Ratio	2:1 by volume (A:B)
Pot Life	45-60 minutes @ 77°F (25°C)
	Pot life accelerates greatly at elevated temperatures

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Plural Component Airless Spray	Pump Ratio: 30:1
	Air Supply (in): 100 psi
	Hose Diameter (ID): 1/4" (0.64 cm)
	Hose Length: 75' (22.9 m)
	Tip Size: 0.027" (0.69 mm)
	Atomization Pressure: 2,400 psi

APPLICATION CONDITIONS

Condition	Ambient
Minimum	50°F (10°C)

Do not apply if temperature is below 50°F (10°C) and/or above 85% relative humidity.

CURING SCHEDULE

Surface Temp.	Dry Hard	Maximum Recoat Time
77°F (25°C)	18 Hours	24 Hours

Curing Details | Catalytic cure

CLEANUP & SAFETY

Safety | Keep away from heat, sparks or flame. Use with adequate ventilation. Do not breathe vapors or spray mist. Wear an appropriate, properly fitted respirator during and after application unless air monitoring demonstrates vapor/mist levels are below applicable limits.

WARNING! COMBUSTIBLE. HARMFUL IF INHALED. CAUSES IRRITATION

PACKAGING, HANDLING & STORAGE

Packaging	Part A: Fives Part B: Fives
	UN No. 1263
Shelf Life	1 year



PACKAGING, HANDLING & STORAGE

Shipping Weight (Approximate) | Part A: 52.5 lbs (23.8 kg)
Part B: 45.5 lbs (20.6 kg)

Flash Point (Setaflash) | Part A: >200°F (93°C)
Part B: >200°F (93°C)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.