

SELECTION & SPECIFICATION DATA

Generic Type	One component high solids non-skid alkyd
Features	<ul style="list-style-type: none"> • Non-Slip Deck Coating • Easy One Coat High Build Coverage • Excellent Adhesion to Steel & Concrete • Good Corrosion Resistance • Outstanding wear resistance • Self-priming over most existing coatings • Very Low Haps
Color	White, Black, Grey, Brown
Finish	<ul style="list-style-type: none"> • Eggshell • Textured
Dry Film Thickness	10 - 30 mils (254 - 762 microns) per coat Do not exceed 40 mils (1016 microns)
Typical Uses	<ul style="list-style-type: none"> • Ship/Barge Decks • Railcar Walk-ways • Offshore installations • Drilling Rigs • Power Plants • Chemical Processing Plants
Solids Content	By Volume 60% +/- 3% These are nominal values and may vary slightly with color.
Theoretical Coverage Rate	962 ft ² /gal at 1.0 mils (23.6 m ² /l at 25 microns) 96 ft ² /gal at 10.0 mils (2.4 m ² /l at 250 microns) 32 ft ² /gal at 30.0 mils (0.8 m ² /l at 750 microns) Allow for loss in mixing and application.
VOC Values	As Supplied : Per EPA Method: 2.8 lbs / gal (336 g/l)
Viscosity	105 KU's +/- 10 KU's

MIXING & THINNING

Mixing	Agitate thoroughly. If necessary, reduce up to 15%
Thinning	None required Contact Carboline representative for recommendations.

APPLICATION PROCEDURES

General	Spray, Trowel, Pour or roll
----------------	-----------------------------

Railplex[®] 2.8 LH Non-Skid

PRODUCT DATA SHEET



CURING SCHEDULE

Surface Temp.	Dry to Touch	Dry to Handle
77°F (25°C)	1 Hour	90 Minutes

PACKAGING, HANDLING & STORAGE

Shelf Life | 24 months

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.