

## SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	Aliphatic Polyaspartic
<b>Description</b>	This fast-cure, high-build polyaspartic coating provides good corrosion protection plus long term weatherability in just one coat. It can be applied direct to metal (DTM). For improved corrosion protection it can be applied over approved primers including Carbozinc 859. These 1 - 2 coat systems can eliminate the need for typical primers and/or intermediate coats to significantly speed up the painting process. Suitable for use in USDA inspected facilities.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Fast cure with good pot life - speeds the painting process</li> <li>• High build, up to 10 mils DFT per coat</li> <li>• Can be applied direct to metal (DTM)</li> <li>• Excellent corrosion protection - ISO 12944-6 C3 Low, DTM; C5 High over Carbozinc 859</li> <li>• Excellent corrosion protection over phosphatized carbon steel - ISO 12944-6 C3 High</li> <li>• Excellent weathering - SSPC Ctg. Spec. No. 39 Level 3A (highest level)</li> <li>• 1 - 2 coats instead of 2 - 3 coats saves significant time, labor and money</li> <li>• Excellent durability - abrasion and impact resistant</li> <li>• Low VOC and low HAPS</li> <li>• Indefinite recoatability</li> </ul>
<b>Color</b>	1864 (White), S800 (White), C703 (Grey), C705 (Light Grey), C900 (Black). Other colors are available on request. Contact your Carboline Representative for availability.
<b>Gloss</b>	Gloss
<b>Primer</b>	Self-priming, DTM, for many applications. For more severe service use with one of the following approved Carboline primers: Carbozinc 11 Series; Carbozinc 859; Carbozinc 608 HB; Carbozinc 808; Carboguard 635 Series; or Carboguard 8922 Series.  Contact Carboline for recommendations.
<b>Dry Film Thickness</b>	6 - 10 mils (152 - 254 microns) per coat  Can be applied at 4 - 5 mils DFT (102 - 127 microns) when applied over approved primer(s).
<b>Solids Content</b>	By Volume 69% +/- 2%
<b>HAPs Values</b>	0.03 lbs/solid gallon.  This value may vary by color.
<b>Theoretical Coverage Rate</b>	1107 ft <sup>2</sup> /gal at 1.0 mils (27.2 m <sup>2</sup> /l at 25 microns) 184 ft <sup>2</sup> /gal at 6.0 mils (4.5 m <sup>2</sup> /l at 150 microns) 111 ft <sup>2</sup> /gal at 10.0 mils (2.7 m <sup>2</sup> /l at 250 microns) Allow for loss in mixing and application.
<b>VOC Values</b>	<b>As Supplied</b> : 2.02 lbs/gal (242 g/l)  These values may vary by color.
<b>Dry Temp. Resistance</b>	Continuous: 200°F (93°C) Non-Continuous: 250°F (121°C)  Discoloration may occur at temperatures near 200 °F, 93 °C.

### SUBSTRATES & SURFACE PREPARATION

<b>General</b>	Clean to remove all contaminants per SSPC-SP 1.
<b>Steel</b>	Minimum Commercial Blast Clean per NACE No. 3/SSPC-SP 6 with a 2.0 - 3.0 mil (50 - 75 micron) anchor profile for maximum protection.
<b>Galvanized Steel</b>	Clean per SSPC-SP 16 with 2.0 - 3.0 mils (50 - 75 micron) anchor profile or prime as recommended by your Carboline Sales Representative. Refer to the specific primer's Product Data Sheet for substrate preparation requirements.
<b>Phosphatized Steel</b>	Clean to remove all contaminants per SSPC-SP 1.
<b>Non-Ferrous Metals</b>	Clean per SSPC-SP 16 with 2.0 - 3.0 mils (50 - 75 microns) anchor profile or prime as recommended by your Carboline Sales Representative. Refer to the specific primer's Product Data Sheet for substrate preparation requirements.

### MIXING & THINNING

<b>Mixing</b>	Power mix separately, then combine and power mix thoroughly.
<b>Thinning</b>	Not normally required. Can be reduced up to 6 oz/gal with Thinner 242 E, Thinner 236 E, or Thinner 225 E. Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.
<b>Ratio</b>	2:1 (Part A to Part B)
<b>Pot Life</b>	2 hours at 75 °F (24 °C) and less at higher temperatures. Pot life ends when coating becomes too viscous to use. Moisture contamination will shorten pot life and cause gellation. Remove any skin that may form on top of the mixed product in the container.

### APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

<b>Spray Application</b>	It may be necessary to make adjustments in spray techniques since wet film thickness is easily and quickly achieved. The following spray equipment has been found suitable and is available from various manufacturers.
<b>Conventional Spray</b>	Pressure pot equipped with dual regulators, minimum 3/8" I.D. material hose, 0.070" I.D. fluid tip and appropriate air cap.
<b>Airless Spray</b>	<ul style="list-style-type: none"><li>• Pump Ratio: 30:1 (min.)</li><li>• Volume Output: minimum 2.5 gpm (9.5 l/min.)</li><li>• Airless Hose: 3/8" I.D. min. (9.5 mm min.)</li><li>• Tip Size: 0.013 - 0.019" (0.33 - 0.48 mm)</li><li>• Output PSI: 2,200-2,800 psi (155 - 197 kg/cm<sup>2</sup>)</li><li>• Filter Size: 60 mesh</li><li>• PTFE packings are recommended and available from the pump manufacturer.</li></ul>
<b>Brush &amp; Roller (General)</b>	Recommended for small areas or touch-up only. Multiple coats may be required to obtain desired appearance, recommended dry film thickness and adequate hiding. Avoid excessive brushing and rolling. For best results, tie-in within 10 minutes at 75 °F (24 °C).

## APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	40°F (4°C)	35°F (2°C)	35°F (2°C)	10%
Maximum	90°F (32°C)	140°F (60°C)	110°F (43°C)	95%

Substrate temperatures must be 5°F (3°C) above the dew point. Caution: this product reacts with moisture in order to complete the final cure. Relative humidity below 30% will slow cure time.

## CURING SCHEDULE

Surface Temp.	Dry to Touch	Dry to Handle or Recoat	Final Cure General
35°F (2°C)	2 Hours	8 Hours	7 Days
40°F (4°C)	1.5 Hours	6 Hours	7 Days
50°F (10°C)	50 Minutes	4 Hours	7 Days
75°F (24°C)	30 Minutes	1 Hour	4 Days
90°F (32°C)	20 Minutes	45 Minutes	2 Days

These times are based on 50% relative humidity (RH). RH lower than 50%, higher film thickness, insufficient ventilation and/or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure. Excessive humidity and/or condensation on the surface during curing can interfere with the cure, can cause micro-foaming and may result in loss of sheen and/or discoloration. Maximum recoat times are indefinite. As part of good painting practice it is recommended to first test for adhesion by wiping the surface with Thinner 76 or one of the other solvents listed for thinning. If the film shows a slight "tack" the surface is suitable for recoating without abrading to create profile.

## CLEANUP & SAFETY

<b>Cleanup</b>	Use Thinner 2, Thinner 225 E or Acetone. In case of spillage, dispose of in accordance with local applicable regulations.
<b>Safety</b>	Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions. Use adequate ventilation. Keep container closed when not in use.
<b>Ventilation</b>	When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not able to monitor levels, use MSHA/NIOSH approved respirator.

## PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	<ul style="list-style-type: none"> <li>• Part A: Minimum 24 months at 75 °F (24 °C)</li> <li>• Part B: Minimum 24 months at 75 °F (24 °C)</li> </ul> <p>Shelf life: keep at recommended storage conditions and in original unopened containers.</p>
<b>Storage Temperature &amp; Humidity</b>	40 -110 °F (4-43 °C), 0-90% Relative Humidity
<b>Storage</b>	<p>Store indoors.</p> <p>This product is solvent based and not affected by excursions below these published storage temperatures, down to 10 F, for a duration of no more than 14 days. Always inspect the product prior to use to make sure it is smooth and homogeneous when properly mixed.</p>

# Carboquick® 201

## PRODUCT DATA SHEET

---



## PACKAGING, HANDLING & STORAGE

---

**Shipping Weight (Approximate)** | • 0.75 gallon kit: 10.25 lbs (4.65 kg)  
• 3 gallon kit: 41.0 lbs (18.6 kg)

**Flash Point (Setaflash)** | • Part A: 50°F, (10°C)  
• Part B: 80°F, (27°C)

## WARRANTY

---

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.