

SELECTION & SPECIFICATION DATA

| | |
|----------------------------------|--|
| Generic Type | Aliphatic Acrylic Polyurethane |
| Description | Thin film, high gloss finish with exceptional weathering performance characteristics. Used extensively in virtually all industrial markets, 134 LV provides a smooth, durable finish that has superior resistance to corrosion, abrasion and chemical exposure. |
| Features | <ul style="list-style-type: none"> • High solids, low VOC content • Excellent weatherability • Exceeds SSPC Paint 36 specification for a Level 3 urethane • Available in all Carboline colors including metallic-pigmented colors • Excellent flow characteristics allow for application by spray or roller • Superior impact and abrasion resistance • Indefinite recoatability • VOC compliant to current AIM regulations • Suitable for use in USDA inspected facilities |
| Color | Refer to Carboline Color Guide. Certain colors, particularly in non-lead safety oranges, reds and yellows may require multiple coats for adequate hiding. Check color suitability before use. |
| Finish | Gloss |
| Primer | Refer to Substrates & Surface Preparation. TopCoat with Carbothane® 134 Clear Coat when required |
| Dry Film Thickness | 2 - 3 mils (51 - 76 microns) per coat |
| Solids Content | By Volume 70% +/- 2% |
| Theoretical Coverage Rate | 1123 ft ² /gal at 1.0 mils (27.6 m ² /l at 25 microns) 561 ft ² /gal at 2.0 mils (13.8 m ² /l at 50 microns) 374 ft ² /gal at 3.0 mils (9.2 m ² /l at 75 microns) Allow for loss in mixing and application. |
| VOC Value(s) | Per EPA Method 24: 1.63 lbs./gal (195 g/l) 11 oz/gal of Thinner 214: 2.08 lbs./gal (249 g/l) 10 oz/gal of Thinner 215: 2.06 lbs./gal (247 g/l) 19 oz/gal of Thinner 236 E: 1.63 lbs./gal (195 g/l) 10 oz/gal of Thinner 25: 2.08 lbs./gal (249 g/l) These are nominal values and may vary slightly with color. Product contains VOC-exempt dimethyl carbonate. Check local regulations regarding product usage. |
| Dry Temp. Resistance | Continuous: 200°F (93°C) Non-Continuous: 250°F (121°C) Discoloration and loss of gloss is observed above 200°F (93°C). |
| Limitations | *The alignment of aluminum flakes in aluminum-filled finishes is very dependent on application conditions and techniques. Care must be taken to keep conditions as constant as possible to reduce variations in final appearance. It is also advisable to work from a single batch of material since variations can occur from batch to batch. For more information consult Carboline Technical Service Department. |

Carbothane 134 LV

PRODUCT DATA SHEET



SUBSTRATES & SURFACE PREPARATION

General | Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. For all surfaces prime with specific Carboline primer as recommended by your Carboline sales representative. Refer to the specific primer's Product Data Sheet for detailed requirements.

Galvanized Steel | Prime with specific Carboline primer as recommended by your Carboline Sales Representative. Refer to the specific primer's Product Data Sheet for substrate preparation requirements.

Previously Painted Surfaces | Lightly sand to roughen and degloss the surface. Existing paint must attain a minimum 3A rating in accordance with ASTM D3359 "X-Scribe" adhesion test.

PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

| Test Method | System | Results |
|-----------------------------------|---|--|
| ASTM B117 Salt Fog | Blasted Steel 1 ct Org Zinc 1 ct. Epoxy 1 ct 134 series | No rusting, blistering, loss of bond or any measurable creepage from the scribe after 3000 hours. |
| ASTM D2794 Impact Resistance | Blasted Steel 1 ct 134 series | 155 inch-pounds; no visible cracking. Gardner Impact Tester |
| ASTM D3359 Adhesion | Blasted Steel 1 ct. Epoxy 1 ct 134 series | 5A |
| ASTM D3363 Hardness | Blasted Steel 1 ct Epoxy 1 ct 134 series | H |
| ASTM D4060 Abrasion | Blasted Steel 1 ct 134 series | 70 mg. loss after 1000 cycles, CS17 wheel, 1000 gm. load |
| ASTM D4541 Adhesion | Blasted Steel 1 ct. Epoxy 1 ct. 134 series | 2562 psi Pneumatic |
| ASTM D4587 Accelerated Weathering | Blasted Steel 1 ct. Org. Zinc 1 ct. Epoxy 1 ct. 134 series | No rusting, blistering or loss of adhesion; less than 5% gloss loss after 3000 hours |
| ASTM G26 Weatherometer | Blasted Steel 1 ct. Epoxy 1 ct. 134 series | No blistering, rusting or cracking; gloss retention of 85%; color change of 1 McAdam unit after 2000 |

MIXING & THINNING

Mixing | Power mix Part A separately, then combine with Part B and power mix. DO NOT MIX PARTIAL KITS.

Thinning | Spray: Up to 11 oz/gal (8.5%) w/ Thinner 214, 10 oz/gal (7.5%) w/ Thinner 25 or 19 oz/gal (15%) w/ Thinner 236E
Roller: Up to 10 oz/gal (7.5%) w/ Thinner 215
Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied. Carboline Thinner 236E may also be used to minimize HAP and VOC emissions.

Ratio | 4:1 Ratio (A to B)

Pot Life | 4 Hours at 75°F (24°C) and less at higher temps. Pot life ends when coating becomes too viscous to use. MOISTURE CONTAMINATION WILL SHORTEN POT LIFE AND CAUSE GELLATION.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Spray Application (General) | This is a high solids coating and may require adjustments in spray techniques. Wet film thickness is easily and quickly achieved. Spray equipment is available from various manufacturers.

Conventional Spray | Pressure pot equipped with dual regulators, 3/8" I.D. minimum material hose, .070" I.D. fluid tip and appropriate air cap.

Airless Spray | *Pump Ratio: 30:1 (min.)
GPM Output: 3.0 (min.)
Material Hose: 3/8" I.D. (min.)
Tip Size: .015-.017"
Output PSI: 2100-2400
Filter Size: 60 mesh
*PTFE packings are recommended and available from the pump manufacturer.

Brush & Roller (General) | Multiple coats may be required to obtain desired appearance, recommended dry film thickness and adequate hiding. Avoid excessive re-brushing or rerolling. For best results, tie-in within 10 minutes at 75°F (24°C).

Brush | Recommended for touch-up only. Use a medium, natural bristle brush.

Roller | Use a short-nap mohair roller cover with phenolic core.

APPLICATION CONDITIONS

| Condition | Material | Surface | Ambient | Humidity |
|-----------|--------------|--------------|-------------|----------|
| Minimum | 50°F (10°C) | 35°F (2°C) | 35°F (2°C) | 0% |
| Maximum | 100°F (38°C) | 120°F (49°C) | 95°F (35°C) | 80% |

Industry standards are for substrate temperatures to be above 5°F (3°C) the dew point. Caution: This product is moisture sensitive in the liquid stage and until fully cured. Protect from high humidity, dew and moisture contact until fully cured. Application and/or curing in humidities above maximum, or exposure to moisture from rain or dew may result in a loss of gloss and/or microbubbling of the product.

CURING SCHEDULE

| Surface Temp. | Dry to Handle | Dry to Recoat & Topcoat w/ other finishes | Final Cure General |
|---------------|---------------|---|--------------------|
| 35°F (2°C) | 36 Hours | 36 Hours | 14 Days |
| 50°F (10°C) | 16 Hours | 16 Hours | 10 Days |
| 75°F (24°C) | 8 Hours | 8 Hours | 7 Days |
| 90°F (32°C) | 4 Hours | 4 Hours | 5 Days |

These times are based on a 2.0 mil (50 micron) dry film thickness. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure.

***Maximum recoat times are indefinite.** Surface must be clean and dry. As part of good painting practice it is recommended to test for adhesion by wiping the surface with Thinner 214 or 215. If the film shows a slight "tack" the surface is suitable for recoating without extensive surface preparation such as abrading.

Carboline Additive 101 can be used to accelerate the film forming process in this product for conditions outside of the parameters of this data sheet. Carboline Additive 101 is added at a rate of 1.0-2.0 oz per mixed gallon or a maximum of 6 oz per mixed five gallons. At this addition rate, Additive 101 will accelerate the cure rate of the urethane product between 25-40% depending on the

Carbothane 134 LV

PRODUCT DATA SHEET



CURING SCHEDULE

substrate temperature range and reduce the pot life of the product by approximately 40-50% of that stated on the product data sheet. With the use of Additive 101, this product will continue to cure at temperatures as low as 20°F (-7°C).

CLEANUP & SAFETY

| | |
|--------------------|---|
| Cleanup | Use Thinner 2 or Acetone. In case of spillage, dispose of in accordance with local applicable regulations. |
| Safety | Read and follow all caution statements on this product data sheet and on the SDS for this product and use personal protective equipment as directed. |
| Ventilation | When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not able to monitor levels, use MSHA / NIOSH approved respirator. |

PACKAGING, HANDLING & STORAGE

| | |
|---|---|
| Shelf Life | Part A: Min. 36 months at 75°F (24°C) Part B: Min. 24 months at 75°F (24°C) *Shelf Life: when kept at recommended storage conditions and in original unopened containers. |
| Storage Temperature & Humidity | 40° -110°F (4°-43°C) 0-80% Relative Humidity |
| Storage | Store Indoors. This product is solvent based and not affected by excursions below these published storage temperatures, down to 10°F, for a duration of no more than 14 days. Always inspect the product prior to use to make sure it is smooth and homogeneous when properly mixed. |
| Shipping Weight (Approximate) | 1 Gallon Kit - 13 lbs (5kg) 5 Gallon Kit - 57 lbs (26 kg) |
| Flash Point (Setaflash) | Carbothane 134 LV Part A: 60°F (16°C) Urethane Converter 811 Part B: 127°F (53°C) |

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.