

SELECTION & SPECIFICATION DATA

Generic Type	High solids epoxy amine
Description	A high solids epoxy cured with an amine curing agent. Formulated with particular attention to latex resin resistance with special modification to provide superior release properties. Plasite 9145 TFE is used as a second coat over Plasite 9145 when additional release properties are desired or required.
Features	Excellent resistance to a wide range of latex resin solutions
Typical Uses	Plasite 9145 TFE can be used as the second coat over Plasite 9145 for tank lining.
Color	White, Light Grey, & Light Blue
Finish	Semi-Gloss
Primer	Plasite 9145
Dry Film Thickness	6 - 7 mils (152 - 178 microns) per coat 12 - 15 mils (305 - 381 microns) total
Solids Content	By Volume 83% +/- 2%
Theoretical Coverage Rate	1331 ft ² /gal at 1.0 mils (32.7 m ² /l at 25 microns) 222 ft ² /gal at 6.0 mils (5.4 m ² /l at 150 microns) 89 ft ² /gal at 15.0 mils (2.2 m ² /l at 375 microns) Allow for loss in mixing and application.
VOC Values	As Supplied : 0.82 lbs/gal (99 g/l) ± 2% Plasite Thinner #71 : Thinned 10%: 1.37 lbs/gal (164 g/l) ± 2%

SUBSTRATES & SURFACE PREPARATION

General	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.
Steel	Immersion: SSPC-SP10 Non-Immersion: SSPC-SP6 Surface Profile: 2.0-3.0 mils (50-75 micron)
Concrete or CMU	Concrete shall be designed, placed, cured, and prepared per NACE No. 6/SSPC-SP 13, latest edition. Abrade to remove all laitance, loose concrete, etc. and to create surface profile in accordance with the appropriate ICRI CSP 5-7.

PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

Test Method	System	Results
Abrasion Resistance (ASTM D4060, Taber CS-17 Wheel, 1000 gram weight, 1000 cycles)*	Plasite 9145TFE (Two Coats)	19 milligrams average loss
Surface Hardness (ASTM Method D4366-84) König Pendulum (Glass Standard = 250 seconds)*	Plasite 9145TFE (Two Coats)	136 seconds
Thermal Shock	Plasite 9145TFE (Two Coats)	Unaffected 5 cycles, minus 70 °F to plus 212 °F (-57 °C to 100 °C)

***Note:** Above tests were conducted on film cured at 200 °F (93 °C).

MIXING & THINNING

Mixing	The curing agent is in a separate container and measured for the resin unit supplied. Thoroughly mix the pigments. After the pigment and liquid are thoroughly mixed, add the measured liquid curing agent slowly and mix completely with the resin.
Thinning	Plasite Thinner 71 is recommended. The amounts required will vary depending on air and surface temperatures and application equipment. Normal application temperatures and conditions will require the addition of approximately 5-10% thinner by volume with approximately 5% additional thinner added for each 5 °F (3 °C) of increased temperature. It is recommended that the amount of thinner included on each order amount to approximately 20% of the coating order.
Pot Life	1 hour at 70 °F (21 °C)

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Spray Application (General)	<p>All spray equipment should be thoroughly cleaned and the hose, in particular, should be free of old paint film and other contaminants. Apply a "mist" bonding pass. Allow to dry approximately one minute, but not long enough to allow film to completely dry. Apply crisscross multi-passes, moving gun at fairly rapid rate, maintaining a wet appearing film. Fast multi-passes may be applied until you have a film thickness of approximately 6-7 mil/150-175 microns (approximately 7-9 wet mil [175-225 microns]). Repeat this procedure for the second coat to obtain a 12-15 mil (300-350 microns) DFT. Remove all overspray by dry brushing or scraping if required. Equipment must be thoroughly cleaned immediately after use with Plasite thinner to prevent the setting of the coating.</p> <p>Note: Prior to spray application, stripe brush all welds, attachments and surface irregularities using Plasite 9145 / Plasite 9145 TFE thinned a minimum of 50% by volume with Plasite Thinner 71.</p>
Conventional Spray	<p>Use standard production-type spray guns. Air supply shall be uncontaminated. Adjust air pressure to approximately 50 lbs. at the gun and provide 5-10 lbs. of pot pressure. Adjust spray gun first by opening liquid valve and then adjusting air valve to give an 8-12 inch wide spray pattern with best possible atomization.</p>

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Airless Spray	When airless spray equipment is used, the recommended liquid pressure is 1500-1800 psi (1.03-1.24 MPa) with tip size from 0.017-0.021 inches. Thinning requirements are more than for conventional spray.
----------------------	---

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	50°F (10°C)	50°F (10°C)	50°F (10°C)	0%
Minimum	90°F (32°C)	125°F (52°C)	110°F (43°C)	80%

Substrate temperature should be 5 °F (3 °C) above the dew point.

Application and curing times are dependent upon ambient conditions. Consult Carboline's Technical Service Department if conditions are not within recommended guidelines.

CURING SCHEDULE

Surface Temp.	Dry to Recoat Minimum	Dry to Recoat Maximum	Tack Free	Cure for Service
70°F (21°C)	10 Hours	12 Hours	12 Hours	7 Days
90°F (32°C)	NR	NR	NR	5 Days

Surface will normally be tack-free in 10-12 hours at 70 °F (21 °C).

Overcoat time will vary both with temperature and ventilation and will require from 10-12 hours at 70 °F (21 °C) for enclosed spaces.

Within 24 hours after coating is applied, a minimum substrate temperature of 70 °F (21 °C) is required for proper polymerization.

Surface Temp.	Final Cure Immersion
150°F (66°C)	12 Hours
175°F (79°C)	6 Hours
200°F (93°C)	4 Hours

Listed above are a few curing schedules that may be used for time and work planning. Prior to raising the metal to the force curing temperature, it is necessary that an air dry time of 2-5 hours at temperatures from 70-100 °F (21-37 °C) be allowed. After the air dry period has elapsed, the temperature should be raised by approximately 30 °F (18 °C) each 30 minutes until the desired force curing temperatures are reached.

Note: The 200 °F (93 °C) cure will result in maximum hardness and release properties.

Final cure may be checked by exposing coated surface to MIBK for 10 minutes. If no dissolving and only minor softening of film occurs, the curing can be considered complete. The film should reharden after exposure if cured.

INSPECTION

Degree of surface preparation shall conform to appropriate specification as outlined in SURFACE PREPARATION section. Film thickness of each coat and total dry film thickness of coating system shall be determined with a nondestructive magnetic gauge, properly calibrated.

Refer to Plasite Bulletin PA-3, Section 3, for inspection requirements.

CLEANUP & SAFETY

Cleanup	Use Thinner 2, Thinner 71, or Acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.
----------------	---

CLEANUP & SAFETY

Safety | Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions. Use adequate ventilation. Keep container closed when not in use.

Ventilation | When used as a tank lining or in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved supplied air respirator.

PACKAGING, HANDLING & STORAGE

Packaging | **1 Gallon Kit**
Part A: 0.73 gallons (in a 1 gallon can)
Part B: 0.27 can Part B (in a 1 gallon can)
5 Gallon Kit
Part A: 3.63 gallons (in a 5 gallon can)
Part B: 1.35 gallons (in a 3 gallon can)

Shelf Life | 24 months at 70 °F (21 °C)

Shipping Weight (Approximate) | 11.5 lbs/gallon.

Flash Point (Setaflash) | Part A: 24 °F (-4.5 °C)
Part B: 219 °F (104 °C)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS. Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.