

## SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	100% solids epoxy
<b>Description</b>	High performance lining system designed for concrete. Semi-leveling coating which may be applied as an aggregate filled and/or reinforced coating system. Specially formulated to withstand some of industry's most aggressive chemicals.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Excellent resistance to chemical attack</li> <li>• Excellent abrasion and impact resistance</li> <li>• Exceptional thermal shock resistance</li> <li>• Superior bonding properties</li> <li>• High cohesive strength</li> <li>• Low permeability</li> <li>• Low odor</li> </ul>
<b>Primer</b>	Semstone 110 Primer <b>Note:</b> For substrates with out-gassing concerns use Carboguard 1340. Primer should be applied while the substrate temperature is decreasing.
<b>Dry Film Thickness</b>	30 mils (762 microns) per coat  Application thickness may vary from 30-150 mils (0.75-3.8 mm) depending on expected service conditions (i.e., chemical exposure, temperature, traffic load and other mechanical abuse, immersion service vs. splash-spill, etc.). Consult Carboline's Technical Service Department for specific thickness recommendations. In addition, coverage rates will be affected by the condition of the surface being coated (degraded vs. smooth, steel vs. concrete, etc.).
<b>Typical Uses</b>	<ul style="list-style-type: none"> <li>• Process Slabs</li> <li>• Tank Farm Floors</li> <li>• Chemical Loading and Unloading Areas</li> <li>• Spill Containment Areas</li> </ul>
<b>Solids Content</b>	By Volume 100% +/- 2%
<b>Coverage Rate</b>	Semstone 140 will cover 1,604 sq. ft. at 1 mil DFT per gallon (39.4 sq. m/l). With aggregate included application thickness may vary from 30 to 150 mils (0.75-3.8 mm), depending on expected service conditions and system design.  See Application Procedures for more specific coverage information.
<b>Theoretical Coverage Rate</b>	1604 ft <sup>2</sup> /gal at 1.0 mils (39.4 m <sup>2</sup> /l at 25 microns) 53 ft <sup>2</sup> /gal at 30.0 mils (1.3 m <sup>2</sup> /l at 750 microns) Allow for loss in mixing and application.
<b>VOC Values</b>	<b>As Supplied : 0</b>

## SUBSTRATES & SURFACE PREPARATION

<b>General</b>	Proper preparation is critical to ensure an adequate bond. The substrate <u>must</u> be dry and free of all wax, grease, oils, fats, soil, loose or foreign materials and laitance. Laitance and unbonded cement particles <u>must</u> be removed by mechanical methods, i.e., abrasive blasting or scarifying. Other contaminants may be removed by scrubbing with a heavy-duty industrial detergent and rinsing with clean water. For recommendations or additional information regarding substrate preparation, please contact Carboline's Technical Service Department.
----------------	---

### SUBSTRATES & SURFACE PREPARATION

---

<b>Steel</b>	Equipment base plates, etc. to be coated along with the concrete should be abrasive blasted to a near white metal finish, SSPC-10 or NACE-2, with a 1 to 2 mils anchor profile.
<b>Concrete or CMU</b>	Concrete should be properly cured for 28 days and have the following characteristics: Substrate tensile strength of at least 300 psi. pH in the range of 7 to 11. The surface <u>must</u> show open pores throughout and have a sandpaper texture.

### MIXING & THINNING

---

<b>Mixing</b>	Premix part A for 30 seconds using a Jiffy-type mixer. Pour part B into the part A and mix thoroughly for two minutes.
<b>Ratio</b>	4:1 A:B
<b>Pot Life</b>	45-60 minutes @ 75°F (24°C)* *Significantly less at elevated temperatures.

### APPLICATION PROCEDURES

---

<b>General</b>	<p><b>Broadcast Application (AFC-Broadcast)</b> Apply a base coat at the specified thickness using a squeegee or notched trowel. For a 60 mil (1.5mm) system apply a 25 mil(0.63mm) base coat and for a 125 mil(3.1mm) system apply a 50 mil(1.3 mm) base coat. Immediately after applying the base coat begin broadcasting the aggregate until a dry appearance is achieved. Note: the use of a 20/40 mesh aggregate is recommended. After the base coat has cured remove the loose aggregate. Apply a 10-15 mil(0.25-0.38 mm) top coat using a squeegee or roller.</p> <p><b>Blended Application (AFC-Blended)</b> After mixing part A and B split the mix into two 5-gallon buckets. While continuing to mix with a Jiffy mixer, slowly add the aggregate. Note: A 2:1 sand to liquid weight ratio will produce a trowel-like consistency. A 3:1 ratio will give a grout-like consistency. The use of 20/40 mesh silica aggregate is recommended. Apply the mixture at the desired thickness using a notched trowel. After the surface has cured it must be washed with soap and water prior to re-coating.</p> <p><b>Reinforced (AFRC-Broadcast)</b> A fiberglass scrim cloth may be added to the 125 mil broadcast system. Apply the cloth into the base coat prior to applying the aggregate.</p> <p><b>Reinforced (AFRC-Blended)</b> A fiberglass scrim cloth may be added to the 125 blended system. Apply a 25-35 mil base coat and then lay the scrim cloth into the base coat. <b>Note:</b> When using the Blended Application methods above a "vertical-grade" mix can be achieved by blending the base coat with Thixotrope D in a 1:1 by volume mix. Thixotrope D is sold separately.</p>
----------------	---

## APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	50°F (10°C)	50°F (10°C)	50°F (10°C)	0%
Maximum	90°F (32°C)	90°F (32°C)	90°F (32°C)	90%

Substrate temperature should be greater than 5°F (3°C) above dew point.

For optimal working conditions, substrate temperature must be between 60°F (15°C) and 80°F (27°C). Measure the surface temperature with a surface thermometer. Cold areas must be heated until the slab temperature is above 50°F (10°C). This will allow the material to achieve a proper cure. Also, a cold substrate will make the material stiff and difficult to apply. Warm areas or areas in direct sunlight must be shaded or arrangements made to work during evenings or at night. A warm substrate (60-80°F (15-27°C)) will aid in the material's workability; however, a hot substrate (80-100°F (27-37°C)) or a substrate directly in the sun will shorten the material's working time and can cause other phenomenon such as pinholing and bubbling.

If the temperature is expected to drop below 50°F (10°C) use Semstone 140 CT.

Consult Carboline Technical Service if conditions are not within the recommended guidelines.

## CURING SCHEDULE

Surface Temp.	Chemical Service	Dry to Touch	Firm
75°F (24°C)	36 Hours	12 Hours	24 Hours

\* And 50% relative humidity

## CLEANUP & SAFETY

<b>Cleanup</b>	MEK, Toluene or Xylene solvents are recommended for clean up of Semstone 140 material spills. Use these materials only in strict accordance with manufacturer's recommended safety procedures. Dispose of waste materials in accordance with government regulations.
<b>Safety</b>	The selection of proper protective clothing and equipment will significantly reduce risk to injury. Body covering apparel, safety goggles and impermeable gloves are highly recommended.
<b>Ventilation</b>	<ul style="list-style-type: none"> <li>The use of a NIOSH/MSHA approved respirator using a #TC-23C-738 organic vapor or a #TC-23C-740 organic vapor acid gas cartridge is mandatory.</li> <li>Use only with adequate ventilation.</li> </ul>

## PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	Part A: 24 months Part B: 24 months
<b>Storage Temperature &amp; Humidity</b>	Store all components between 50-75°F (10-24°C) Twenty-four hours before application, all components should be stored at 70-85°F (21-29°C) to facilitate handling
<b>Storage</b>	Store indoors, keep out of direct sunlight
<b>Shipping Weight (Approximate)</b>	1 gal unit: 11.2 lbs (5.1 kg) 5 gal unit: 54.1 lbs (24.6 kg)
<b>Flash Point (Setaflash)</b>	Part A: 350°F (177°C) Part B: 240°F (116°C)

### **WARRANTY**

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.