

---

## SELECTION & SPECIFICATION DATA

---

<b>Generic Type</b>	Clear Acrylic Latex
<b>Description</b>	Clear, high gloss acrylic latex. May be applied by dipping
<b>Finish</b>	High Gloss
<b>Dry Film Thickness</b>	1 mil (25 microns) per coat
<b>Solids Content</b>	By Volume 30% +/- 3% Solids by weight: 33% +/- 3%
<b>Coverage Rate</b>	Optimum Coverage: 455 sq ft/gal @ 1.0 mil
<b>Theoretical Coverage Rate</b>	481 ft <sup>2</sup> /gal at 1.0 mils (11.8 m <sup>2</sup> /l at 25 microns) Allow for loss in mixing and application.
<b>VOC Values</b>	<b>As Supplied</b> : 2.75 lbs/gal (330 g/l)

---

## SUBSTRATES & SURFACE PREPARATION

---

**General** | Brass, Copper, Aluminum

---

## MIXING & THINNING

---

**Thinning** | Reduce with water if needed

---

## APPLICATION PROCEDURES

---

**General** | Dip

---

## PACKAGING, HANDLING & STORAGE

---

**Nominal Weight** | 8.38 lbs/gal (1.00 kg/l)

**Flash Point (Setaflash)** | 150°F (66°C)

---

## WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.