

SELECTION & SPECIFICATION DATA

Generic Type	Silicone Rubber Finish
Description	For use as a high performance finish for surfaces in service from 300 °F (149 °C) to 800 °F (426 °C) with excellent resistance to thermal shock. It is typically used to prevent corrosion in service under insulation. For use over carbon steel, it can be applied over modified silicone primers or Carbozinc® 11 series.
Features	<ul style="list-style-type: none"> • Will air dry at ambient • Resistant to severe thermal shock
Color	Black only
Finish	Flat
Primer	Thermaline® 2977 Series, Thermaline 4765 Series or Carbozinc® 11 Series
Dry Film Thickness	1.5 - 2 mils (38 - 51 microns) per coat
Solids Content	By Volume 30% +/- 2%
Theoretical Coverage Rate	481 ft ² /gal at 1.0 mils (11.8 m ² /l at 25 microns) 321 ft ² /gal at 1.5 mils (7.9 m ² /l at 38 microns) 241 ft ² /gal at 2.0 mils (5.9 m ² /l at 50 microns) Allow for loss in mixing and application.
VOC Values	As Supplied : 5.1 lbs/gal. (611 g/l) Thinner 235 : 12.8 oz/gal (10%): 5.3 lbs/gal (635 g/l) Thinner 235 : 32 oz/Gal (25%): 5.5 lbs/gal (656 g/l)
Dry Temp. Resistance	Continuous: 800°F (427°C)

SUBSTRATES & SURFACE PREPARATION

General	All surfaces must be thoroughly cleaned to remove dirt, grease, mill scale, loose rust and any other contaminants that can reduce adhesion via SSPC-SP1 solvent cleaning with recommended surface preparation.
Aluminum	SSPC-SP 16
Ferrous Metal	Apply over properly applied and cured primer
Stainless Steel	SSPC-SP 16

MIXING & THINNING

Mixing	Thoroughly mix to a uniform consistency prior to use.
Thinning	Normally not required. May be thinned up to 32 oz/gal. (25%) by volume with Thinner 235 for "hot" applications exceeding 150 °F (66 °C) and for mist coating. Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Spray Application (General) | Conventional spray application is preferred.

Conventional Spray | Use DeVilbiss P-MBC, E-needle and tip, and a 704 air cap or equal. Use adequate air volume for proper equipment operation. Hold gun 10-12" from the surface and at right angles. Lap each pass 50%. Apply 5.0 wet mils to obtain desired dry film.

Brush & Roller (General) | Use only good quality brushes and roller covers where spray application is not permitted.

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	55°F (13°C)	40°F (4°C)	40°F (4°C)	0%
Maximum	95°F (35°C)	300°F (149°C)	120°F (49°C)	90%

This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions.

CURING SCHEDULE

Surface Temp.	Final Cure	Dry to Touch	Firm Set
77°F (25°C)	24 Hours	1 Hour	12 Hours

These times are based on a 2.0 mil (50 micron) dry film thickness. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure. While Thermaline 2954 is an ambient temperature-cure coating, optimum performance properties are achieved when final heat cure occurs at temperatures of 400 °F (204 °C) for a minimum of 2 hours.

CLEANUP & SAFETY

Cleanup | Use Thinner 2.

Safety | Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions. Use adequate ventilation. Keep container closed when not in use.

Ventilation | When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not able to monitor levels, use MSHA/NIOSH approved supplied air respirator.

PACKAGING, HANDLING & STORAGE

Shelf Life | Min. 24 months at 77 °F (25 °C)

*Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.

PACKAGING, HANDLING & STORAGE

Storage Temperature & Humidity | 40-100 °F (4-38 °C)
0-90% Relative Humidity

Shipping Weight (Approximate) | 1 Gallon: 10 lbs. (4.5kg)
5 Gallon: 46 lbs. (21kg)

Flash Point (Setaflash) | 71 °F (22 °C)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.