

SELECTION & SPECIFICATION DATA

Generic Type	Cleaning solution
Designation	<p>This is a Carboline Specialty Product</p> <p>Minimum order quantities and special pricing will apply in North America. Contact your Carboline Sales Representative for more details.</p>
Description	Plaskleen-A is a cleaning solution used in conjunction with Plasite 3070, 3070 L and 3076. When the surface to be coated has previously been in sulfuric acid service, Plaskleen-A must be used.
Coverage Rate	<p>One gallon of Plaskleen-A Concentrate to 10 gallons of tap water (total of 11 gallons of solution) will cover approximately 270 ft² (25.08 sq²) per each gallon of mixed solution (coverage may vary depending upon condition of steel).</p> <p>Note: Coverage information has been obtained through field experience. Plaskleen-A solution shall be applied after the steam cleaning of prebaking procedures and prior to final blast.</p>

MIXING & THINNING

Mixing	<ol style="list-style-type: none"> 1. Store Plaskleen-A Concentrate at room temperature. 2. Before diluting Plaskleen-A Concentrate, check for the following: Mix or shake Concentrate thoroughly making sure any solid residue is in solution. If Concentrate has been frozen, or is very cold, a crystalline mass will form. Allow Concentrate to reach room temperature and mix or shake into solution. 3. After Concentrate is in solution, while mixing add Concentrate (at a ratio of 10 gallons tap water to 1 gallon Plaskleen-A Concentrate) slowly to tap water and mix the diluted solution at least 5 minutes.
Ratio	One gallon of Plaskleen-A Concentrate to 10 gallons of tap water (total of 11 gallons of solution)

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Airless Spray	Plaskleen-A solution is applied with airless spray equipment with a minimum of 1800 psi liquid pressure. The objective is to thoroughly wet out and completely saturate all exposed surfaces.
----------------------	---

PACKAGING, HANDLING & STORAGE

Packaging	1 Gallon & 5 Gallon Units
Shipping Weight (Approximate)	<p>1 Gallon Unit - 10 lbs (4.5 kg)</p> <p>5 Gallon Unit - 50 lbs (22.7 kg)</p>

PLASKLEEN-A

PRODUCT DATA SHEET



WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS. Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.