

## SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	Solvent-free epoxy patching compound
<b>Description</b>	An epoxy based patching compound for filling surface defects and bugholes in concrete substrates. This product uses an epoxy resin and a unique, inert mineral filler to achieve a smooth non-slumping fill material. The system is formulated to improve the integrity and continuity of a prepared substrate, prior to the application of a coating or lining system.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Contributes toward satisfying credit for low emitting material under LEED 4.1</li> <li>• Meets SCAQMD Rule 1113 for VOC content</li> <li>• Vertical and overhead applications</li> <li>• Low odor</li> <li>• Meets all VOC requirements</li> </ul>
<b>Color</b>	Gray
<b>Primer</b>	Primer 67 series or Steri-Prime series
<b>Dry Film Thickness</b>	5 - 125 mils (127 - 3175 microns) DFT
<b>Solid(s) Content</b>	By Volume 100%
<b>Coverage Rate</b>	Coverage rate is dependent on the condition of the substrate.
<b>VOC Value(s)</b>	4 g/l
<b>Topcoats</b>	Topcoat selection will depend on exposure

## SUBSTRATES & SURFACE PREPARATION

<b>Steel</b>	<b>DO NOT USE ON STEEL FOR IMMERSION SERVICE</b> May be used as a pit or void filler on steel in ambient or atmospheric service.
<b>Concrete</b>	Refer to System Information Sheet or product data sheet of the topcoat where Scratch-Coat 300 is being used for concrete surface preparation requirements.

## PERFORMANCE DATA (TYPICAL VALUES)

Test Method	Results
Adhesion to Concrete ASTM D7234	Cohesion Failure of Concrete
Compressive Strength ASTM C579	2,000 PSI (13.8 MPa)

## MIXING & THINNING

<b>Mixing</b>	Mix the pre-measured units of Part A and Part B separately for approximately 2-3 minutes. The Part A is white in color and Part B is black. Mix until a uniform color is achieved. No color streaks should be present.
<b>Thinning</b>	DO NOT THIN

# Scratch-Coat 300

## PRODUCT DATA SHEET



### MIXING & THINNING

<b>Ratio</b>	2.6:1 by volume (A:B) DO NOT MIX PARTIAL KITS
	To prevent material waste and avoid damage to equipment, do not mix more material than can be used.
<b>Pot Life</b>	45 minutes @ 50°F (10°C) 25 minutes @ 75°F (24°C) 10 minutes @ 90°F (32°C)

### APPLICATION PROCEDURES

<b>General</b>	With all epoxies, after priming and before each additional coat, examine the surface for amine blush (oily film). If present, remove by washing with warm water and detergent.
<b>Trowel</b>	Though the Scratch-Coat 300 is a trowel or squeegee applied material, it is not intended to be utilized as a surface "coating". The compound should be spread firmly, forcing the material into voids and pinholes. Use the trowel blade to scrape excess material from flat, void-free surfaces. The consistency of the mortar provides excellent non-slumping characteristics for vertical or overhead use. This normally allows completion of the surface preparation following only one application. Allow the Scratch-Coat 300 to cure until firm before proceeding with the specified basecoat and topcoat. Excessive trowel marks and/or rough areas should be sanded smooth.

### APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	60°F (16°C)	50°F (10°C)	50°F (10°C)	0%
Maximum	80°F (27°C)	110°F (43°C)	110°F (43°C)	90%

Substrate temperature must be 5°F (3°C) above the dew point.

### CURING SCHEDULE

Surface Temp.	Minimum Recoat Time	Maximum Recoat Time
50°F (10°C)	12 Hours	72 Hours
75°F (24°C)	8 Hours	48 Hours
90°F (32°C)	4 Hours	24 Hours

If these recoat times are exceeded, sanding or abrasive blasting may be required before the next coat. Recoat times are dramatically reduced when coating is exposed to direct sunlight.

Application in direct sunlight may lead to blistering, pinholes, or wrinkling due to outgassing of air in the concrete and high substrate temperatures.

### CLEANUP & SAFETY

<b>Cleanup</b>	Use S-10 Cleaning Solvent or Carboline Thinner 2 to clean tools and equipment.
<b>Safety</b>	Read and follow all caution statements on this product data sheet and on the SDS. Employ normal safety precautions. Keep container closed when not in use.

---

## CLEANUP & SAFETY

---

<b>Ventilation</b>	Ventilation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. Use MSHA/NIOSH approved air respirators as needed.
<b>Caution</b>	Fire and explosion hazards: This product contains less than 1% volatile components, however, vapors are heavier than air and can travel long distances, ignite and flash back. Eliminate all Ignitions sources. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workers should be required to use non-ferrous tools and wear conductive and non-sparking shoes.

---

## PACKAGING, HANDLING & STORAGE

---

<b>Packaging</b>	<b>2 Gallon Kits:</b> Part A: 1.46 Gallons (in a 3.5 gal pail) Part B: 0.54 oz (in a 3.5 gal pail)
<b>Shelf Life</b>	Part A: 12 months @ 75°F (24°C) Part B: 12 months @ 75°F (24°C)  When properly stored in their original containers. Storage in direct sunlight or excessive heat will cause premature gelling and reduce working time and shelf life.
<b>Storage</b>	All products should be stored in a cool, dry area away from open flames, sparks or other hazards.  <b>Warning:</b> All Dudick products classified by DOT with either white, yellow or red labels must not be mixed or stored together as an explosive reaction can occur.
<b>Shipping Weight (Approximate)</b>	2 Gallon Kits: 17.5 lbs

---

## WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.