

SELECTION & SPECIFICATION DATA

Generic Type	100% solids multi-functional epoxy coating
Description	A high-solids, multi-functional epoxy coating for walls and ceilings. The unique hybrid binder provides high film integrity, and excellent chemical resistance required for prolonged substrate protection. It can be spray applied to a high film build in one or two coats to achieve a monolithic barrier for protecting substrates in aggressive environments.
Features	<ul style="list-style-type: none"> • Excellent chemical resistance • Good abrasion resistance • Can be applied at high film thicknesses to ceilings and walls • USDA Compliant • Anti-Microbial Agents are available as an option • Low emitting material • Low VOC • Low installation odor
Typical Uses	<ul style="list-style-type: none"> • High Containment Research Facilities • Clean Rooms • Food & Beverage Processing Facilities • Warehouses/Storage Areas • Manufacturing & Waste Water Treatment Plants • Maintenance Garages • Pharmaceutical & Research Facilities
Color	Available colors can be found in the Universal Color Pack section of Dudick Flooring Color Chart
Primer	Prime with Steri-Prime, Primer 67-series or others as recommended by Carboline Technical Service
Dry Film Thickness	15 - 20 mils (381 - 508 microns) per coat
Solids Content	By Volume 100%
Theoretical Coverage Rate	1604 ft ² /gal at 1.0 mils (39.4 m ² /l at 25 microns) 107 ft ² /gal at 15.0 mils (2.6 m ² /l at 375 microns) 80 ft ² /gal at 20.0 mils (2.0 m ² /l at 500 microns) Allow for loss in mixing and application.
VOC Values	As Supplied : 30 g/l
Chemical Resistance	<ul style="list-style-type: none"> • Decontamination Solutions • Dilute Inorganic Acids • Aliphatic Hydrocarbons • Sodium Hydroxide • Salt & Brine Solutions • Mineral Oils
Topcoats	Optional Sealers: If enhanced scuff and scratch resistance is desired, optional topcoat and urethane sealers are available. Consult your Dudick or Carboline representative or technical service for recommendations specific to the service environment.

Steri-Seal HB

PRODUCT DATA SHEET



SUBSTRATES & SURFACE PREPARATION

Concrete or CMU	Must be primed with Steri-Prime, Primer 67-series or others as recommended by Carboline Technical Service Concrete must be prepared mechanically to remove surface laitance. Oils, grease or other contaminant must be removed prior to surface preparation. Concrete must be free of curing compounds and form release agents (per SSPC SP-13/NACE No.6). Surface texture should be similar to 40-60 grit sandpaper or the visual standard, CSP 3 from the International Concrete Repair Institute (ICRI) with pea gravel exposed. The prepared surface shall have a minimum tensile strength of 250 PSI per ASTM D7234.
	All concrete substrates must be checked for moisture and pass the ASTM D4263 Plastic Sheet Test prior to product application.
Drywall & Plaster	Must be primed with Steri-Prime, Primer 67-series or others as recommended by Carboline Technical Service. Refer to the product data sheet for surface preparation requirements.
Metallic Substrates	SSPC SP-6 Commercial Blast or NACE No.3, minimum 2.0 mil profile.

PERFORMANCE DATA (TYPICAL VALUES)

Test Method	Results
Flame Spread ASTM D635	<5 mm / self extinguishing
Fungus Resistance	No growth
Specular Gloss Factor ASTM D523	85-90
Taber Abrasion ASTM D4060	60 mg
Tensile Bond Strength ASTM D7234	Cohesive failure of concrete

MIXING & THINNING

Mixing	Mechanically mix the Part A separately for 1-2 minutes to disperse any pigments or fillers which have settled prior to adding the Part B. Add the correct amount of Part B and mix until a uniform color is achieved.
Ratio	2.7:1 ratio by volume (A:B)
Pot Life	75 minutes @ 50°F (10°C) 50 minutes @ 75°F (23°C) 25 minutes @ 90°F (32°C)

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Airless Spray	Pump Ratio: 40:1 (min.) GPM Output: 2.5 (min.) Material Hose: 1/2" I.D. (min.) Tip Size: 0.015"-0.021" Output PSI: >3,000 PSI PTFE packings are recommended and available from the pump manufacturer.
----------------------	--

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	60°F (16°C)	50°F (10°C)	50°F (10°C)	0%
Maximum	80°F (27°C)	110°F (43°C)	110°F (43°C)	90%

Substrate temperature must be 5°F (3°C) above the dew point.

CURING SCHEDULE

Surface Temp.	Minimum Recoat Time	Maximum Recoat Time	Cure Time
50°F (10°C)	16 Hours	5 Days	4 Days
75°F (24°C)	10 Hours	3 Days	24 Hours
90°F (32°C)	6 Hours	2 Days	20 Hours

CLEANUP & SAFETY

Cleanup | Use S-10 Cleaning Solvent or Carboline Thinner 2 to clean tools and equipment.

Safety | Read and follow all caution statements on this product data sheet and on the SDS. Employ normal safety precautions. Keep container closed when not in use.

Ventilation | Ventilation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. Use MSHA/NIOSH approved air respirators as needed.

Caution | Fire and explosion hazards: This product contains less than 1% volatile components, however, vapors are heavier than air and can travel long distances, ignite and flash back. Eliminate all Ignitions sources. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workers should be required to use non-ferrous tools and wear conductive and non-sparking shoes.

PACKAGING, HANDLING & STORAGE

Packaging | **1 Gallon Kits:**
 Part A: 0.73 Gallons (in a 1 gal can)
 Part B: 0.27 Gallons (in a 1 gal can)

— **5 Gallon Kits:**
 Part A: 3.65 Gallons (in a 5 gal pail)
 Part B: 1.35 Gallons (in a 3.5 gal pail)

Shelf Life | Part A: 12 months
 Part B: 12 months

Storage | Warning: All Dudick products classified by DOT labels as either white, yellow or red labels must not be mixed or stored together as an explosive reaction may occur.
 Store all products in a cool, dry area away from open flames, sparks or other hazards.

Shipping Weight (Approximate) | 1 gallon kits: 16.1 lbs
 5 gallon kits: 61 lbs

Steri-Seal HB

PRODUCT DATA SHEET



WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS. Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.