

PRODUCT DATA SHEET

SELECTION & SPECIFICATION DATA

Generic Type 100% solids, self-leveling epoxy floor coating

Description

Steri-Flor UV is a multi-functional epoxy floor coating with increased UV stability compared to conventional epoxies.

It provides good resistance to common chemicals and daily traffic and may be used as a base/color coat, receiving coat, or grout coat for decorative broadcast floors.

- Meets SCAQMD Rule 1113 for VOC content
- · Low viscosity good wetting properties, approximately 500 cps mixed.

Features

- · Low installation odor, for use in occupied areas.
- · Stain resistance with excellent cleanability
- USDA compliant
- · Food processing floors
- · Laboratories
- **Typical Uses**
- Pharmaceutical plants · Wastewater treatment facilities
- Aisleways
- Warehouses

Clear

Color

May be pigmented by the end user by adding Universal Color Packs. Available colors can be found in the Dudick Flooring Color Chart

Finish Gloss

Primer

- Though Steri-Flor UV may be used without a primer, the use of Steri-Prime under Steri-Flor UV is strongly recommended to mitigate outgassing and promote higher adhesion.
- On properly cleaned and prepared, hydrocarbon saturated substrates use of Steri-Prime DTO.
- Contact your representative for other recommendations or more information.

Dry Film Thickness | 8 - 20 mils (203 - 508 microns) DFT

Solids Content | By Volume 100%

Theoretical Coverage Rate

1604 ft²/gal at 1.0 mils (39.4 m²/l at 25 microns) 200 ft²/gal at 8.0 mils (4.9 m²/l at 200 microns) 80 ft²/gal at 20.0 mils (2.0 m²/l at 500 microns) Allow for loss in mixing and application.

VOC Values As Supplied: 90 g/l

Limitations

This product contains an ultraviolet light inhibitor that allows it to perform better than traditional epoxies when exposed to to direct sunlight, however chalking and fading will occur if installed in a service environment with extended exposure.

- Dilute inorganic acids
- · Dilute alkali solutions

Chemical Resistance

- Cleaning & sanitizing solutions
- Mineral oils
- · Salt solutions

PRODUCT DATA SHEET



SELECTION & SPECIFICATION DATA

Topcoats

Optional topcoats available depending on exposure, increased UV stability, and durability requirements.

Contact your representative for more recommendations.

SUBSTRATES & SURFACE PREPARATION

Concrete: Concrete must be prepared mechanically to remove surface laitance. Oils, grease or other contaminant must be removed prior to surface preparation. Concrete must be free of curing compounds and form release agents. Water dropped on the surface should be readily absorbed. Surface texture should be similar to 60-80 grit sandpaper or in accordance with visual standards CSP 2-3 from ICRI. The prepared surface should have a nominal tensile strength of 250 PSI per ASTM D7234.

Concrete

All concrete substrates must be checked for moisture prior to primer application using the Plastic Sheet test, ASTM D4263.

Additional surface preparation will be required if the surface laitance not completely removed with first mechanical preparation, even if the minimum profile has been acheived.

If mechanical preparation exposes honeycombs or voids, These can be filled with Scratch-Coat 300. Consult your representative for system recommendations

MIXING & THINNING

Universal Color Packs can be added to Steri-Flor UV. Add 1 Universal Color Pack for every 2 gallons of Part A and mix, prior to adding the gallon of Part B.

Mixing

Combine Part A and Part B in a pail then stir mechanically for approximately 2-3 minutes to achieve a uniform color and consistency. Pour the Steri-Flor UV directly onto the prepared substrate.

If using plural component mixing and dispensing equipment, pre-mix Part A with optional Universal Color Packs before loading into the A-side of the pump. Ensure the equipment is set to dose at 2:1 by volume. Perform a ratio check. After assuring that the equipment is on proper ratio, set desired amount to dispense and pump it into a bucket to run out to the prepared substrate or pump directly onto the prepared substrate while when rolling the pump.

Ratio | 2:1

30-40 minutes at 75°F

Pot Life

The pot life of Steri-Flor UV system components will depend upon the temperature. To prevent material waste and avoid damage to equipment, do not mix more material then can be used according to the corresponding pot life data.

APPLICATION PROCEDURES

The mixed product should be spread to desired thickness with a flat or serrated squeegee. After spreading the material to the proper thickness, roll with a short nap roller to level.

Application

To terminate work, use duct tape to set a straight edge and remove the tape when the topping becomes lightly tacky. Start the next work period butting into this area. Permanent terminating lines should be made into the saw cuts in the concrete.



PRODUCT DATA SHEET

APPLICATION CONDITIONS

| Condition | Material | Surface | Ambient | Humidity |
|-----------|-------------|-------------|-------------|----------|
| Minimum | 60°F (16°C) | 50°F (10°C) | 50°F (10°C) | 0% |
| Maximum | 80°F (27°C) | 90°F (32°C) | 90°F (32°C) | 90% |

Substrate temperature must be 5°F above the dew point.

Application of Steri-Flor UV in direct sunlight may lead to blistering, pinholes, or wrinkling due to outgassing of air in the concrete and high substrate temperatures. Double priming, shading or evening application may be required. Consult with your representative for more information.

CURING SCHEDULE

| Surface Temp. | Maximum Recoat Time | Minimum Recoat Time | Cure Time |
|---------------|---------------------|---------------------|-----------|
| 50°F (10°C) | 24 Hours | 17 Hours | 3 Days |
| 75°F (24°C) | 24 Hours | 8 Hours | 24 Hours |
| 90°F (32°C) | 24 Hours | 6 Hours | 20 Hours |

Important: With all epoxies after priming and before each additional coat, examine the surface for amine blush (oily film). If present, remove by washing with warm water and detergent.

TESTING / CERTIFICATION / LISTING

General

Dudick flooring systems can be built to meet or exceed the requirements of Static or Dynamic Coefficient of Friction testing per installation to meet static coefficient of friction requirements for ANSI B101.1 of >0.6 and dynamic coefficient of friction (DCOF)* – Wet ANSI A326.3 of >0.42.

CLEANUP & SAFETY

Cleanup

Use S-10 Cleaning Solvent, Thinner 76 (MEK), or Thinner 225E (Acetone) to clean tools and equipment.

Safety

Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal safety precautions. Use adequate ventilation. Keep container closed when not in use.

PACKAGING, HANDLING & STORAGE

3 Gallon (11.4 liter) kit

Steri-Flor UV Part A 2 gal (7.57 liters) Steri-Flor UV Part B 1 gal (3.79 liters)

For colors, 1 Universal Color Pack (White will need 2 color packs added)

Packaging

15 Gallon (56.8 liter) Kit

Steri-Flor UV Part A 2 x 5 gal (18.93 liters) Steri-Flor UV Part B 1 x 5 gal (18.93 liters)

For colors, 5 Universal Color Packs (White will need 10 color packs added)

Shelf Life

12 months when stored in their original, unopened containers at 50°F-75°F (10°C-24°C). Storage in direct sunlight or excessive heat will reduce working time and shelf life.

PRODUCT DATA SHEET



PACKAGING, HANDLING & STORAGE

Store all products in a cool, dry area away from open flames, sparks or other hazards.

Storage

Do not attempt to store mixed material. Residual material should be properly disposed of at the end of each work period.

Warning: All Dudick products classified by DOT with either white, yellow, or red labels must not be mixed or stored together as an explosive reaction can occur.

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS, Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.