

### SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	High solids, moisture-tolerant, static dissipative epoxy primer
<b>Description</b>	A high solids static dissipative epoxy primer for concrete. It is used as part of static dissipative flooring system, intended to dissipate stray electrical current by running excess current to ground. It increases adhesion and reduces the potential for outgassing on concrete substrates.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Tolerant to moisture vapor transmission (&lt;5 lbs per 1000 ft<sup>2</sup> / &lt;24.4 g/m<sup>2</sup>)</li> <li>• Meets most VOC Requirements</li> <li>• Low Odor</li> <li>• User Friendly</li> </ul>
<b>Typical Uses</b>	<ul style="list-style-type: none"> <li>• Semi-conductor facilities</li> <li>• Electrical vehicle battery plants</li> <li>• Food processing floors</li> <li>• Laboratories</li> <li>• Pharmaceutical plants</li> <li>• Wastewater treatment facilities</li> <li>• Aisleways</li> <li>• Hangers</li> <li>• Facilities requiring ESD flooring</li> </ul>
<b>Color</b>	Black (0900)
<b>Dry Film Thickness</b>	3 - 4 mils (76 - 102 microns) per coat
<b>Solids Content</b>	By Volume 93%
<b>Theoretical Coverage Rate</b>	1492 ft <sup>2</sup> /gal at 1.0 mils (36.6 m <sup>2</sup> /l at 25 microns) 497 ft <sup>2</sup> /gal at 3.0 mils (12.2 m <sup>2</sup> /l at 75 microns) 373 ft <sup>2</sup> /gal at 4.0 mils (9.2 m <sup>2</sup> /l at 100 microns) Allow for loss in mixing and application.
<b>VOC Values</b>	<b>As Supplied</b> : 40 g/L
<b>Topcoats</b>	Polymer Alloy 2000SD

### SUBSTRATES & SURFACE PREPARATION

<b>General</b>	With all epoxies after priming and before each additional coat, examine the surface for amine blush (oily film). If present, remove by washing with warm water and detergent.
	Concrete shall be designed, placed, cured, and prepared per NACE No. 6/SSPC-SP 13, latest edition. Abrade to remove all laitance, loose concrete, etc. and to create surface profile in accordance with ICRI CSP 2 or greater.
<b>Concrete</b>	The prepared surface should have a tensile strength of 250 PSI per ASTM D-7234. All concrete substrates must be checked for moisture prior to product application using the Plastic Sheet Test, ASTM D-4263. If moisture is present the use of Vapor Stop Primer may be required. Consult your Dudick representative for further information about moisture vapor transmission or specific profile requirements which are dependent on the selected topcoat.

# Primer 67SD

## PRODUCT DATA SHEET



### PERFORMANCE DATA (TYPICAL VALUES)

Test Method	Results
Adhesion to Concrete (ASTM D4541)	Cohesive Failure of concrete
Electrical Properties (NFPA #99, ASTM F150)	$10^6$ - $10^9$ ohms
Tensile Elongation (ASTM C307)	15-25%
Tensile Strength (ASTM C307)	2,000 - 2,500 PSI (15.2-17.2 MPa)

### MIXING & THINNING

Mixing	Add the correct amount of Part B to Part A and mix for approximately 1 minute. Scrape the sides and the bottom of the container and mix thoroughly to a uniform consistency.
	Do not attempt to store mixed material. Residual material should be properly disposed of at the end of each work period.
Thinning	DO NOT THIN
Ratio	3.2:1 by volume (A:B)
Pot Life	The pot life will depend on the temperature. To prevent material waste and avoid damage to equipment, do not mix more material than can be used according to the following: 90 minutes @ 50°F (10°C) 60 minutes @ 75°F (24°C) 30 minutes @ 90°F (32°C)
	Do not attempt to store mixed material. Residual material should be properly disposed of at the end of each work period.

### APPLICATION PROCEDURES

General	Prime all surfaces to be coated at 3-4 mils (76-102 microns). <b>Do not allow the primer to puddle.</b> At stated minimum recoat times, primer may still be tacky. To optimize intercoat adhesion, it is recommended to apply the basecoat over primer that is tacky. If this is not possible, adhere to maximum recoat times referenced in the curing schedule.
	<b>To insure surface resistivity properties, the components must be applied within 30 days of product manufacture. Please refer to storage instructions.</b>

### APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	60°F (16°C)	50°F (10°C)	50°F (10°C)	0%
Maximum	80°F (27°C)	110°F (43°C)	110°F (43°C)	90%

Substrate temperature must be 5°F (3°C) above dew point.

### CURING SCHEDULE

Surface Temp.	Minimum Recoat Time	Maximum Recoat Time	Cure for Service
50°F (10°C)	4 Hours	5 Days	5 Days
75°F (24°C)	2 Hours	3 Days	3 Days
90°F (32°C)	1 Hour	2 Days	2 Days

- To optimize intercoat adhesion Primer 67SD may be top coated once it is dry enough to be tacky but does not transfer when touched.
- Application in direct sunlight may lead to blistering, pinholes, or wrinkling due to outgassing of air in the concrete and high substrate temperatures. Double priming, shading, or evening application may be required.
- Exposure of the primer to direct sunlight or heat will considerably shorten the recoat times.
- If recommended recoat times are exceeded, sanding or abrasive blasting may be required before further coats can be applied.

### TESTING / CERTIFICATION / LISTING

<b>General</b>	Dudick flooring systems can be built to meet or exceed the requirements of Static or Dynamic Coefficient of Friction testing per installation to meet static coefficient of friction requirements for ANSI B101.1 of >0.6 and dynamic coefficient of friction (DCOF)* – Wet ANSI A326.3 of >0.42.
----------------	---

### CLEANUP & SAFETY

<b>Cleanup</b>	Use S-10 Cleaning Solvent or Carboline Thinner 2 to clean tools and equipment.
<b>Safety</b>	Read and follow all caution statements on this product data sheet and on the SDS. Employ normal safety precautions. Keep container closed when not in use.
<b>Ventilation</b>	Ventilation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. Use MSHA/NIOSH approved air respirators as needed.
<b>Caution</b>	Fire and explosion hazards: This product contains less than 1% volatile components, however, vapors are heavier than air and can travel long distances, ignite and flash back. Eliminate all Ignitions sources. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workers should be required to use non-ferrous tools and wear conductive and non-sparking shoes.

### PACKAGING, HANDLING & STORAGE

<b>Packaging</b>	<b>1 Gallon Kits:</b> Part A: 0.76 Gallons (in a 1 gal can) Part B: 0.24 Gallons (in a 1 gal can) <hr/> <b>5 Gallon Kits:</b> Part A: 3.8 Gallons (in a 5 gal pail) Part B: 1.2 Gallon (in a 3.5 gal pail)
<b>Shelf Life</b>	30 days when stored in their original, unopened containers at 50°F-75°F (10°C-24°C). Exposure to excessive heat may cause premature gelling, reduce working time and shelf life.

# Primer 67SD

## PRODUCT DATA SHEET



### PACKAGING, HANDLING & STORAGE

Storage	All products should be stored in a cool, dry area away from open flames, sparks or other hazards.
	<b>Warning:</b> All Dudick, Inc. products classified by DOT with either white, yellow or red labels, must not be mixed or stored together as an explosive reaction can occur.
Shipping Weight (Approximate)	1 Gallon Kit: 11 lbs (4.99 kg)
	5 Gallon Kit: 50.86 lbs (23.08 kg)

### WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS. Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.