

## SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	100% Solids, Ceramic-Filled Multi-Functional Surface Grade Resurfacer
<b>Description</b>	A surface grade, fluid applied epoxy coating used to provide both corrosion and abrasion resistance for degraded steel substrates. It resists a wide variety of chemicals and is engineered to repair corroded and worn metallic surfaces efficiently and economically.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Smooth, slick finish</li> <li>• Corrosion and galvanic resistant</li> <li>• Good overall chemical resistance</li> <li>• High build capabilities</li> <li>• Zero VOC</li> <li>• Exceptional adhesion</li> <li>• Excellent abrasion resistance</li> </ul>
<b>Typical Uses</b>	<ul style="list-style-type: none"> <li>• Chutes</li> <li>• Hoppers</li> <li>• Fan Blades</li> <li>• Pump Housings</li> <li>• Impellers</li> <li>• Valve bodies</li> </ul>
<b>Color</b>	Orange (0400), Grey (0700), Blue (0100)
<b>Dry Film Thickness</b>	20 - 30 mils (508 - 762 microns) DFT
<b>Solids Content</b>	By Volume 100%
<b>Theoretical Coverage Rate</b>	1604 ft <sup>2</sup> /gal at 1.0 mils (39.4 m <sup>2</sup> /l at 25 microns) 80 ft <sup>2</sup> /gal at 20.0 mils (2.0 m <sup>2</sup> /l at 500 microns) 53 ft <sup>2</sup> /gal at 30.0 mils (1.3 m <sup>2</sup> /l at 750 microns) Allow for loss in mixing and application.
<b>VOC Values</b>	<b>As Supplied</b> : 0 g/l
<b>Dry Temp. Resistance</b>	Continuous: 250°F (121°C) Non-Continuous: 450°F (232°C)
<b>Chemical Resistance</b>	<ul style="list-style-type: none"> <li>• Inorganic Acids</li> <li>• Alkali Solutions</li> <li>• Some Solvents</li> <li>• Salts</li> <li>• Oils</li> </ul>

## SUBSTRATES & SURFACE PREPARATION

<b>Metal</b>	White Metal SSPC SP-5 or NACE No.1, 3.0 mil minimum profile.
--------------	--

# Polymer Steel SG Ceramic

## PRODUCT DATA SHEET



## PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

Test Method	Results
Compressive Strength (ASTM D695)	20,500 PSI
Shore D Hardness (ASTM D2240)	95-97
Taber Abrasion, 1000 cycles, C17 wheel (ASTM D4060)	70 mg loss
Tensile Adhesion (ASTM D4541)	1,800-2,000 PSI
Tensile Shear Adhesion (ASTM D1002)	3,000 PSI

## MIXING & THINNING

Mixing	Add Part B to Part A and mix until a uniform consistency is achieved. Apply to the prepared surface using a stiff brush, plastic squeegee or trowel.
	If amine blush (oily film) is present wash with warm water and detergent and dry surface before recoating.
Ratio	3.86:1 ratio by volume (A:B)
Pot Life	90 minutes @ 50°F (10°C)
	40 minutes @ 70°F (21°C)
	15-20 minutes @ 90°F (32°C)

## APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	60°F (16°C)	50°F (10°C)	50°F (10°C)	0%
Maximum	80°F (27°C)	110°F (43°C)	110°F (43°C)	90%

Substrate temperature must be 5°F (3°C) above the dew point.

## CURING SCHEDULE

Surface Temp.	Dry to Touch	Minimum Recoat Time	Minimum Cure for Normal Operations	Cure for Service
75°F (24°C)	4 Hours	4 Hours	8 Hours	24 Hours

Application of additional heat will shorten cure times.

## CLEANUP & SAFETY

Cleanup	Use S-10 Cleaning Solvent, Acetone or MEK to clean tools and equipment..
Safety	Read and follow all caution statements on this product data sheet and on the SDS. Employ normal safety precautions. Keep container closed when not in use.
Ventilation	Ventilation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. Use MSHA/NIOSH approved air respirators as needed.

### CLEANUP & SAFETY

<b>Caution</b>	Fire and explosion hazards: This product contains less than 1% volatile components, however, vapors are heavier than air and can travel long distances, ignite and flash back. Eliminate all Ignitions sources. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workers should be required to use non-ferrous tools and wear conductive and non-sparking shoes.
----------------	--

### PACKAGING, HANDLING & STORAGE

<b>Packaging</b>	<p><b><u>2 lb Kit:</u></b>  <i>Packaged together in one cardboard box</i>            Part A: 0.136 Gallon (in a 32 oz white jar w/ lid)            Part B: 0.038 Gallon (in 8 oz white jar w/ lid)</p> <p><b><u>11.5 lb (1 Gallon) Kit:</u></b>  <i>Packaged together in one cardboard box</i>            Part A: 0.78 Gallon (in a one gallon can)            Part B: 0.22 Gallon (in a quart can)</p> <p>Includes mixing sticks and applicator squeegee.</p>
<b>Shelf Life</b>	<p>12 months when stored in their original, unopened containers at 50°F-75°F (10°C-24°C). Storage in direct sunlight or excessive heat will reduce working time and shelf life.</p> <p>Material is not returnable after 90 days from purchase.</p>
<b>Storage</b>	<p>Warning: All Dudick products classified with DOT labels as either white, yellow or red labels must not be mixed or stored together as an explosive reaction can occur.</p> <p>All products should be stored in a cool, dry area away from open flames, sparks or other hazards.</p>
<b>Shipping Weight (Approximate)</b>	<p>Outside packaging:            2 lb kit: 2.9 lbs            11.5 lb kit: 13.5 lbs</p>

### WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS. Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.