

SELECTION & SPECIFICATION DATA

Generic Type	Single Component Phenolic Modified Alkyd
Description	Heavy-duty primer formulated to provide long term protection of structural steel. It provides excellent adhesion and can be welded through to yield sound welds.
Features	<ul style="list-style-type: none"> • Good for extended exposure demands • Ability to be welded through • Heavy-metal free • VOC compliant for most areas • VOC = 2.3 lbs/gallon
Color	Red (0500); Gray (0700)
Finish	Flat
Dry Film Thickness	2 - 3 mils (51 - 76 microns) per coat Don't exceed 3.0 mils (75 microns) in a single coat. Weldable areas should be limited to less than 1 mil in thickness.
Solids Content	By Volume 52% +/- 2%
HAPs Values	As supplied: 0.6 lbs./solid gallon
Theoretical Coverage Rate	834 ft ² /gal at 1.0 mils (20.5 m ² /l at 25 microns) 417 ft ² /gal at 2.0 mils (10.2 m ² /l at 50 microns) 278 ft ² /gal at 3.0 mils (6.8 m ² /l at 75 microns) Allow for loss in mixing and application.
VOC Value(s)	Per EPA Method 24: 2.3 lbs./gal (276 g/l) Thinner 242 E (6 oz/gal): 2.3 lbs./gal (276 g/l) These are nominal values and may vary slightly with color. Product contains VOC-exempt t-butyl acetate. Check local regulations regarding product usage.
Dry Temp. Resistance	Continuous: 200°F (93°C) Non-Continuous: 250°F (121°C) Discoloration and loss of gloss is observed above 200 °F (93 °C).
Topcoats	May be coated with Acrylics, Epoxies, Alkyds, or Polyurethanes depending on exposure and need. (May also be topcoated with catalyzed epoxies and urethanes. Call for specific recommendations.)

SUBSTRATES & SURFACE PREPARATION

General	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion.
Steel	SSPC-SP6 with a 1.0-2.0 mil (25-50 micron) surface profile for maximum protection. SSPC-SP2 or SP3 as minimum requirement. When using under fireproofing products, defer to the primer surface preparation requirements in the product data sheet of the fireproofing product.

Carbocoat[®] 8229 Non-Lift Primer

PRODUCT DATA SHEET



MIXING & THINNING

Mixing | Power mix until uniform in consistency.

Thinning | Normally not required but may thin as follows: Spray, brush or roller may be thinned up to 5 oz/gal (5%) with Thinner 242E. Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Spray Application (General) | The following spray equipment has been found suitable and is available from manufacturers.

Conventional Spray | Pressure pot equipped with dual regulators, 3/8" I.D. minimum material hose, 0.052" fluid tip and appropriate air cap.

Airless Spray | Pump Ratio: 30:1 (minimum)*
GPM Output: 3.0 (minimum)
Material Hose: 3/8" I.D. (minimum)
Tip Size: 0.013" - 0.017"
Output PSI: 2000-2300
Filter Size: 60 mesh
*PTFE packings are recommended and available from the pump manufacturer.

Brush & Roller (General) | Multiple coats may be required to achieve desired appearance, hiding and recommended dry film thickness. Avoid excessive rebrushing or rerolling.

Brush | Use a natural bristle brush.

Roller | Use a short-nap synthetic roller cover with solvent resistant core.

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	35°F (2°C)	35°F (2°C)	35°F (2°C)	0%
Maximum	120°F (49°C)	120°F (49°C)	120°F (49°C)	90%

This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions.

CURING SCHEDULE

Surface Temp.	Dry to Touch	Tack Free	Dry to Topcoat w/ itself or other alkyds	Dry to Topcoat w/ epoxies or urethanes
35°F (2°C)	60 Minutes	4 Hours	4 Hours	8 Hours
55°F (13°C)	35 Minutes	60 Minutes	2 Hours	2 Hours
75°F (24°C)	10 Minutes	25 Minutes	30 Minutes	30 Minutes

These times are based on a 2.0 mil (50 microns) dry film thickness. Higher film thickness, insufficient ventilation, high humidity or cooler temperatures will require longer cure times and could result in solvent entrapment or premature failure. Recoat intervals may vary from those listed above when using under intumescent fireproofing products. Consult Carboline Technical Service for recommended cure times before applying Carboline intumescent products.

CLEANUP & SAFETY

Cleanup	Use Thinner 242E or Acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.
Safety	Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions. Keep container closed when not in use.
Ventilation	When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved respirator.
Caution	This product contains flammable solvents. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workers should be required to use non-ferrous tools and wear conductive and non-sparking shoes.

PACKAGING, HANDLING & STORAGE

Shelf Life	24 months at 75 °F (24 °C) *Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.
Storage Temperature & Humidity	35-110 °F (2-43 °C) 0-100% Relative Humidity
Storage	Store Indoors.
Shipping Weight (Approximate)	5 Gallon - 66 lbs. (30 kg) 50 Gallon - 660 lbs. (300 kg)
Flash Point (Setaflash)	52 °F (11 °C)

Carbocoat[®] 8229 Non-Lift Primer

PRODUCT DATA SHEET



WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.