



SELECTION & SPECIFICATION DATA

Generic Type	High Performance Polyurethane
Description	<p>A “coal tar free”, high performance two-component polyurethane coating engineered for applications in Marine, Industrial and Pipeline industries. This low friction, high abrasion and impact resistant coating is used on exterior hulls to reduce ad-freezing of ships provide abrasion and corrosion protection.</p> <p>Further, it is used to coat marine pilings and docks where impact and abrasion resistance is required and cathodic protection is utilized.</p> <p>Available in Spray Grade and Brush Grade.</p>
Features	<ul style="list-style-type: none">• Excellent resistance to high temperature cathodic disbonding up to 65°C (149°F)• Excellent adhesion to steel surfaces, Fusion Bond Epoxy (FBE), Fiber Reinforced Plastic (FRP) and concrete• High build one-coat application• 100% solids – Does not contain coal tar• Excellent fresh and salt water, impact and abrasion resistance
Typical Uses	<ul style="list-style-type: none">• Ship hulls• Decks• Use on girth welds• Hot bends on pipelines operating at high temperatures
Color	Grey (0700)
Primer	<p>No primer required on steel.</p> <p>SP-1264 Damp Concrete Primer Sealer required prior to application of this product to concrete.</p>
Dry Film Thickness	<p>20 - 100 mils (508 - 2540 microns) DFT</p> <p>Depends upon application. Consult with SPC Representative.</p>
Solids Content	By Volume 100%
Theoretical Coverage Rate	<p>1604 ft²/gal at 1.0 mils (39.4 m²/l at 25 microns)</p> <p>80 ft²/gal at 20.0 mils (2.0 m²/l at 500 microns)</p> <p>16 ft²/gal at 100.0 mils (0.4 m²/l at 2500 microns)</p> <p>Allow for loss in mixing and application.</p>
VOC Values	As Supplied : 0 g/L
Dry Temp. Resistance	Continuous: 149°F (65°C)
Specific Gravity	<p>Base: 1.29±0.03</p> <p>Hardener: 1.24±0.03</p> <p>Mixed Material: 1.28±0.03</p>

SUBSTRATES & SURFACE PREPARATION

Steel	<p>Cleanliness: NACE No. 2/SSPC SP-10, SA 2.5 (ISO 8501-1)</p> <p>Profile: 75 microns minimum to 125 microns maximum (3.0 mils to 5.0 mils)</p>
Concrete	<p>Cleanliness: Remove laitance and other surface contaminants by grit blasting or mechanical scarification. Seal using SP-1264 Damp Concrete Primer Sealer.</p>

SP-1864

PRODUCT DATA SHEET



PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

Test Method	Results
Adhesion to Steel (Hot Water Soak) (CSA-Z245.20)	60 days @ 80°C (176°F): Rating #1
Adhesion to Steel (Pull Off Strength) (ASTM D4541)	>27 MPa (>4000 psi) @ 25°C (77°F)
Cathodic Disbondment Resistance (CSA-Z245.20)	28 days @ 25°C (77°F) @ - 1.5 Volts: 3.50 mmR
Elongation at Break (ASTM D522)	25°C (77°F) >30%
Flexibility (CSA-Z245.20)	2.50°PPD @ 25°C (77°F) 1.50°PPD @ 0°C (32°F) 0.50°PPD @ -30°C (-22°F)
Hardness (ASTM D2240)	25°C (77°F): 78 Shore D
Impact Resistance (CSA-Z245.20)	>8.1 Joules (>6.0 ft-lbf) @ 25°C (77°F) >6.8 Joules (>5.0 ft-lbf) @ 0°C (32°F) >2.0 Joules (>1.4 ft-lbf) @ -30°C (-22°F)
Volume Resistivity (ASTM D257)	1.0 x 10 ¹⁴ (ohm-cm)

MIXING & THINNING

Mixing	Spray Grade: Agitation of the Part A component is recommended during the preheating process and during application to ensure a uniform heat throughout the base portion. Component Details for Color: Grey (0700): The Base is Grey (0700) and the Hardener is Amber (0908)
Thinning	DO NOT THIN.
Ratio	3:1 Base to Activator, by volume
Pot Life	Brush Grade: 8-10 minutes 200 gms mass @ 25°C (77°F)
Gel Time	Spray Grade: 4 minutes 30 seconds 200 gm mass @ Base @ 60°C (140°F) Activator @ 25°C (77°F)

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Spray Grade	Plural Component Spray Equipment: Graco XP-70 or equivalent Tip Size:: 0.019-0.031 0.031 Heated hose bundle consisting of 3/8" ID base and 1/4" ID hardener with a solvent flush line. Glycol heat trace or equivalent capable of 80°C (176°F)
--------------------	-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------



APPLICATION CONDITIONS

Table with 4 columns: Condition, Surface, Ambient, Humidity. Rows for Minimum and Maximum values.

Preheating of the substrate is required if the surface to be coated is below 1°C (33°F).

Material Temperature: Base: 60°C-65°C (140°F-149°F); Activator: 25°C (77°F)

The substrate temperature must be a minimum of 3°C (5°F) above the dew point temperature before proceeding with the coating operation.

CURING SCHEDULE

Table with 3 columns: Surface Temp., Touch Dry, Dry Hard (Spray Grade). Rows for temperatures from 68°F to 194°F.

Substrate: 12 mm (0.50 inch) Thick Steel Panels

Note: The information above is to serve as a guide only. The test results were compiled under laboratory-controlled conditions, as per ASTM D1640. Field results may vary due to variable conditions such as radiant heat loss and the cooling effects of wind.

Full Cure | 4 days @ 25°C (77°F)

Maximum 48 hours @ 25°C (77°F) @ 50% RH

Recoat Interval

This product is a one-coat application system. However, if there are areas below the specified thickness and the coating has cured beyond the specified re-coat window, roughening of the surface is necessary to ensure inter-coat adhesion. Small areas ≤ 316 sq. cm. (≤ 49 sq. in.) may be sanded using a medium grit (80- 100) carborundum cloth. All dust from the sanding or blast roughening must be removed from the surface prior to the application of the coating.

CLEANUP & SAFETY

Cleanup | Carboline Thinner 2 or SP-100 Equipment Wash

Safety

Refer to SPC's Safety Data Sheet prior to use. Carefully read and follow all safety instructions on labels and packaging. Handle and store material with care in accordance to the Safety Data Sheet. Follow and observe any applicable local or national laws and regulations.

PACKAGING, HANDLING & STORAGE

Shelf Life

Base: 24 months maximum
Activator: 12 months maximum

When kept at recommended storage conditions and in original unopened containers.

Storage Temperature & Humidity

4°C to 49°C (40°F to 120°F)
0 to 95% Humidity

SP-1864

PRODUCT DATA SHEET



PACKAGING, HANDLING & STORAGE

Storage	Store indoors and keep Dry. Do not place drums directly on concrete or earth. Store on top of wood slats or pallets. Blanket all partial drums with nitrogen gas to prevent moisture contamination. Avoid freezing. Do not open until ready to use. Rotate Resin (Part A) drums regularly if stored for the long term
Packaging - Brush Grade	1 Liter (0.26 Gallon) Kit Part A: 0.75 liters (0.2 gallons) Part B: 0.25 liters (0.06 gallons) 2 Liter (0.53 gallons) Kit Part A: 1.5 liters (0.40 gallons) Part B: 0.5 liters (0.13 gallons)
Packaging - Spray Grade	800 Liter (211.3 Gallon) Kit Part A: 600 liters (158.5 gallons) Part B: 200 liters (52.8 gallons)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.