



# SP-888-4 Spray

## PRODUCT DATA SHEET

### SELECTION & SPECIFICATION DATA

|                                  |  |
|----------------------------------|--|
| <b>Generic Type</b>              | Epoxy Novolac  |
| <b>Description</b>               | SP-8888® Pipe Coating is based on the latest Zero VOC Novolac Technology. The product cures to a highly cross-linked coating for high temperature service in the Oil and Gas Industry [cathodic disbondment resistance up to 150°C (302°F)]. SP-8888® is available in Spray Grade and Brush Grade, and is also available in cartridges for coating repairs.  |
| <b>Features</b>                  | <ul style="list-style-type: none"> <li>• 100% Solids – No VOCs.</li> <li>• Isocyanate free.</li> <li>• Excellent resistance to high temperature cathodic disbondment up to 150°C (302°F).</li> <li>• Excellent adhesion to grit blasted steel surfaces, Fusion Bond Epoxy (FBE), and Fiber Reinforced Plastic (FRP).</li> <li>• Excellent impact resistance.</li> <li>• Good flexibility.</li> </ul> |
| <b>Color</b>                     | Primer color (0700) gray. Variety of other finish coat colors in rapid tint service. MiO additive will darken (grey) all colors.   |
| <b>Finish</b>                    | Semi-Gloss   |
| <b>Primer</b>                    | Self-priming. May be applied over organic and inorganic zinc rich primers. A mist coat may be required to minimize bubbling over zinc rich primers.  |
| <b>Dry Film Thickness</b>        | <p>4 - 6 mils (102 - 152 microns) per coat as a primer or an intermediate without additives<br/>           4 - 10 mils (102 - 254 microns) per coat (2 coats) may be used direct-to-metal<br/>           8 - 12 mils (203 - 305 microns) per coat with GF or MiO additives</p> <p>Do not exceed 10 mils in a single coat (without additives)</p>   |
| <b>Solids Content</b>            | By Volume 72% +/- 2%   |
| <b>Theoretical Coverage Rate</b> | <p>1155 ft<sup>2</sup>/gal at 1.0 mils (28.3 m<sup>2</sup>/l at 25 microns)<br/>           289 ft<sup>2</sup>/gal at 4.0 mils (7.1 m<sup>2</sup>/l at 100 microns)<br/>           96 ft<sup>2</sup>/gal at 12.0 mils (2.4 m<sup>2</sup>/l at 300 microns)<br/>           Allow for loss in mixing and application.</p>   |
| <b>VOC Values</b>                | <p>Thinner 2 : 13 oz/gal 2.47 lbs./gal 296 g/l<br/>           Thinner 33 : 15 oz/gal 2.57 lbs./gal 308 g/l<br/> <b>As Supplied</b> : 2.00 lbs./gal 240 g/l<br/>           Thinner 2 : 6 oz/gal 2.23 lbs./gal 267 g/l</p> <p>These are nominal values for the liquid components only and may vary slightly with color and with the addition of GF or MiO fillers.</p>                                 |
| <b>Dry Temp. Resistance</b>      | <p>Continuous: 300°F (149°C)<br/>           Non-Continuous: 350°F (177°C)</p> <p>Exposure above 200°F/93°C may cause discoloration (darkening) or loss of gloss, but will not affect performance.</p>  |
| <b>Limitations</b>               | RTS colors and the use of Additive 8505 with this product are not recommended for immersion. Additive 8505 will cause discoloration of this product, but will not affect product performance.  |
| <b>Topcoats</b>                  | May be topcoated with Acrylics, Epoxies, Alkyds, or Polyurethanes depending on exposure and need.  |

# SP-888-4 Spray

## PRODUCT DATA SHEET



### SUBSTRATES & SURFACE PREPARATION

|                                    |   |
|------------------------------------|---|
| <b>General</b>                     | Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.   |
| <b>Steel</b>                       | For most applications:<br>Immersion: SSPC-SP10<br>Non-immersion: SSPC-SP6<br>1.5-3.0 mils (38-75 microns)   |
| <b>Galvanized Steel</b>            | SSPC-SP16   |
| <b>Concrete or CMU</b>             | Concrete must be cured 28 days at 75°F (24°C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with ASTM D4258 Surface Cleaning of Concrete and ASTM D4259 Abrading Concrete. Voids in concrete may require surfacing. |
| <b>Previously Painted Surfaces</b> | SSPC-SP2 or SP3   |

### PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

| Test Method                  | System                  | Results                                    |
|------------------------------|-------------------------|--|
| ASTM D2794 Impact resistance | Blasted Steel 1ct.      | 100 in. lbs (direct)                       |
| ASTM D3366 Pencil Hardness   | Blasted Steel 1 ct.     | 4H-5H                                      |
| ASTM D4541 Adhesion          | Blasted Steel 1ct. 2ct. | (Pneumatic) 1 ct. 1500+psi 2 ct. 1500+ psi |
| ASTM D522 Flexibility        | Blasted Steel 1 ct.     | No cracking, 5/8" Conical Mandrel Bend     |

Data based on Carboguard 60 without filler additives.

### MIXING & THINNING

|                 |  |
|-----------------|--|
| <b>Mixing</b>   | Power mix separately, then combine and power mix. Allow mixed product 15 minute sweat in time before thinning if material is under 70°F. No sweat in needed above 70°F DO NOT MIX PARTIAL KITS. For GF or MiO additives, slowly add while mixing.  |
| <b>Thinning</b> | Spray: Up to 13 oz/gal (10%) with Thinner #2. Brush & Roller: Up to 15 oz/gal (12%) with Thinner #33. Thinner 236E or 250E may be used as an exempt thinner in lieu of those listed above. Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied. |
| <b>Ratio</b>    | <ul style="list-style-type: none"><li>• Liquid Components: 1:1 Ratio (A to B)</li><li>• Glass Flake (GF) Additive: (1.8 lbs/mixed gal)</li><li>• Micaceous Iron Oxide (MiO) Additive: (2.0 lbs/gal)</li></ul>  |



**MIXING & THINNING**

|                 |   |
|-----------------|---|
| <b>Pot Life</b> | <p>4 Hours at 75°F (24°C)<br/>Pot life ends when coating loses body and begins to sag. Pot life times will be less at higher temperatures.</p> <p>Carboline Additive 8505 can be used to aid the film forming process in the product for temperatures down to 35°F. Carboline Additive 8505 is added at a rate of 4 oz per mixed two gallon kit or 20 oz per mixed ten gallon kit. Allow mixed product 15 minute sweat in time before thinning, if material is under 70°F, and 24 hrs cure prior to topcoating for surface temperatures down to 40°F. At this addition rate, Additive 8505 will accelerate the cure rate of the epoxy product and reduce the pot life of the product.</p> |
|-----------------|---|

**APPLICATION EQUIPMENT GUIDELINES**

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

|   |  |
|---|--|
| <b>Conventional Spray</b>               | Pressure pot equipped with dual regulators, 3/8" I.D. minimum material hose, .070" I.D. fluid tip and appropriate air cap. For filler additives use a 0.110" I.D. fluid tip.   |
| <b>Airless Spray</b>                    | <p>Pump Ratio: 30:1 (min.)*<br/>GPM Output: 2.5 (min.)<br/>Material Hose: 3/8" I.D. (min.)<br/>Tip Size: .017"-.021" (.035"-.041" for filler additives)<br/>Output PSI: 2100-2500<br/>Filter Size: 60 mesh (remove mesh for filler additives)<br/>PTFE packings are recommended and available from the pump manufacturer.</p>  |
| <b>Brush &amp; Roller<br/>(General)</b> | <p>Not recommended for tank lining applications except when striping welds. Multiple coats may be required to obtain desired appearance, recommended dry film thickness and adequate hiding. Avoid excessive re-brushing or re-rolling. For best results, tie-in within 10 minutes at 75°F (24°C). The addition of GF or MiO fillers is best applied by spray application.</p> |
| <b>Brush</b>                            | Use a medium bristle brush.  |
| <b>Roller</b>                           | Use 3/8" nap roller with a solvent resistant core.   |

**APPLICATION CONDITIONS**

| Condition | Material    | Surface      | Ambient      | Humidity |
|-----------|-------------|--------------|--------------|----------|
| Minimum   | 50°F (10°C) | 40°F (4°C)   | 40°F (4°C)   | 0%       |
| Maximum   | 90°F (32°C) | 140°F (60°C) | 120°F (49°C) | 85%      |

This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions.

# SP-888-4 Spray

## PRODUCT DATA SHEET



## CURING SCHEDULE

| Surface Temp. | Dry to Handle | Dry to Recoat | Dry to Touch | Maximum Recoat Time |
|---------------|---------------|---------------|--------------|---------------------|
| 40°F (4°C)    | 30 Hours      | 48 Hours      | 3 Hours      | 1 Year              |
| 50°F (10°C)   | 20 Hours      | 24 Hours      | 2 Hours      | 1 Year              |
| 60°F (16°C)   | 8 Hours       | 10 Hours      | 1 Hour       | 1 Year              |
| 75°F (24°C)   | 5 Hours       | 7 Hours       | 45 Minutes   | 1 Year              |
| 90°F (32°C)   | 3 Hours       | 4 Hours       | 30 Minutes   | 1 Year              |

\*These times are based on a 5.0 mil (125 micron) dry film thickness and 50% RH. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure. Excessive humidity or condensation on the surface during curing can interfere with the cure, can cause discoloration and may result in a surface haze. Any haze or blush must be removed by water washing before recoating.

**NOTE:** The maximum recoat times in the chart above are for atmospheric exposures. When used as a blast-hold primer, maximum recoat time is limited to 30 days. If the maximum recoat times have been exceeded, the surface must be abraded by sweep blasting or sanding prior to the application of additional coats. For force curing, contact Carboline Technical Service for specific requirements.

## CLEANUP & SAFETY

|                    |  |
|--------------------|--|
| <b>Cleanup</b>     | Use Thinner #2 or Acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.   |
| <b>Safety</b>      | Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions.   |
| <b>Ventilation</b> | When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved respirator. |

## PACKAGING, HANDLING & STORAGE

|   |   |
|---|---|
| <b>Shelf Life</b>                         | Part A & B: Min. 36 months at 75°F (24°C)<br>*Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.   |
| <b>Storage Temperature &amp; Humidity</b> | 40° - 100°F (4° - 37.8°C)<br>0-100% Relative Humidity   |
| <b>Storage</b>                            | Store Indoors.<br>This product is solvent based and not affected by excursions below these published storage temperatures, down to 10°F, for a duration of no more than 14 days. Always inspect the product prior to use to make sure it is smooth and homogeneous when properly mixed. |
| <b>Shipping Weight (Approximate)</b>      | <u>2 Gallon Kit</u><br>26 lbs. (12 kg)<br><u>10 Gallon Kit</u><br>127 lbs. (58 kg)  |
| <b>Flash Point (Setflash)</b>             | Part A: 82°F (27.8°C)<br>Part B: 71°F (21.7°C)<br>Mixed: 78°F (25.6°C)  |



# SP-888-4 Spray

## PRODUCT DATA SHEET

---

### WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.