

SELECTION & SPECIFICATION DATA

Generic Type	Epoxy Polyamide
Description	<p>Carboguard 60 is a high solids, versatile, abrasion resistant, chemical resistant, and corrosion resistant coating. It can be used as a primer, intermediate coat, or self-priming finish over steel or inorganic zinc primers. May be topcoated with itself, or a broad variety of high performance finish coats. This product has excellent wetting properties giving it the capability of going over marginally prepared substrates. It is ideal for maintenance and fabrication shop applications.</p> <p>An optional Glass Flake (GF) additive or micaceous iron oxide (MiO) additive can be purchased separately and may be used to enhance film strength for more abusive applications for severe marine or heavy industrial uses.</p> <p>Consult Technical Service for suitability as a lining or other exposures.</p>
Features	<ul style="list-style-type: none"> • Low odor and low VOC • Available in a variety of colors • Attractive medium sheen for tank exteriors • Good chemical resistance • Used as a primer, intermediate, or finish coat • Fast cure & dry times • Can be applied over power tool cleaned surfaces • VOC compliant to current AIM regulations • Good abrasion resistance
Color	Available in a variety of colors. Refer to the Carboline color chart. MiO additive will darken (grey) all colors.
Finish	Semi-Gloss
Primer	Self-priming. May be applied over organic and inorganic zinc rich primers. A mist coat may be required to minimize bubbling over zinc rich primers.
Dry Film Thickness	<p>102 - 152 microns (4 - 6 mils) per coat as a primer or an intermediate without additives 102 - 254 microns (4 - 10 mils) per coat (2 coats) may be used direct-to-metal 203 - 305 microns (8 - 12 mils) per coat with GF or MiO additives</p> <p>Do not exceed 250 microns (10 mils) in a single coat (without additives)</p>
Solids Content	By Volume 72% +/- 2%
Theoretical Coverage Rate	<p>28.3 m²/l at 25 microns (1155 ft²/gal at 1.0 mils) 7.1 m²/l at 100 microns (289 ft²/gal at 4.0 mils) 2.4 m²/l at 300 microns (96 ft²/gal at 12.0 mils) Allow for loss in mixing and application.</p>
VOC Values	<p>As Supplied : 240 g/l (2.00 lbs./gal) Thinner 2 :10% (13 oz/gal): 296 g/l (2.47 lbs./gal) Thinner 2 : 5% (6 oz/gal): 267 g/l (2.23 lbs./gal) Thinner 33 : 12% (15 oz/gal): 308 g/l (2.57 lbs./gal)</p> <p>These are nominal values for the liquid components only and may vary slightly with color and with the addition of GF or MiO fillers.</p>

Carboguard 60

PRODUCT DATA SHEET



SELECTION & SPECIFICATION DATA

Dry Temp. Resistance	Continuous: 149°C (300°F) Non-Continuous: 177°C (351°F) Exposure above 93°C/200°F may cause discoloration (darkening) or loss of gloss, but will not affect performance.
Limitations	Additive 8505 will cause discoloration of this product, but will not affect product performance in atmospheric service.
Topcoats	May be topcoated with Acrylics, Epoxies, Alkyds, or Polyurethanes depending on exposure and need.

SUBSTRATES & SURFACE PREPARATION

General	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.
Steel	For most applications: SSPC-SP6 1.5-3.0 mils (38-75 microns) When using under fireproofing products, defer to the primer surface preparation requirements in the product data sheet of the fireproofing product.
Galvanized Steel	SSPC-SP16 When using under fireproofing products, defer to the primer surface preparation requirements in the product data sheet of the fireproofing product.
Concrete or CMU	Concrete must be cured 28 days at 24°C (75°F) and 50% relative humidity or equivalent. Prepare surfaces in accordance with ASTM D4258 Surface Cleaning of Concrete and ASTM D4259 Abrading Concrete. Voids in concrete may require surfacing.
Previously Painted Surfaces	SSPC-SP2 or SP3
Stainless Steel	SSPC-SP 16: for heavy industrial and marine service conditions create 38 to 75 microns (1.5 to 3.0 mils) anchor profile.

PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

Test Method	System	Results
ASTM D2794 Impact resistance	Blasted Steel 1ct.	100 in. lbs (direct)
ASTM D3363 Pencil Hardness	Blasted Steel 1 ct.	4H-5H
ASTM D4541 Adhesion	Blasted Steel 1ct. 2ct.	(Pneumatic) 1 ct. 1500+psi 2 ct. 1500+ psi
ASTM D522 Flexibility	Blasted Steel 1 ct.	No cracking, 5/8" Conical Mandrel Bend

Data based on Carboguard 60 without filler additives.

MIXING & THINNING

Mixing	Power mix separately, then combine and power mix. Allow mixed product 15 minute sweat in time before thinning if material is under 21 °C (70°F). No sweat in needed above 21 °C (70°F). DO NOT MIX PARTIAL KITS. For GF or MiO additives, slowly add while mixing.
Thinning	Spray: Up to 10% (13 oz/gal) with Thinner #2. Brush & Roller: Up to 12% (15 oz/gal) with Thinner #33. Thinner 236E or 250E may be used as an exempt thinner in lieu of those listed above. Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.
Ratio	<ul style="list-style-type: none"> • Liquid Components: 1:1 Ratio (A to B) • Glass Flake (GF) Additive: 215 grams/mix.liter (1.8 lbs/mixed gal) • Micaceous Iron Oxide (MiO) Additive: 240 grams/mix.liter (2.0 lbs/gal)
Pot Life	4 Hours at 24°C (75°F) Pot life ends when coating loses body and begins to sag. Pot life times will be less at higher temperatures.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Conventional Spray	Pressure pot equipped with dual regulators, 3/8" I.D. minimum material hose, 0.070" I.D. fluid tip and appropriate air cap. For filler additives use a 0.110" I.D. fluid tip.
Airless Spray	Pump Ratio: 30:1 (min.)* GPM Output: 2.5 (min.) Material Hose: 3/8" I.D. (min.) Tip Size: .017"-.021" (.035"-.041" for filler additives) Output PSI: 2100-2500 Filter Size: 60 mesh (remove mesh for filler additives) * PTFE packings are recommended and available from the pump manufacturer.
Brush & Roller (General)	Multiple coats may be required to obtain desired appearance, recommended dry film thickness and adequate hiding. Avoid excessive re-brushing or re-rolling. For best results, tie-in within 10 minutes at 24°C (75°F). The addition of GF or MiO fillers is best applied by spray application.
Brush	Use a medium bristle brush.
Roller	Use 3/8" nap roller with a solvent resistant core.

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	10°C (50°F)	4°C (39°F)	4°C (39°F)	0%
Maximum	32°C (90°F)	60°C (140°F)	49°C (120°F)	85%

This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions.

Carboguard 60

PRODUCT DATA SHEET



CURING SCHEDULE

Surface Temp.	Dry to Touch	Dry to Handle/ Recoat w/ Itself	Dry to Topcoat w/ Other Finishes	Maximum Recoat Time
4°C (39°F)	3 Hours	30 Hours	48 Hours	1 Year
10°C (50°F)	2 Hours	20 Hours	24 Hours	1 Year
16°C (61°F)	1 Hour	8 Hours	10 Hours	1 Year
24°C (75°F)	45 Minutes	5 Hours	7 Hours	1 Year
32°C (90°F)	30 Minutes	3 Hours	4 Hours	1 Year

These times are based on a 125 micron (5.0 mil) dry film thickness and 50% RH. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure. Excessive humidity or condensation on the surface during curing can interfere with the cure, can cause discoloration and may result in a surface haze. Any haze or blush must be removed by water washing before recoating. Recoat intervals may vary from those listed above when using under intumescent fireproofing products. Consult Carboline Technical Service for recommended cure times before applying Carboline intumescent products.

NOTE: If the maximum recoat times have been exceeded, the surface must be abraded by brush-off blast cleaning or mechanical methods prior to the application of additional coats. For force curing, contact Carboline Technical Service for specific requirements. Carboline Additive 8505 can be used to aid the film forming process in the product for temperatures down to 1.7°C (35°F). Carboline Additive 8505 is added at a rate of 4 oz per mixed two gallon kit or 20 oz per mixed ten gallon kit (approx.: 299.6g /20liters mixed product). Allow mixed product 15 minute sweat in time before thinning, if material is under 21°C (70°F), and 24 hrs cure prior to topcoating for surface temperatures down to 4°C (40°F). At this addition rate, Additive 8505 will accelerate the cure rate of the epoxy product and reduce the pot life of the product.

CLEANUP & SAFETY

Cleanup	Use Thinner #2 or Acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.
Safety	Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Use adequate ventilation. Keep container closed when not in use.
Ventilation	When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved respirator.

PACKAGING, HANDLING & STORAGE

Shelf Life	Part A & B: Min. 36 months at 24°C (75°F) *Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.
Shipping Weight (Approximate)	Part A: 10 liters Part B: 10 liters
Storage Temperature & Humidity	4° - 38°C (40° - 100°F) 0 - 100% Relative Humidity
Flash Point (Setaflash)	Part A: 28°C (82°F) Part B: 22°C (71°F)

PACKAGING, HANDLING & STORAGE

Storage	Store Indoors.
	This product is solvent based and not affected by excursions below these published storage temperatures, down to -12°C (10°F), for a duration of no more than 14 days. Always inspect the product prior to use to make sure it is smooth and homogeneous when properly mixed.

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.