

## SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	Aliphatic Acrylic Polyurethane
<b>Description</b>	A satin, tile-like polyurethane topcoat which produces a smooth, slick and tough, easy to clean surface. Carbothane 134 PU has very good resistance to splash and spillage of acids, alkalies, most solvents and excellent splash and spillage resistance to salts and water
<b>Features</b>	<ul style="list-style-type: none"> <li>• Excellent weatherability</li> <li>• Excellent flexibility</li> <li>• Excellent abrasion resistance</li> <li>• Optimal protection with minimum layer thickness</li> <li>• Excellent flow behavior with spray and roll application</li> <li>• Available in many colors</li> <li>• VOC compliant to current AIM regulation</li> </ul>
<b>Color</b>	RAL, BS, Munsell etc. Certain colors needs an additional coat for optimal opacity.
<b>Finish</b>	Satin
<b>Primer</b>	May be used over epoxies, urethanes and others as recommended. Typically applied as topcoat for CG 893, CM 15 /LT, CG 890, CZ 858 (P)
<b>Dry Film Thickness</b>	50 micron per layer.
<b>Solid(s) Content</b>	By volume: 55 ± 2% Aluminum color: 45 ± 2%
<b>Theoretical Coverage Rates</b>	22 m <sup>2</sup> /l at 25 microns (18 m <sup>2</sup> /l for aluminum) Allow for loss in mixing and application.
<b>VOC Value(s)</b>	Per EPA Method 24: 430 g/l These are nominal values and may vary slightly with color.
<b>Dry Temp. Resistance</b>	Continuous: 93°C (199°F) Non-Continuous: 121°C (250°F) Discoloration and loss of gloss is observed above 93°C.
<b>Limitations</b>	Immersion service
<b>Topcoats</b>	n.a.

## SUBSTRATES & SURFACE PREPARATION

<b>General</b>	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.
<b>Steel</b>	Prime with specific Carboline primers as recommended.

# Carbothane PU 134 LG

## PRODUCT DATA SHEET



### SUBSTRATES & SURFACE PREPARATION

**Previously Painted Surfaces** | Lightly sand or abrade to roughen and degloss the surface. Existing paint must attain a minimum 3b rating in accordance with ASTM D3359 "X-Scribe" adhesion test. Prime with specific primers as recommended by Carboline.

### MIXING & THINNING

**Mixing** | First mix separately the two components carefully. Then add them together and mix again carefully. NEVER MIX PARTIAL KITS.

**Thinning** | Spray: up to 20% with Thinner 25  
For hot and/or windy conditions: up to 25% with Thinner 82.  
Roller: up to 20% with Thinner 215  
Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.

**Ratio** | 7:1 (A to B).

**Pot Life** | 4 Hours at 24°C and less at higher temperatures. Pot Life ends when coating becomes too viscous to use. **MOISTURE CONTAMINATION WILL SHORTEN POT LIFE AND CAUSE GELLATION.**

### APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

**Spray Application** | The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss, Graco and others.

**Conventional Spray** | Pressure pot equipment with dual regulators, 3/8" I.D. minimum material hose, 0.043" I.D. fluid tip and appropriate air cap.

**Airless Spray** | Pump Ratio: 30:1 (min.)  
GPM Output: 3.0 (min.)  
Material Hose: 3/8" I.D. (min.)  
Tip Size: .015-.017"  
Pressure BAR: 148-168  
Filter Size: 60 mesh  
Teflon packings are recommended and available from the pump manufacturer.

**Brush & Roller (General)** | The brush and roller are recommended only for retouching.

**Brush** | Use a medium natural bristle brush.

**Roller** | Use a short nap mohair roller that is suitable for 2k products.

## APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	4°C (39°F)	4°C (39°F)	4°C (39°F)	0%
Maximum	43°C (109°F)	54°C (129°F)	49°C (120°F)	85%

Substrate temperatures should be 3°C above the dew point. This product is moisture sensitive in the liquid stage. Protect from high humidity, dew and direct moisture contact until fully cured. Application and/or curing in humidity above maximum, or exposure to moisture from rain or dew may result in a loss of gloss and/or micro bubbling of the product.

## CURING SCHEDULE

Surface Temp.	Dry to Handle	Dry to Recoat	Final Cure
4°C (39°F)	10 Hours	10 Hours	14 Days
16°C (61°F)	6 Hours	6 Hours	10 Days
24°C (75°F)	3 Hours	3 Hours	7 Days
32°C (90°F)	30 Minutes	30 Minutes	5 Days

These times are based on 50 micron dry film thickness. Higher fill thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure.

## CLEANUP & SAFETY

<b>Cleanup</b>	Use Thinner 2 or acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.
<b>Safety</b>	Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Hypersensitive persons should wear protective clothing, gloves and use protective cream on face, hands and all exposed areas.
<b>Ventilation</b>	When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved supplied air respirator.
<b>Caution</b>	Contains flammable solvents, keep away from flames and sparks. All electrical installations must be earthed. In areas where there is a danger of explosion, operators must use non-ferrous tools and non-sparking shoes.

## PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	Part A & B: 24 months at 24°C.
<b>Shipping Weight (Approximate)</b>	5 Liter 6,65 KG 20 Liter 26,5 KG
<b>Storage Temperature &amp; Humidity</b>	4°C-43°C 0-90% Relative Humidity
<b>Flash Point (Setflash)</b>	Part A: 25°C Part B: 38°C

# Carbothane PU 134 LG

## PRODUCT DATA SHEET

---



## PACKAGING, HANDLING & STORAGE

---

**Storage** | Store indoors and frost-free.

## WARRANTY

---

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.