

## SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	Single package, water-based, flexible mastic fire protective coating for cables and cable trays.
<b>Description</b>	A water based mastic that can be applied to electrical cables to retard fire propagation. Once applied, it meets code and insurance requirements for interior and exterior use. It provides a hard and flexible surface that will not dust, flake, or spall.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Flexible</li> <li>• Hard, dust free surface</li> <li>• Allows easy replacement of cables</li> <li>• Water-based product, low odor</li> <li>• Asbestos-Free – complies with EPA and OSHA regulations</li> <li>• Does not de-rate cables</li> <li>• Weathering – approved for exterior use</li> <li>• Quality Manufactured – under strict Carboline quality standards</li> </ul>
<b>Color</b>	Grey
<b>Finish</b>	Textured Textured finish varies depending on the method of application.
<b>Primer</b>	Primer is not required.
<b>Fireproofing Wet Film Thickness</b>	1900 microns
<b>Fireproofing Dry Film Thickness</b>	1000 microns
<b>Solids Content</b>	By Volume 53% +/- 2%
<b>Theoretical Coverage Rates</b>	0.53 m <sup>2</sup> /l at 1000 microns
<b>VOC Values</b>	<b>As Supplied</b> : 0.24 lb/gal (29 g/l)
<b>Limitations</b>	Not recommended for long-term surface temperatures over 195°F (91°C) in continuous use, 220°F (104°C) in non-continuous use.
<b>Topcoats</b>	Topcoats are generally not required. In severely corrosive atmospheres, contact Carboline Technical Service for a topcoat recommendation most suitable for the operating environment.

## SUBSTRATES & SURFACE PREPARATION

<b>General</b>	Before applying Thermo-Lag® 270 to electrical cables, the cables must be dry and free of all oil, grease, condensation or any other contamination.
----------------	--

# Thermo-Lag 270

## PRODUCT DATA SHEET



### PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

Test Method	System	Results
ASTM D2240 Hardness	Thermo-Lag 270	Shore D - 30-40
ASTM E84 Surface Burning	Thermo-Lag 270	Class A
DEFSTAN 02-711-2 Smoke Index	Thermo-Lag 270	Class A
EPS 96202 Ampacity	Thermo-Lag 270	No de-rating
IEC 60331-1 Fire resistance circuit integrity	Thermo-Lag 270	50 minutes @ 1.60 mm (1/16")
IEC 60331-21 Fire resistance circuit integrity	Thermo-Lag 270	80 minutes @ 1.64 mm (cable type 3x6mm <sup>2</sup> )
IEC 60331-21 Fire resistance circuit integrity	Thermo-Lag 270	90 minutes @ 1.00 mm (cable type 3x6mm <sup>2</sup> )
IEC 60332-3-22 Flame Propagation	Thermo-Lag 270	2 hours @ 1.60 mm (1/16")
IEC 60754 Halogen Gas Content	Thermo-Lag 270	Pass (<5.0 mg/g HCL)

\*All values derived under controlled laboratory conditions.

\*Test reports and additional information available upon written request.

### TYPICAL CHEMICAL RESISTANCE

Exposure	Fumes	Splashes & Spills
Acids	Very Good	Fair
Alkalies	Very Good	Fair
Salt	Excellent	Very Good
Solvents	Good	Good

### MIXING & THINNING

**Mixer** | Use 23 mm (1/2") electric or air driven drill with a slotted paddle mixer (300 rpm under load).

**Mixing** | Thermo-Lag® 270 must be mixed using a 1/2" electric or air driven drill with a slotted paddle or Jiffy mixer blade. Mix material for a minimum of 5 minutes to achieve the necessary texture required before spraying.

**Thinning** | Thermo-Lag® 270 may be thinned with clean potable water up to 5% by volume.

### APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

**Air Spray** | Graco 5:1 Bulldog with Even-Flo regulator valve, 4.6 gpm (17 lpm) output  
Graco 10:1 President with Even-Flo regulator valve, 1.7 gpm (6.4 lpm) output  
Air line must be a minimum 6.9 kPa (100 psi). Use 9 mm (3/8") I.D. line from gun to Even-Flo regulator valve with an air adjusting valve attached at the gun end for atomization control.

**Airless Spray** | Graco 30:1 Bulldog, 3.0 gpm (11.0 lpm) output (6.4 lpm) output

## APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

<b>Spray Gun</b>	<p>For Airless Spray Use: Graco Mastic Golden Gun with Graco HDRAC 1.50-1.6 mm (00.059" - 0.063") tips</p> <p>For Air Spray Use: Binks 7E2 Gun with 47-49 fluid tip / 9,53 mm (3/8") or 12,7 mm (1/2") air cap Graco 204000 Gun with 164331 fluid tip / 160658 air cap</p>
<b>Material Hose</b>	<p>3/4" (19 mm) I.D. minimum (50') is recommended for all pump recommendations listed. For hose lengths over 50' (15.3 m), a 1-1/2" I.D. hose is recommended. A 10' (3 m) 3/4" (19 mm) whip hose may be added to better facilitate handling.</p> <p>Minimum bursting pressure on material lines should be 1000 psi (68.9 kPa) when using 5:1 or 10:1 pumps. When using a 30:1 pump, the minimum bursting pressure should be 3,000 psi (206.7 kPa).</p>
<b>Compressor</b>	<p>Be certain that the air supply is a minimum of 75 cfm @ 100 psi (6.9 kPa). Air volume and pressure required will depend on equipment used.</p>

## APPLICATION PROCEDURES

<b>General</b>	<p>Thermo-Lag® 270 may be applied by spray, trowel or hand application. When spray applying, Thermo-Lag® 270 must be thinned 5% by volume (1 quart water per 5 gallons maximum). A single coat built up with a number of quick passes allows greater control over quantities, thickness and finish. In most conditions, it is advantageous to apply two thin coats rather than one thick coat.</p>
<b>Application Rates</b>	<p>At an ambient temperature of 70°F (21°C), apply 1/8" (3mm) per coat (wet)</p>
<b>Wet Film Thickness</b>	<p>Frequent thickness measurements with a wet film gauge are recommended during the application process to ensure uniform thickness.</p>
<b>Palming</b>	<p>Hand application of Thermo-Lag® 270 may be more economical when cables are "ganged" or for protecting individual strands. Rubber gloves are recommended</p>
<b>Trowel</b>	<p>A standard plasterer's hawk and trowel may be used for suitable applications. Selection of instruments is left to the discretion of the applicator.</p>

## APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	10°C (50°F)	4°C (40°F)	4°C (40°F)	0%
Maximum	43°C (110°F)	35°C (95°F)	35°C (95°F)	90%

\*Air and substrate temperature must be at least 40°F (4.4°C) and rising. Surface temperature should be a minimum of 5°F (3°C) above the dew point. The maximum humidity is 90%. Area must be protected from rain or running water during application until material is cured. Minimum ambient temperatures must be maintained for 24 hours after application.

## CURING SCHEDULE

Surface Temp.	Dry to Touch	Final Cure Time
21°C (70°F)	24 Hours	15 Days

\*Curing times are dependent on thickness, humidity and temperature. Normal dry times are based on a wet thickness of 1/8" (3.2 mm).

# Thermo-Lag 270

## PRODUCT DATA SHEET



### CLEANUP & SAFETY

<b>Cleanup</b>	Pump, gun, tips and hoses should be cleaned with clean, potable water at least once every 4 hours at 70°F (21°C) and more often at higher temperatures.
<b>Safety</b>	Follow all safety precautions on the Thermo-Lag® 270 Material Safety Data Sheet. It is recommended that personal protective equipment be worn including spray suits, gloves, eye protection and respirators when applying Thermo-Lag® 270.
<b>Overspray</b>	All adjacent and finished surfaces shall be protected from damage and overspray. Wet overspray may be cleaned with soapy or clean potable water. Cured overspray may require chipping or scraping to remove.
<b>Ventilation</b>	In enclosed areas, ventilation shall not be less than 4 complete air exchanges per hour until the material is dry.
<b>Caution</b>	Thermo-Lag® 270, like most water based coatings, is electrically conductive until it is dry. Extreme caution should be exercised when the material is applied to energized cables and equipment. The material should never be applied without the supervision of plant safety personnel.

### TESTING / CERTIFICATION / LISTING

<b>Intertek</b>	Thermo-Lag 270 has been successfully tested at Intertek laboratories to the following international test standards: <b>IEC 60331-1</b> - Tests for electric cables under fire conditions - Circuit integrity - Part 1: Test method for fire with shock at a temperature of at least 830°C for cables of rated voltage up to and including 0,6/1,0 kV and with an overall diameter exceeding 20 mm <b>IEC 60332-3-22</b> - Tests on electric and optical fibre cables under fire conditions - Part 3-22: Test for vertical flame spread of vertically-mounted bunched wires or cables - Category A <b>IEC 60754-1</b> - Test on gases evolved during combustion of materials from cables - Part 1: Determination of the halogen acid gas content <b>DEFSTAN 02-711-2</b> - Determination of the Smoke Index of the Products of Combustion from Small Specimens of Materials
<b>BRE Global Ltd</b>	Thermo-Lag 270 has been successfully tested at Bre Global Ltd laboratories to the following international test standards: <b>IEC 60331-21</b> - Tests for electric cables under fire conditions - Circuit integrity - Part 21: Procedures and requirements - Cables of rated voltage up to and including 0,6/1,0 kV
<b>EXOVA Warringtonfire</b>	Thermo-lag 270 has been successfully tested at Bre Global Ltd laboratories to the following international test standards: <b>IEC 60331-21</b> - Tests for electric cables under fire conditions - Circuit integrity - Part 21: Procedures and requirements - Cables of rated voltage up to and including 0,6/1,0 kV

### PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	18 Months *Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.
<b>Shipping Weight (Approximate)</b>	20 kg (16.53 litres)
<b>Flash Point (Setaflash)</b>	>300°F (148°C)

---

## **PACKAGING, HANDLING & STORAGE**

---

**Storage** | Store indoors in a dry environment between 40°F - 110°F (4.4°C - 43.3°C). Keep from freezing.

**Packaging** | 20 kg (16.53 litres)

## **WARRANTY**

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.