

## SÉLECTION & CARACTÉRISTIQUES

<b>Type générique</b>	Gypsum based fire resistant mortar with thermal insulation properties for passive fire protection.
<b>Description</b>	Fireproof and ecological mortar for the passive fire protection of steel, concrete, composite concrete-steel sheet slab structural elements, fire compartmentation and fire stop partitions. Fire resistance of up to 4 hours depending on the construction system.
<b>Caractéristiques</b>	<ul style="list-style-type: none"> <li>• Formulation with light high-performance fillers.</li> <li>• Non-combustible.</li> <li>• Can be sprayed by discontinuous machine to improve its performance by 15%.</li> <li>• Asbestos free – Complies with regulations 2003/18/EC and RD 396/2006.</li> <li>• Good adhesion on different substrates.</li> <li>• Light and low abrasion with the use of spraying equipment. Saving on consumables.</li> <li>• Low protection thicknesses. Saving on transport and labour.</li> <li>• Wide range of fire solutions.</li> </ul> <p><b>Environmental Certifications</b>            EPD - Environmental Product Declaration            Cradle to Cradle (C2C) Certification            VOC content and emission (EN 16516)            LEED Compliance (VOC Emission)</p>
<b>Couleur</b>	Antique white
<b>Finition</b>	Texturé Can be smoothed
<b>Primaire</b>	PERLIFOC HP Eco+ can be applied on bare steel and on primed steel, and it is compatible with different primer families as stated on its CE marking. For application on other substrates such as galvanised steel, concrete and masonry, no prior priming or bonding bridge is required. Contact the Perlita y Vermiculita SLU technical service for further information. PERLIFOC HP Eco+ does not promote or prevent corrosion.
<b>Epaisseur d'application</b>	30 mm maximum thickness per coat
<b>Rendement théorique</b>	3.5 ± 15% Kg/m <sup>2</sup> /cm (BATCH-MIX machine) <sup>1</sup> 4.1 ± 15% Kg/m <sup>2</sup> /cm (CONTINUOUS machine) <sup>2</sup> <sup>1</sup> Average value obtained under laboratory conditions, with a mixing speed of 60 rpm for 90 seconds. If any of these parameters are changed, both the final density and the performance could vary. Lower density at higher speed, and higher density with a shorter mixing time. <sup>2</sup> Average value obtained under laboratory conditions.
<b>Limites</b>	It is not designed for exteriors beyond the normal construction phases and timescales. It must not be exposed to the rain or water leakage. It is not recommended as a refractory mortar or where normal operating temperatures exceed 90°C.
<b>Finitions</b>	Generally not necessary. In highly corrosive atmospheres, consult the Perlita y Vermiculita, SLU Technical Service for the selection of the most appropriate coating for the work environment.

### SUPPORTS & PRÉPARATION DE SURFACE

<b>Général</b>	Before application, all the substrates must be clean and free of loose particles, dirt, oil, grease, condensation or any other substance that may affect the adhesion. Contact the Perlita y Vermiculita SLU technical service for further information.
<b>Acier Galvanisé</b>	PERLIFOC HP Eco+ can be directly applied to galvanised steel without the need for priming or an adhesion promoter. Ensure that the substrate is clean, free of loose particles, dirt, grease, condensation or salts that could affect the adhesion. Contact the Perlita y Vermiculita SLU technical service for further information.
<b>Béton</b>	PERLIFOC HP Eco+ can be directly applied to concrete without the need for priming or an adhesion promoter. Ensure that the substrate is clean, free of loose particles, decorative paints, dirt, grease or condensation that could affect the adhesion. If there are doubts about the condition of the substrate or it has an old coating, the use of a metal mesh prior to the application of the mortar is recommended. Contact the Perlita y Vermiculita SLU technical service for further information.
<b>Painted/Primed Structural Steel</b>	If the steel structure is not primed, it must be cleaned using an abrasive material to an Sa 2 ½ grade of cleanliness, in accordance with ISO 8501 or equivalent. If it is primed, this must be clean, free of loose particles, dirt, grease or condensation that could affect the adhesion. Furthermore, it must be ensured that the existing primer is compatible with the PERLIFOC HP Eco + mortar, in accordance with the CE marking. Mesh is not required in any case, although its use is recommended on beam flanges wider than 500 mm, on columns with only one sprayed face and profiles subject to high deformations. Contact the Perlita y Vermiculita SLU technical service for further information.

### DONNÉES DE PERFORMANCE

Toutes les données des tests sont obtenues en conditions de laboratoire. Les résultats sur site peuvent varier.

Méthode d'essai	Résultats
Adhesion	=0.1 MPa (In accordance with EGOLF SM/5)
Apparent Density	350 ± 15% Kg/m <sup>3</sup>
Asbestos	Does not contain asbestos
Flexural Strength	= 0.2 MPa
Hardened Density	=480 ± Kg/m <sup>3</sup> (BATCH-MIX machine) <sup>1</sup> 550 ± 15% Kg/m <sup>3</sup> (CONTINUOUS machine) <sup>2</sup>
Reaction to Fire	A1 (In accordance with EN 13501-1)
Resistance to Compression	= 0.2 MPa
Sound Absorption	aw=0.2 (In accordance with UNE-EN-ISO 354 and 20 mm thickness) NRC=0.2 (In accordance with ASTM C423 and 20 mm thickness)
Thermal Conductivity	0.087 W/mK
Yield	3.5 ± 15% Kg/m <sup>2</sup> /cm (BATCH-MIX machine) <sup>1</sup> 4,1 ± 15% Kg/m <sup>2</sup> /cm (CONTINUOUS machine) <sup>2</sup>

<sup>1</sup> Average value obtained under laboratory conditions, with a mixing speed of 60 rpm for 90 seconds. If any of these parameters are changed, both the final density and the performance could vary. Lower density at higher speed, and higher density with a shorter mixing time.

<sup>2</sup> Average value obtained under laboratory conditions.

## MÉLANGE & DILUTION

<b>Mixer</b>	<p>1. BATCH-MIX. Use a gypsum mortar mixer or similar with a capacity of at least 100 litres and capable of rotating at 60 rpm with rubber-tipped blades that wipe the sides of the hopper.</p> <p>2. CONTINUOUS. Contact the Perlita y Vermiculita SLU technical service for recommendations. Densities may vary when using this type of mixing equipment.</p>
<b>Mélange</b>	<p>Always mix with clean drinking water. The mixer should be kept clean and free of any previously mixed material which could cause premature setting of the product. A 2 bag mix with discontinuous machines is recommended. The mixing time should be approximately 1.5 minutes when mixing at 60 rpm. Use <math>15.3 \pm 1.7</math> litres of water per 17 kg bag. First add water to the hopper with the blades stopped. With the mixer on, add mortar to the water and start to mix.</p>
<b>Densité</b>	<p>To obtain information and recommendations on how to obtain adequate density and performance, contact the sales or technical Department of Perlita y Vermiculita SLU.</p>
<b>Working Time</b>	<p>1 hour at 20°C, the higher the temperature the shorter the usage time. These times are for guidance and can vary depending on the ambient humidity and air currents. The useful life of the material ends when it hardens and becomes unusable.</p>

## EQUIPEMENT D'APPLICATION

Ci-dessous informations générales de l'équipement à utiliser. Les conditions sur site peuvent demander la modification de ces caractéristiques pour l'obtention du résultat souhaité.

<b>Pompe</b>	<p>This material may be pumped with a wide range of piston, rotor, stator and compressor pumps designed for pumping cement and plaster materials, including:</p> <p>PFT – model # ZP 3 L Multimix (Batch-mix)</p> <p>Putzmeister – model # S5EV (Batch-mix)</p> <p>Wall Goe – model # JP70-L. (Batch-mix)</p> <p>Putzmeister – model # MP25 (Continuous)</p> <p>PFT – model # G4 Smart (Continuous)</p> <p>Essick – model # FM9/FM5E (Continuous)</p> <p>Hy-Flex – model # HZ-30E (Continuous)</p>
<b>Ball Valves</b>	<p>Ball valves must be fitted on at least one end of the spray hose to facilitate cleaning.</p>
<b>Hose Length</b>	<p>Use a flexible spray hose of between 5 and 10 m in length and at least 25 mm inner diameter. Working pressure at least 30 bar.</p>
<b>Buses/Pistolet</b>	<p>From 10 to 16 mm depending on the desired finish.</p>
<b>Compresseur</b>	<p>The pump compressor must be capable of maintaining a minimum of 2 bar (30 psi) and from 250 to 300 l/min at the nozzle.</p>
<b>Air Line</b>	<p>Use a line with an inner diameter of 16 mm. Hose with a minimum burst pressure of 7 bar (100 psi).</p>
<b>Spray Lance</b>	<p>Minimum length of 600 mm and minimum inner diameter of 25 mm. With material shut-off ball valve and air shut-off valve.</p>

## PROCÉDURES D'APPLICATION

**Général** | Thicknesses of 30 mm or less can be applied in one pass. When additional coats are required to reach the specified thickness, it is recommended to apply the subsequent coats once the previous coat has started to set. If the previous coat has set and is dry, wet the surface with water before applying additional coats. Contact the Perlita y Vermiculita SLU technical service if further information is required.

**Finition** | Normally the finish is a sprayed texture.

## CONDITIONS D'APPLICATION

Condition	Matériau	Surface	Ambiante	Humidité
Minimum	3°C (37°F)	3°C (37°F)	3°C (37°F)	0%
Maximum	38°C (100°F)	52°C (126°F)	43°C (109°F)	90%

The air and ambient temperatures must be maintained 24 hours before, during and after the application. Gypsum-based mortars are sensitive to water and therefore must be adequately protected. For additional recommendations, contact the Perlita y Vermiculita, S.L.U. technical department.

## TEMPS DE SÉCHAGE

Temp. de surface	Sec pour être surcouché
25°C (77°F)	2 Heures

The new coat application times are for guidance and could vary depending on the ambient conditions and air currents. In enclosed areas with little ventilation (basements, confined spaces, etc.), for the mortar to dry properly, it is recommended that the RH does not exceed 60% and there is adequate ventilation, which means at least 4 complete changes of air per hour until the material is dry (or for at least 2 weeks after the end of the application).

## NETTOYAGE & SÉCURITÉ

**Nettoyage** | The case, mixer and the hoses should be cleaned with drinking water. Pass sponges or plenty of water through the hoses to remove any material residue that remains in them. Excess wet sprayed mortar should be cleaned with clean drinking water. Dry sprayed mortar may require scraping off to remove it.

**Sécurité** | Follow all the safety precautions described in the safety data sheet for the mortar. The use of personal protective equipment is recommended, including overalls, gloves and eye protection.

**Overspray** | Adjacent surfaces should be protected against damage and splashing. Sprayed fireproof materials can be difficult to remove from surfaces and can damage architectural finishes.

**Ventilation** | In enclosed areas, ventilation must be no less than 4 complete air exchanges per hour until the material is dry.

## TEST / CERTIFICATION / RÉFÉRENCEMENT

EN Standards	<i>Fire Resistance to EN standards conducted in accredited laboratories:</i>
	<b>Protection of structural steel elements (EN 13381-4)</b>
	Open beams and columns and tubular profiles up to R240
	<b>Protection of structural concrete elements (EN 13381-3)</b>
	Columns, beams, slabs and walls up to REI 240
	<b>Protection of concrete/profiled sheet steel composite members (EN 13381-5)</b>
	Protection of mixed slabs up to REI 180
	<b>Non loadbearing divisions (EN 1364-1)</b>
	Vertical compartment walls classified up to EI 120
	<b>Fire break strips (following the Spanish Ministry of industry)</b>
	Strap anchored system up to EI 180

## CONDITIONNEMENT, MANUTENTION & STOCKAGE

Durée de vie	12 months
Poids (Approximatif)	17 kg/bag
Stockage	Store indoors and in dry environments between 0°C and 50°C.
	Material must be kept dry or clumping of material may occur.
Conditionnement	42 bags/pallet

## GARANTIE

Au meilleur de nos connaissances, les données techniques contenues dans le présent document sont véridiques et exactes à la date de leur publication et sont susceptibles d'être modifiées sans préavis. Les utilisateurs doivent contacter la société Carboline pour vérifier la conformité du produit avant de l'installer ou de passer commande. Aucune garantie de précision n'est expresse ou implicite. Nous garantissons que nos produits sont conformes au contrôle qualité de Carboline. Nous n'assumons aucune responsabilité pour la couverture, la performance ou les blessures liées à l'utilisation. La responsabilité, le cas échéant, est limitée au remplacement des produits. AUCUNE AUTRE GARANTIE D'AUCUNE SORTE N'EST DONNÉE PAR CARBOLINE, QU'ELLE SOIT EXPRESSE OU IMPLICITE, STATUTAIRE, EN VERTU DE LA LOI OU AUTRE, Y COMPRIS À CARACTÈRE COMMERCIAL ET D'ADÉQUATION À UNE UTILISATION SPÉCIFIQUE. Toutes les autres marques auxquelles il est fait référence ici sont la propriété de Carboline International Corporation, sauf indication contraire.