

**SELECTION & SPECIFICATION DATA**

|                                  |   |
|----------------------------------|---|
| <b>Generic Type</b>              | Polymeric epoxy amine.  |
| <b>Description</b>               | Rustbond FC is a cross-linked penetrating primer/sealer with excellent wetting properties. It is highly flexible with good chemical and solvent resistance, and accept a variety of topcoats. Recommended use as primer/sealers for marginally prepared steel and over old coatings. Its excellent wetting properties allows it to penetrate rust and discontinuities in existing coatings and provide a firm anchorage for a variety of topcoats. Its thixotropic character reduces run off, ensuring that the edges of existing coatings are encapsulated thus reducing undercutting and peeling. It may also be used as a tie-coat for coatings that exceed their "recoat window." Consult Carboline Technical Services Department for specific recommendations. |
| <b>Features</b>                  | <ul style="list-style-type: none"> <li>• Universal primer and tie-coat</li> <li>• Cures down to 35°F (2°C)</li> <li>• Excellent adhesion to SSPC-SP 2 prepared steel, galvanizing, aluminum, stainless steel and copper</li> <li>• Low stress, highly flexible film</li> <li>• Extremely high solids</li> <li>• Low odor</li> <li>• Contains corrosion inhibitors</li> <li>• Compatible with a variety of topcoats</li> <li>• User friendly brush and roller application</li> <li>• VOC compliant to current AIM regulations</li> </ul>   |
| <b>Color</b>                     | Translucent Green (0300)  |
| <b>Finish</b>                    | High Gloss (85-100)<br>Chalks rapidly in sunlight.  |
| <b>Primer</b>                    | Self-priming. May be applied over most generic types of coatings.   |
| <b>Dry Film Thickness</b>        | 25 - 51 microns (1 - 2 mils) per coat   |
| <b>Solids Content</b>            | By Volume 90% +/- 1%  |
| <b>Theoretical Coverage Rate</b> | 35.4 m <sup>2</sup> /l at 25 microns (1444 ft <sup>2</sup> /gal at 1.0 mils)<br>17.7 m <sup>2</sup> /l at 50 microns (722 ft <sup>2</sup> /gal at 2.0 mils)<br>Allow for loss in mixing and application.  |
| <b>VOC Values</b>                | <p><b>As Supplied</b> : 0.9 lbs./gal (108 g/l) EPA Method 24<br/>           Thinner 2 : 7 oz/gal: 1.22 lbs/gal (147 g/l)<br/>           Thinner 76 : 8 oz/gal: 1.24 lbs/gal (149 g/l)</p> <p>These are nominal values</p>   |
| <b>Dry Temp. Resistance</b>      | <p>Continuous: 79°C (175°F)<br/>           Non-Continuous: 93°C (200°F)</p> <p>Discoloration and loss of gloss is observed above 175°F (80°C)</p>   |
| <b>Limitations</b>               | <ul style="list-style-type: none"> <li>• Epoxies lose gloss, discolor and eventually chalk in sunlight exposure</li> <li>• <b>Do not use for immersion service</b></li> <li>• Rustbond sealers must be topcoated</li> </ul>   |
| <b>Topcoats</b>                  | Acrylics, alkyds, epoxies, polyurethanes  |

# Rustbond FC

PRODUCT DATA SHEET



## SUBSTRATES & SURFACE PREPARATION

|                                    |   |
|------------------------------------|---|
| <b>General</b>                     | Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.                   |
| <b>Steel</b>                       | SSPC-SP2 or SP3   |
| <b>Previously Painted Surfaces</b> | A test patch is recommended to verify compatibility with existing coating. Existing paint must attain a minimum 3A rating in accordance with ASTM D3359 "X-Scribe" adhesion test. |

## MIXING & THINNING

|                 |  |
|-----------------|--|
| <b>Mixing</b>   | Power mix components separately to break down any gel. Keep the mixing blade at slow speed and submerged in the product to minimize whipping of air into the material. Scrape the sides of the container occasionally to insure uniformity. Continue to mix for 1-2 minutes. <b>DO NOT MIX PARTIAL KITS</b> , and do not intermix unpaired components. |
| <b>Thinning</b> | Thinning not normally required but may be thinned up to 6% (8 oz/gal) with Thinner #76 or Thinner #2. Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether express or implied.  |
| <b>Ratio</b>    | <b>.5 Gallon Kit</b><br>Part A: 1 Quart (0.25 gal)<br>Part B: 1 Quart (0.25 gal)<br><b>2 Gallon Kit</b><br>Part A: 1 Gallon<br>Part B: 1 Gallon  |
| <b>Pot Life</b> | For 1/2 gal units:<br>45 minutes at 75°F (28°C)<br>90 minutes at 40°F and longer at lower temperatures.<br><b>Do not use above 75°F (28°C) material temperature.</b><br>Pot life ends when material begins to thicken and exotherm.  |

## APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

|                                     |  |
|-------------------------------------|--|
| <b>Spray Application (General)</b>  | Contact Carboline Technical Service for specific application instructions.   |
| <b>Brush &amp; Roller (General)</b> | Avoid excessive re-brushing or re-rolling. Apply enough material to uniformly wet the surface. Any puddles formed must be brushed out. |
| <b>Brush</b>                        | Use a medium bristle brush and distribute evenly using full brush strokes.   |
| <b>Roller</b>                       | Use a medium to long nap roller suitable for solvent base materials to evenly distribute the material.                                 |

## APPLICATION CONDITIONS

| Condition | Material    | Surface     | Ambient     | Humidity |
|-----------|-------------|-------------|-------------|----------|
| Minimum   | 4°C (40°F)  | 2°C (35°F)  | 2°C (35°F)  | 0%       |
| Maximum   | 24°C (75°F) | 32°C (90°F) | 32°C (90°F) | 90%      |

This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions.

## CURING SCHEDULE

| Surface Temp. | Dry to Handle | Dry to Topcoat | Final Cure General |
|---------------|---------------|----------------|--------------------|
| 2°C (35°F)    | 23 Hours      | 23 Hours       | 9 Days             |
| 10°C (50°F)   | 18 Hours      | 18 Hours       | 6 Days             |
| 24°C (75°F)   | 6 Hours       | 6 Hours        | 3 Days             |
| 32°C (90°F)   | 3 Hours       | 3 Hours        | 2 Days             |

These times are based on 50% relative humidity and 1.0–2.0 mils (25-50 microns) dry film thickness. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure. Excessive humidity or condensation on the surface during curing can interfere with the cure, can cause discoloration and may result in a surface haze. Any haze or blush must be removed by water washing before recoating. During high humidity conditions, it is recommended that the application be done while temperatures are increasing.

| Surface Temp. | Maximum Recoat Time<br>Acrylics & Alkyds | Maximum Recoat Time<br>Epoxyes & Urethanes |
|---------------|--|--|
| 2°C (35°F)    | 7 Days                                   | 21 Days                                    |
| 10°C (50°F)   | 7 Days                                   | 21 Days                                    |
| 24°C (75°F)   | 7 Days                                   | 21 Days                                    |

## CLEANUP & SAFETY

|                    |   |
|--------------------|---|
| <b>Cleanup</b>     | Use Thinner #2 or Acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.  |
| <b>Safety</b>      | Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions.  |
| <b>Ventilation</b> | When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved respirator.  |
| <b>Caution</b>     | <b>THIS PRODUCT EXOTHERMS AT THE END OF ITS POT LIFE.</b> Any unused quantities will become extremely hot. Immediately spread out on an appropriate surface or add sand or other suitable heat sink to the unused material to reduce the severity of exotherm. Take appropriate precautions against breathing fumes. This product contains flammable solvents. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workmen should be required to use non-ferrous tools and wear conductive and non-sparking shoes. |

# Rustbond FC

PRODUCT DATA SHEET



---

## PACKAGING, HANDLING & STORAGE

---

|  |   |
|--|---|
| <b>Shelf Life</b>                              | Part A & B: Min. 36 months at 75°F (24°C)<br>*Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers. |
| <b>Shipping Weight (Approximate)</b>           | 0.5 Gallon Kit - 5 lbs. (2.2 kg)<br>2 Gallon Kit - 19 lbs. (8.6 kg)   |
| <b>Storage Temperature &amp; Humidity</b>      | 40° - 110°F (4°-43°C)<br>0-90% Relative Humidity  |
| <b>Flash Point (Pensky Martens Closed Cup)</b> | • Part A: 45°F (7.2°C)<br>• Part B: 42°F (6°C)  |
| <b>Storage</b>                                 | Store Indoors.  |

## WARRANTY

---

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.