

SELECTION & SPECIFICATION DATA

Generic Type	Water borne acrylic latex
Description	A high quality acrylic latex coating formulated from durable 100% acrylic resins to protect and beautify exterior surfaces.
Features	<ul style="list-style-type: none"> • Excellent UV and weathering resistance • Semi-gloss finish • Meets the most stringent VOC (Volatile Organic Content) regulations • Used as a topcoat for primers when used over steel substrate • Protection of concrete or masonry in new or maintenance applications • Not recommended for immersion service
Color	White & Pastel shades only. May require multiple coats for adequate hiding.
Finish	Semi-gloss
Dry Film Thickness	50 Microns
Solid(s) Content	By Volume 36% ± 2%
Theoretical Coverage Rates	7.2m ² /litre at 50 microns NOTE: Material losses during mixing and application will vary and must be taken into consideration when estimating job requirements.
VOC Values	As Supplied : 24 g/l
Dry Temp. Resistance	Continuous: 77°C (171°F) Non-Continuous: 93°C (199°F) Coating may discolour

SUBSTRATES & SURFACE PREPARATION

General	Remove any dirt, oil, grease or other contaminants from surface to be coated by washing with water-rinseable alkaline detergent, followed by a thorough rinse with clean potable water.
Steel	Apply over clean, dry, recommended primers.
Concrete	Apply over clean, dry, recommended surfacer or primer. Can be applied directly to dry concrete where an uneven surface can be tolerated. Remove laitance by abrasive blasting or other means. Do not coat concrete treated with hardening solutions unless test patches indicate satisfactory adhesion. Do not apply coating unless concrete has cured at least 28 days at 21°C and 50% RH or equivalent time.

MIXING & THINNING

Mixing	Mix to a smooth consistency with mechanical agitator such as a "Jiffy" mixer.
Thinning	Thin up to 10% by volume with clean potable water if required.

Carbocrylic 3350

PRODUCT DATA SHEET



APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Conventional Spray	Pressure pot equipped with dual regulators, 10mm minimum I.D. material hose, 1.8mm fluid tip and appropriate air cap. Gun: 905 Spray Gun Fluid Tip: 1.8mm Air Cap: 905-PV
Airless Spray	* Teflon packings are recommended and are available from the pump manufacturer.
Brush	Use synthetic bristle brush, applying with full strokes. Avoid excessive re-brushing.
Roller	Use a short nap mohair roller with phenolic core. Avoid rerolling. Multiple coats may be required for uniform hiding when applied by brush or roller.

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	10°C (50°F)	10°C (50°F)	10°C (50°F)	0%
Maximum	38°C (100°F)	50°C (122°F)	49°C (120°F)	90%
Optimum	23°C (73°F)	24°C (75°F)	25°C (77°F)	45%

Do not apply when the surface temperature is less than 2°C above the dew point. Water-based products are sensitive to moisture during curing. Do not apply if the temperatures are expected to drop below 10°C within 24 hours of application, or if rainfall is imminent.

Special thinning and application techniques may be required above or below normal conditions.

NOTE: High humidity will lengthen cure times due to slower water evaporation rate.

CURING SCHEDULE

Surface Temp.	Dry to Recoat	Final Cure
10°C (50°F)	8 Hours	60 Hours
16°C (61°F)	4 Hours	36 Hours
25°C (77°F)	3 Hours	24 Hours
32°C (90°F)	1 Hour	12 Hours

Curing Details | Relative Humidity: 50%

CLEANUP & SAFETY

Cleanup	Use warm, soapy water. If material has dried or if equipment is to be used with solvent-based coatings, use Thinner # 2.
Safety	Read and follow all caution statements on this product data sheet and on the material safety data sheet for this product. Employ normal workmanlike safety precautions. Use adequate ventilation and wear gloves or use protective cream on face and hands if hypersensitive. Keep container closed when not in use.

CLEANUP & SAFETY

Caution	Read and follow all caution statements on this product data sheet and on the material safety data sheet for this product.
	Water-based product. Keep above 0°C. Employ normal workmanlike safety precautions. Keep container closed when not in use. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

PACKAGING, HANDLING & STORAGE

Shelf Life	24 Months minimum when stored at 25°C
	*Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.
Shipping Weight (Approximate)	5 Litre: Carbocrylic 3350: 7kg
Storage Temperature & Humidity	10 to 43°C 0 to 90% Store indoors. Do not allow product to freeze.
Flash Point (Pensky Martens Closed Cup)	Carbocrylic 3350: >93°C

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.