

SELECTION & SPECIFICATION DATA

Generic Type	Reflective fibre reinforced aluminium coating
Description	Alumanation 301 is a premium grade, industrial maintenance, self-priming, high build aluminium coating formulated from specially processed polymers, a proprietary blend of natural and synthetic fibres, and a fine aluminium pigment. Alumanation 301 contains no asbestos. It reflects heat, prevents corrosion and protects against mild acid and alkali fumes on a variety of substrates, including metal, concrete, transite, built-up roofing and modified bitumen.
Features	<ul style="list-style-type: none"> • Used for the rust proofing and weatherproofing of metal roofs, sidewalls, tanks, bridges, structural steel, electrical transmission towers, piping, guard rails, etc. • Can be applied in colder temperatures than its water-based counterpart. • The thick one-coat application makes it a very economical and easy to use product. • Aluminium finish is highly reflective, protecting the roof from harmful UV as well as keeping building cooling costs to a minimum.
Color	Aluminium
Finish	Eggshell (10-25)
Dry Film Thickness	200 microns – Inland Environment 300 microns – Coastal & Industrial Environment
Solid(s) Content	By Mass: 61% ± 1% By Volume: 47% ± 1%
Theoretical Coverage Rates	2.35m ² /litre at 200 microns 1.57m ² /litre at 300 microns The surface dictates the actual coverage.
Limitations	Do not apply when the air or surface temperature is below 5°C or when rain is imminent. Not recommended for use over tar surfaces, slate, tile, wood, shingles or where water continuously ponds. Do not apply over newly installed asphalt built-up roofs without allowing the roof to cure for a minimum of 90 days.
Flexibility	Passes 6mm diameter mandrel bend at 0°C
Specific Gravity	1.06 ± 0.02

SUBSTRATES & SURFACE PREPARATION

General	Remove all debris, dirt, dust and loose gravel by sweeping with a stiff broom or power cleaning equipment or by using high pressure power wash. Remove any oil or grease from surface to be coated. All surfaces must be clean and dry.
Metal	Rust and flaking or peeling paint shall be wire brushed, scraped or pressure washed to ensure a sound surface. No priming is necessary because of the rust inhibiting oils in Alumanation 301. Seams, fasteners and protrusions shall be repaired as needed. Refer to Alumanation 301 Specification Guide.
Other Aged Finishes	Build-up Roofing: Torn flashings, faulty copings, parapet walls, large blisters and surface breaks shall be repaired.

Alumanation 301

PRODUCT DATA SHEET



APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

General	Apply Alumanation 301 by brush, roller or spray. Do not apply when the surface temperature is less than 3°C above the dew point. Precautions should be taken to prevent overspray from settling on nearby objects or structures when spraying in windy conditions. Maintenance: It is recommended that the coating installation be checked on a regular maintenance schedule. Recoating may be necessary at various intervals, depending upon the severity of conditions. Small area touch-up can be made at any time by following recommended application procedures.
Spray Application	Airless equipment: 60:1 with hopper fitted directly to material intake. Airless hose 10mm Ø with a whip hose of 6mm Ø fitted to a front-end feed gun using a reversible self-cleaning tip .043" to .055" with a fan angle of 40° to 50°. Note: All inline filters to be removed. Airless spray tip recommendation would be a reversible self-cleaning tip .043" to .055" with a fan angle of 40° to 50°.

CURING SCHEDULE

Surface Temp.	Cure Time
25°C (77°F)	24 Hours

CLEANUP & SAFETY

Cleanup | Use Thinner # 85

Safety | Read and follow all caution statements on this product data sheet and on the material safety data sheets for this product. Employ normal workmanlike safety precautions. Hypersensitive persons should wear protective clothing, gloves and use protective creams on face, hands and all exposed areas.

PACKAGING, HANDLING & STORAGE

Shelf Life | 12 Months minimum when stored at 25°C

Shipping Weight (Approximate) | 5 Litre
5.5kg
20 Litre
22kg

Storage Temperature & Humidity | 4 to 43°C
0 to 100%

Flash Point (Pensky Martens Closed Cup) | 35°C

APPLICATION PROCEDURES

Mixing | Mechanically mix material prior to use.

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.