

**SELECTION & SPECIFICATION DATA**

<b>Generic Type</b>	Cycloaliphatic (MIO) Amine Epoxy
<b>Description</b>	Thermaline 451 is a (MIO) flake filled cycloaliphatic amine cured epoxy phenolic novolac. This product has been formulated for use in immersion service in water and hydrocarbons such as fuel oil, diesel fuel, and gasoline. It may also be used under thermal insulation at elevated temperatures. Thermaline 451 has been modified with micaceous iron oxide (MIO) to provide excellent edge protection, one coat high build application properties, high temperature resistance and reinforced film properties. This product is self priming and resistant to 425°F- 450°F.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Extreme chemical resistance</li> <li>• Excellent thermal shock resistance</li> <li>• Excellent internal film reinforcement</li> <li>• Excellent edge protection</li> <li>• Excellent abrasion/impact resistance</li> </ul>
<b>Color</b>	Gray only
<b>Finish</b>	Semi-Gloss (35-70)
<b>Primer</b>	This product may be applied directly to steel and concrete surfaces.
<b>Dry Film Thickness</b>	178 - 229 microns (7 - 9 mils) per coat Typically applied as a single coat system @7-9 mils (Do not apply over 9.0 mils for service above 300°F)
<b>Recommended Thickness</b>	125-160 sq ft /gal (10-13 wet mils)
<b>Solids Content</b>	By Volume 76% +/- 2%
<b>Theoretical Coverage Rate</b>	29.9 m <sup>2</sup> /l at 25 microns (1219 ft <sup>2</sup> /gal at 1.0 mils) 4.3 m <sup>2</sup> /l at 175 microns (174 ft <sup>2</sup> /gal at 7.0 mils) 3.3 m <sup>2</sup> /l at 225 microns (135 ft <sup>2</sup> /gal at 9.0 mils) Allow for loss in mixing and application.
<b>VOC Values</b>	<b>As Supplied</b> : 1.69 lbs/gal (203 g/l)
<b>Under Insulation Resistance</b>	Continuous: 218°C (425°F) Non-Continuous: 232°C (450°F)
<b>Topcoats</b>	Not Applicable

**SUBSTRATES & SURFACE PREPARATION**

<b>General</b>	All surfaces must be thoroughly cleaned to remove dirt, grease, mill scale, loose rust, and any other contaminants that can reduce adhesion via SSPC-SP1 solvent cleaning before proceeding with recommended surface preparation.
<b>Concrete or CMU</b>	Prep to SSPC-SP13, masonry surfaces must cure for at least 30 days at 70°F before painting. Remove loose or excess mortar, efflorescence, laitance and concrete form release compounds. Etch or abrasive blast slick or glazed, or powdery concrete.

# Thermaline 451

## PRODUCT DATA SHEET



### SUBSTRATES & SURFACE PREPARATION

<b>Previously Painted Surfaces</b>	If the paint is glossy, sand to dull the surface. Apply test areas, allow to cure and test for adhesion and compatibility with existing coatings. Scrape loose, scaly or peeling paint and sand the edges smooth. Remove rust and scale from ferrous metal. IF mildew is present, remove completely by sterilizing the surface with mildew remover and detergent. Rinse well and allow to dry before painting.
<b>Special Instruction</b>	<b>Do not apply if material, substrate or ambient temperature is below 50°F or above 120°F.</b> Old coatings should be tested for lifting before applying Thermaline 451. If substrate temperatures are above 100°F for more than 72 hours, pretreatment may be required before an addition coat of Thermaline 451 is applied. When recoating beyond 1 month, additional surface preparation may be required. Spread rates are based on volume solids and do not take in to account loss factors, porosity or roughness of the surface being coated, application tools, techniques or any other variables. Relative humidity 85% maximum.
<b>Metal</b>	For maintenance work hand tool clean per SSPC-SP2, Sandblasting is recommended to remove rust and mill scale. Use commercial blast to SSPC-SP6 for mild exposures and near white blast SSPC-SP10 for severe exposures or immersion service.

### MIXING & THINNING

<b>Mixing</b>	Thoroughly stir each component. Pour component B into component A (mixing ratio by volume: 4 parts component A, to 1 part component B). Mix well with a drill type mechanical mixer. No induction time is necessary. <b>Do not mix more than can be applied within the specified pot life at the given temperature; allow additional time to clean lines and equipment.</b>
<b>Thinning</b>	Thin up to 10% by volume with Thinner 2. Thin only if allowed by local air quality and air pollution regulations.
<b>Pot Life</b>	2 hours at 75°F

### APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

<b>Conventional Spray</b>	Binks Model 95 spray gun or equal, reduce coating as needed up to 10% by volume if allowable. Fluid nozzle 66, air nozzle 66PR, 65-80 psi atomizing air pressure, 15-25 psi fluid pressure. Apply using a 45:1 pump at 3600 psi minimum.
<b>Airless Spray</b>	Material Hose: 3/8 – 1/2" x 100; max Tip Size: .019-.021" High Pressure Filter: 30 mesh
<b>Brush</b>	Apply using a natural bristle brush.
<b>Roller</b>	Roll using a 3/8" Phenolic core cover. Keep roller wet. Roll in one direction, rewet, then cross roll.

## CURING SCHEDULE

Surface Temp.	Dry Hard	Set to Handle	Set to Recoat	Set to Touch
10°C (50°F)	20 Days	18 Hours	48 Hours	5.5 Hours
24°C (75°F)	7 Days	7 Hours	18 Hours	3 Hours
38°C (100°F)	3 Days	2 Hours	5.5 Hours	1 Hour

Dry times are calculated with a 12.0 mil wet film at 50% relative humidity. Expect longer dry times in periods of higher humidity or lower temperatures or when applying thicker films. If the maximum re-coat window is exceeded the film must be mechanically abraded before re-coating.

## CLEANUP & SAFETY

<b>Cleanup</b>	Clean up all tools and equipment promptly with Thinner 2. Flush out all spray tips, fluid lines and pressure pots immediately after use.
<b>Safety</b>	Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Use adequate ventilation and wear gloves or use protective cream on face and hands if hypersensitive. Keep container closed when not in use.

## PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	Part A: 24 months at 75°F Part B: 24 months at 75°F  *Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.
<b>Shipping Weight (Approximate)</b>	5 Gal Kit - 77 lbs (35 kg)
<b>Storage Temperature &amp; Humidity</b>	40-110°F 0-90% RH
<b>Flash Point (Setaflash)</b>	Part A: 89°F Part B: >200°F
<b>Storage</b>	Store in protected, dry area.

## WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.