

## SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	Silicone Rubber Finish
<b>Description</b>	For use as a high performance finish for stainless steel surfaces in service from 300°F (149°C) to 800°F (426°C) with excellent resistance to thermal shock. It is typically used to prevent chloride stress corrosion cracking in service under insulation. For use over carbon steel, it can be applied over modified silicone primers or Carbozinc® 11 series.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Will air dry at ambient</li> <li>• Heat cure for ultimate film properties</li> <li>• Resistant to severe thermal shock</li> </ul>
<b>Color</b>	Black only
<b>Finish</b>	Flat (0-10)
<b>Primer</b>	Inorganic zincs; modified silicones
<b>Dry Film Thickness</b>	38 - 51 microns (1.5 - 2 mils) per coat
<b>Solids Content</b>	By Volume 30% +/- 2%
<b>Theoretical Coverage Rate</b>	11.8 m <sup>2</sup> /l at 25 microns (481 ft <sup>2</sup> /gal at 1.0 mils) 7.9 m <sup>2</sup> /l at 38 microns (321 ft <sup>2</sup> /gal at 1.5 mils) 5.9 m <sup>2</sup> /l at 50 microns (241 ft <sup>2</sup> /gal at 2.0 mils) Allow for loss in mixing and application.
<b>VOC Values</b>	<b>As Supplied</b> : 5.1 lbs/gal. (611 g/l) Thinner 235 : Thinned: 12.8 oz/gal (10%): 5.3 lbs/gal (635 g/l)
<b>Dry Temp. Resistance</b>	Continuous: 427°C (800°F)
<b>Topcoats</b>	Not Applicable

## SUBSTRATES & SURFACE PREPARATION

<b>General</b>	All surfaces must be thoroughly cleaned to remove dirt, grease, mill scale, loose rust and any other contaminants that can reduce adhesion via SSPC-SP1 solvent cleaning with recommended surface preparation.
<b>Aluminum</b>	SSPC-SP 7
<b>Ferrous Metal</b>	Apply over properly applied and cured primer
<b>Metal</b>	(Stainless steel) SSPC-SP7

## MIXING & THINNING

<b>Mixing</b>	Thoroughly mix to a uniform consistency prior to use.
<b>Thinning</b>	Normally not required. May be thinned up to 12.8 oz/gal. (10%) by volume with Thinner #235 for "hot" applications exceeding 150°F (66°C). Use of thinners other than those supplied or recommended by Carboline may adversely affect product performance and void product warranty, whether expressed or implied.

# Thermaline 2954

## PRODUCT DATA SHEET



### APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

**Spray Application (General)** | Conventional spray application is preferred.

**Conventional Spray** | Use DeVilbiss P-MBC, E-needle and tip, and a 704 air cap or equal. Use adequate air volume for proper equipment operation. Hold gun 10-12" from the surface and at right angles. Lap each pass 50%. Apply 5.0 wet mils to obtain desired dry film.

**Brush & Roller (General)** | Use only good quality brushes and roller covers where spray application is not permitted.

### APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	13°C (55°F)	4°C (40°F)	4°C (40°F)	0%
Maximum	35°C (95°F)	149°C (300°F)	49°C (120°F)	90%

This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions.

### CURING SCHEDULE

Surface Temp.	Dry to Touch	Firm Set	Hard Cure
25°C (77°F)	1 Hour	12 Hours	NR
149°C (300°F)	NR	NR	3 Hours

These times are based on a 2.0 mil (50 micron) dry film thickness. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure. While Thermaline 2954 is an ambient temperature-cure coating, optimum performance properties are achieved when final heat cure occurs at in-service temperatures of 400°F (204°C). Heat cure is at 300°F (148°C) for 3 hours, or 2 hours at 400°F (204°C).

### CLEANUP & SAFETY

**Cleanup** | Use Thinner # 2.

**Safety** | Read and follow all caution statements on this Product Data Sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Hypersensitive persons should wear protective clothing, gloves and use protective cream on face, hands and all exposed areas.

**Ventilation** | When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not able to monitor levels, use MSHA/NIOSH approved supplied air respirator.

---

## PACKAGING, HANDLING & STORAGE

---

<b>Shelf Life</b>	Min. 24 months at 77°F (24°C) *Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.
<b>Shipping Weight (Approximate)</b>	1 Gallon: 10 lbs. (4.5kg) 5 Gallon: 46 lbs. (21kg)
<b>Storage Temperature &amp; Humidity</b>	40°F-100°F (4°- 43°C) 0-90% Relative Humidity
<b>Flash Point (Setaflash)</b>	71°F (22°C)

## WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.