

SELECTION & SPECIFICATION DATA

Generic Type	Waterborne Acrylic
Description	Versatile high performance finish with excellent corrosion resistance and exterior weathering properties, as well as suitability for interior and mild environments.
Features	<ul style="list-style-type: none"> • Multi-purpose interior/exterior coating • Excellent color retention • Single component • Outstanding corrosion protection • Low odor, low VOC
Color	Refer to Carboline Color Guide. Minimum order quantities apply. Certain colors may require multiple coats to hide.
Finish	Flat (0-10)
Primer	Acrylics, Alkyds, Epoxies, Inorganic and Organic Zincs and others as recommended under Substrates & Surface Preparation. A mist coat may be required to minimize bubbling over Inorganic Zinc primers.
Dry Film Thickness	51 - 76 microns (2 - 3 mils) per coat Do not exceed 3.0 mils in a single coat
Solids Content	By Volume 36% +/- 2%
Theoretical Coverage Rate	14.2 m ² /l at 25 microns (577 ft ² /gal at 1.0 mils) 7.1 m ² /l at 50 microns (289 ft ² /gal at 2.0 mils) 4.7 m ² /l at 75 microns (192 ft ² /gal at 3.0 mils) Allow for loss in mixing and application.
VOC Value(s)	<u>As supplied</u> : 0.5 lbs/gal (60 g/l) w/6 oz #102: 0.8 lbs/gal (96 g/l) w/12 oz #102: 1.1 lbs/gal (132 g/l) <u>EPA Method 24</u> : 1.1 lbs/gal (132 g/l) (Calculated minus water and exempt solvents) w/6 oz #102: 1.8 lbs/gal (216 g/l) w/12 oz #102: 2.3 lbs/gal (276 g/l) These are nominal values and may vary slightly with color.
Dry Temp. Resistance	Continuous: 113°C (235°F) Non-Continuous: 163°C (325°F) Slight discoloration and loss of gloss is observed above 200°F (93°C).
Limitations	Apply and cure at temperatures of 50°F and above for 24 hours.

Carbocrylic 3359 Flat

PRODUCT DATA SHEET



APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	16°C (60°F)	18°C (65°F)	18°C (65°F)	10%
Maximum	32°C (90°F)	29°C (85°F)	32°C (90°F)	80%

Do not apply when the surface temperature is less than 5°F (3°C) above the dew point. Do not apply if temperatures are expected to drop below 50°F (10°C) within 24 hours of application. Special application techniques may be required above or below normal application conditions.

CURING SCHEDULE

Surface Temp.	Dry to Handle	Dry to Topcoat
10°C (50°F)	3 Hours	3 Hours
24°C (75°F)	2 Hours	2 Hours
32°C (90°F)	1 Hour	1 Hour

These times are based on a 2.0-3.0 mil (50-75 micron) dry film thickness. Higher film thicknesses, insufficient ventilation, high humidity or cooler temperatures will require longer cure times.

The acrylic film forming process may require several weeks at 75°F (24°C) with proper ventilation to develop adhesion and water resistance. High humidity, high film thickness, insufficient ventilation or cooler temperatures will lengthen the Dry to Handle and Dry to Topcoat times due to slower water evaporation rate. Waterborne acrylics are sensitive to moisture during early cure and are susceptible to handling damage.

PACKAGING, HANDLING & STORAGE

Shipping Weight (Approximate)	<u>1 Gallon</u> 11 lbs(5 kg)
	<u>5 Gallons</u> 51 lbs(23 kg)
	<u>50 Gallons</u> 525 lbs(239 kg)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS. Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.