

SELECTION & SPECIFICATION DATA

Description	Plasite 4500 S is a 100% solids, flake-filled, premium epoxy coating designed for internal steel and concrete tanks and pipe lining. It is a two component system consisting of 4-parts by volume of Part A resin and one part by volume of Part B hardener. It is applied by plural component or single component spray equipment, in a one-coat application (20-60 mils) for internal lining applications. It also meets AWWA C210 specification.
Finish	N/A
VOC Values	As Supplied : 0.0
Topcoats	Not Applicable

CURING SCHEDULE

Surface Temp.	Dry to Touch	Firm	Limited Chemical Service	Service Final Cure
10°C (50°F)	36 Hours	48 Hours	4 Days	14 Days
10°C (50°F)	48 Hours	72 Hours	5 Days	NR
24°C (75°F)	12 Hours	24 Hours	36 Hours	7 Days
24°C (75°F)	18 Hours	NR	NR	NR

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.