

## SELECTION & SPECIFICATION DATA

|                                  |  |
|----------------------------------|--|
| <b>Generic Type</b>              | Modified Polyamido-Amine Epoxy   |
| <b>Description</b>               | <ul style="list-style-type: none"> <li>• High performance, high solid epoxy with excellent corrosion protection used either as primer or as an intermediate coat over steel and zinc primers</li> <li>• Can be topcoated with a broad variety of high performance finish coats</li> </ul>                    |
| <b>Features</b>                  | <ul style="list-style-type: none"> <li>• Self priming</li> <li>• VOC compliant to current AIM regulations</li> <li>• Complies with BS 5493 standards for MIO (80%)</li> <li>• Excellent film build and edge protection</li> <li>• Good abrasion resistance</li> <li>• Excellent surface tolerance</li> </ul> |
| <b>Color</b>                     | Grey (0700), Red (0500)  |
| <b>Finish</b>                    | Semi-Gloss   |
| <b>Primer</b>                    | May be applied over zinc rich primers. A mist coat may be required to minimize bubbling over inorganic zinc rich primers.  |
| <b>Dry Film Thickness</b>        | 102 - 203 microns (4 - 8 mils) per coat  |
| <b>Solids Content</b>            | By Volume 80% +/- 2%   |
| <b>Theoretical Coverage Rate</b> | 31.5 m <sup>2</sup> /l at 25 microns (1283 ft <sup>2</sup> /gal at 1.0 mils)<br>7.9 m <sup>2</sup> /l at 100 microns (321 ft <sup>2</sup> /gal at 4.0 mils)<br>3.9 m <sup>2</sup> /l at 200 microns (160 ft <sup>2</sup> /gal at 8.0 mils)<br>Allow for loss in mixing and application.                      |
| <b>VOC Value(s)</b>              | As Supplied : 200 g/l  |
| <b>Dry Temp. Resistance</b>      | Continuous: 93°C (199°F)<br>Non-Continuous: 121°C (250°F)<br><br>Discoloration and loss of gloss is observed above 93°C (200°F).   |
| <b>Limitations</b>               | Epoxies lose gloss, discolor and eventually chalk in sunlight exposure. Discoloration is more pronounced with this product. Not recommended for immersion service.   |
| <b>Topcoats</b>                  | Acrylics, Alkyds, Epoxies, Polyurethanes   |

## SUBSTRATES & SURFACE PREPARATION

|                         |   |
|-------------------------|---|
| <b>General</b>          | Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating.   |
| <b>Steel</b>            | For most applications: SSPC-SP10 (ISO 8501 Sa 2 ½) to obtain a blast profile of 1.0-2.0 mils (25-50 microns).   |
| <b>Galvanized Steel</b> | Galvanizing requires a roughened surface for optimum adhesion/performance of high build epoxies. Remove any contaminants per SSPC SP1; ensure there are no chemical treatments that may interfere with adhesion; and abrade the surface to establish a suitable roughness (typically 1 mil). SSPC-SP7 or SP11 are acceptable methods. |

# Carboguard 838

## PRODUCT DATA SHEET



### MIXING & THINNING

|                 |   |
|-----------------|---|
| <b>Mixing</b>   | Power mix separately, then combine and power mix. DO NOT MIX PARTIAL KITS.  |
| <b>Thinning</b> | <ul style="list-style-type: none"><li>• Airless Spray: Up to 15% with Thinner #80</li><li>• Brush &amp; Roller: Up to 5% with Thinner #80</li></ul> |
| <b>Ratio</b>    | 4:1 Ratio (A to B) By Volume  |
| <b>Pot Life</b> | 3 Hours at 25°C<br>Pot life ends when coating thickens and loses application properties. Pot life times will be less at higher temperatures.        |

### APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

|                                     |  |
|-------------------------------------|--|
| <b>Spray Application</b>            | The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco.  |
| <b>Conventional Spray</b>           | Pressure pot equipped with dual regulators, 3/8" I.D. minimum material hose, 0.070" I.D. fluid tip and appropriate air cap.  |
| <b>Airless Spray</b>                | <ul style="list-style-type: none"><li>• Pump Ratio: 30:1 (min.)*</li><li>• GPM Output: 2.5 (min.)</li><li>• Material Hose: 3/8" I.D. (min.)</li><li>• Tip Size: 0.015"-0.021"</li><li>• Output PSI: 2100-2300</li><li>• Filter Size: 60 mesh</li></ul> <p>*PTFE packings are recommended and available from the pump manufacturer.</p> |
| <b>Brush &amp; Roller (General)</b> | Multiple coats may be required to obtain desired appearance, recommended dry film thickness and adequate hiding. Avoid excessive re-brushing or re-rolling. For best results, tie-in within 10 minutes at 75°F (24°C).   |
| <b>Brush</b>                        | Use a medium bristle brush.  |
| <b>Roller</b>                       | Use 3/8" nap phenolic core roller.   |

### APPLICATION CONDITIONS

| Condition | Material    | Surface      | Ambient      | Humidity |
|-----------|-------------|--------------|--------------|----------|
| Minimum   | 10°C (50°F) | 5°C (41°F)   | 5°C (41°F)   | 0%       |
| Maximum   | 32°C (90°F) | 52°C (126°F) | 43°C (109°F) | 85%      |

This product simply requires the substrate temperature to be above the dew point. Condensation due to substrate temperatures below the dew point can cause flash rusting on prepared steel and interfere with proper adhesion to the substrate. Special application techniques may be required above or below normal application conditions.

## CURING SCHEDULE

| Surface Temp. | Dry to Touch | Dry to Recoat | Maximum Recoat Time |
|---------------|--------------|---------------|---------------------|
| 25°C (77°F)   | 3 Hours      | 7 Hours       | 30 Days             |
| 35°C (95°F)   | 2 Hours      | 5 Hours       | 30 Days             |

These times are based on 50% relative humidity and 3.0-4.0 mil (75-100 micron) dry film thickness for atmospheric exposures. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure. Excessive humidity or condensation on the surface during curing can interfere with the cure, can cause discoloration and may result in a surface haze. Any haze or blush must be removed by water washing before recoating. If the maximum recoat times have been exceeded, the surface must be abraded by sweep blasting or sanding prior to the application of additional coats. For force curing, contact StonCor ME Technical Service for specific requirements.

## CLEANUP & SAFETY

|                    |  |
|--------------------|--|
| <b>Cleanup</b>     | Use Thinner #80. In case of spillage, absorb and dispose of in accordance with local applicable regulations.   |
| <b>Safety</b>      | Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions. Hypersensitive persons should wear protective clothing, gloves and use protective cream on face, hands and all exposed areas.   |
| <b>Ventilation</b> | When used in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not sure or if not able to monitor levels, use MSHA/NIOSH approved respirator. |
| <b>Caution</b>     | This product contains flammable solvents. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workers should be required to use non-ferrous tools and wear conductive and non-sparking shoes.   |

## PACKAGING, HANDLING & STORAGE

|   |   |
|---|---|
| <b>Shelf Life</b>                         | Part A & B: Min. 12 months at 75°F (24°C)<br>*Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers. |
| <b>Shipping Weight (Approximate)</b>      | 19 liter kit (Approximately 30 kg)  |
| <b>Storage Temperature &amp; Humidity</b> | Storage Temperature: 40° -110°F (4°-43°C)<br>Relative Humidity: 0-100%  |
| <b>Flash Point (Setaflash)</b>            | Part A: <25°C<br>Part B: <25°C  |
| <b>Storage</b>                            | Store indoors   |

# Carboguard 838

## PRODUCT DATA SHEET



### WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline Company to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance, injuries or damages resulting from use. Carbolines sole obligation, if any, is to replace or refund the purchase price of the Carboline product(s) proven to be defective, at Carbolines option. Carboline shall not be liable for any loss or damage. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated.