

SELECTION & SPECIFICATION DATA

Generic Type	Waterborne Acrylic
Description	Carbotherm 3300 is a ceramic blend insulative composite coating formulated in a high temperature resistant acrylic binder. It is ideally suited as a protective heat barrier to shield personnel from hot surfaces. It also inhibits heat transfer into or out of a structure. Its insulative properties keeps structures exposed to solar radiation significantly cooler. It can be used to minimize or eliminate sweating of pipes or other operating equipment.
Features	<ul style="list-style-type: none"> • Excellent thin-film insulation • Unique formula provides superior coverage during application • Protects personnel from hot surfaces • Multi-purpose interior/exterior coating • Insulation provides anti-condensation properties • Easy to use • Zero VOC; Low odour • May be applied to hot surfaces
Colour	White
Finish	Eggshell
Primer	<p>For service temperatures:</p> <p>Up to 112°C (235°F): Use Carbocrylic 3358 Series; Carboguard 553 or Carboguard 890</p> <p>Up to 149°C (300°F): Use Carbozinc 11 Series; Carboguard 690 or Carbomastic 15 Series</p> <p>Up to 176°C (350°F): Use Altra~Zinc 605</p>
Service Temperature	<p>-51° to 176°C</p> <p>For <u>initial</u> service avoid sudden temperature "surges". Do not exceed 93°C during the first hour.</p>
Dry Film Thickness	<p>406 - 635 microns (16 - 25 mils) per coat</p> <p>Number of coats depends on the operating temperature and degree of insulation or protection needed. Contact your local Carboline Representative for a copy of Carbotherm 3300 User's Guide for thickness needs based on end use.</p>
Solids Content	<p>By Volume 90% +/- 2%</p> <p>Tested in accordance with ASTM D2697</p>
Theoretical Coverage Rate	<p>35.4 m² at 25 microns (1444 ft² at 1.0 mils)</p> <p>2.2 m² at 400 microns (90 ft² at 16.0 mils)</p> <p>1.4 m² at 625 microns (58 ft² at 25.0 mils)</p> <p>Allow for loss in mixing and application.</p>
VOC Values	As Supplied : 0.00
Topcoats	<p>May be topcoated with acrylics for custom colours or gloss.</p> <p>For custom colours or for high humidity/wet exposures use Carbocrylic 3350 or Carbocrylic 3359 Series.</p>

Carbotherm 3300

PRODUCT DATA SHEET



SUBSTRATES & SURFACE PREPARATION

General	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil, and all other contaminants that could interfere with adhesion of the coating.
Steel	Prime with appropriate primers as recommended in section on "Primers".
Stainless Steel	Abrasive blast using non-metallic media to a 25-38 micron profile and apply appropriate primer (See Primers).

PERFORMANCE DATA

Test Method	System	Results
Accelerated Aging/Salt Fog (ASTM B117)	Carbozinc 859/ Carbotherm 3300/ Carbocrylic 3359 DTM	2016 hrs; No blisters or rust on the plane or scribe; Few to medium #2 blisters at scribe.
Cyclic QUV-A/Prohesion (ASTM D5894)	Carbozinc 859/ Carbotherm 3300/ Carbocrylic 3359	2016 hrs; No effect, No blisters or rust on plane or scribe
Elongation (ASTM D638)	Carbotherm 3300	25%
Emissivity (ASTM E408)	Carbotherm 3300	0.88
Flame Spread (ASTM E84)	Carbotherm 3300	Flame Spread: 0 Smoke Development: 0
Humidity Cabinet (ASTM D2247)	Carbozinc 859/ Carbotherm 3300/ Carbocrylic 3359 DTM	2016 hrs; No effect, No blister or rust on plane or scribe
R Value	Carbotherm 3300 (tested at 0.172")	0.251 hr-ft ² -°F/BTU
Solar Reflectivity (ASTM E903)	Carbotherm 3300	86.2
Thermal Conductivity @77°F/24°C; (ASTM C177)	Carbotherm 3300 (tested at 0.172")	0.0570 BTU/hr-ft ² -°F (0.0987 W/m ² -°K)
Thermal Transmittance @77°F (ASTM C177)	Carbotherm 3300 (tested at 0.172")	3.98 BTU/hr-ft ² -°F

All test data was generated under laboratory conditions. Field testing results may vary.

MIXING & THINNING

Mixing | Separation of coating may occur and is common. Turning containers upside down for 5 minutes just prior to mixing will dramatically facilitate mixing. Use a drywall compound mixing paddle (in reverse) to incorporate material to a homogeneous consistency resembling a milkshake. Normally this will take several minutes. Avoid contact of mixing blade and edge of plastic buckets to avoid shearing plastic pieces into coating. If other types of blades or high powered mixers are used, avoid high shear or over mixing.

Thinning | No thinning is required.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Spray Application (General) | Pre-rinse equipment with clean potable water before spraying. The following spray equipment has been found suitable and is available from equipment manufacturers.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Conventional Spray	Bottom outlet pressure pot works best, equipped with dual regulators, ½" I.D. minimum material hose, 1.8 mm (0.070") I.D. fluid tip and appropriate air cap. Adjust line air pressure to 40 psi and pot pressure to 15 psi.
Airless Spray	Pump Ratio: 30:1 minimum* Output: 12 litres/min. minimum Material Hose: 9.5 mm (3/8") I.D. minimum Tip Size: .021-.025*** Output PSI: 1800-2200 Filter Size: Remove filters *PTFE packings are recommended and available from the pump manufacturer. Use of a surge protector is strongly recommended. **Use heavy duty reverse-a-clean non-diffuser tips.
Brush & Roller (General)	Multiple coats may be required to achieve recommended dry film thickness. Brushing may negatively affect insulative properties; use for touch up of small areas only. Avoid excessive re-brushing. Do not apply by roller.
Brush	Use a synthetic bristle brush. Use for touch up of small surface areas only.
Roller	Not recommended

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	10°C (50°F)	10°C (50°F)	10°C (50°F)	0%
Maximum	38°C (100°F)	149°C (300°F)	43°C (109°F)	80%

It is best to spray apply a light 125-250 microns coat and allow to tack dry prior to full coating. This is especially helpful over hot surfaces which may require 2-4 light passes between 65-150°C.

Do not apply when the surface temperature is less than 3°C above the dew point. Do not apply if temperatures are expected to drop below 10°C within 24 hours of application. Special application techniques may be required above or below normal application conditions. Dry times will be aided by higher temperatures, lower humidity, hotter substrates, and more air movement during application and curing.

CURING SCHEDULE

Surface Temp.	Dry to Recoat
16°C (60°F)	6 Hours
24°C (75°F)	3 Hours
32°C (90°F)	1.5 Hours

These times are based on a 500 micron dry film thickness. Higher film thicknesses, insufficient ventilation, high humidity or cooler temperatures will require longer cure times. The material is typically ready to recoat when it passes a "dry to handle" test (thumb twist test). If a final colour coat (see Topcoats) is used; allow 36-48 hours dry time to ensure complete dryness prior to final colour coat.

Carbotherm 3300

PRODUCT DATA SHEET



CLEANUP & SAFETY

Cleanup	Use clean potable water followed with suitable solvent to dry equipment. In case of spillage, absorb and dispose of in accordance with local applicable regulations.
Safety	Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Use adequate ventilation and wear gloves or use protective cream on face and hands if hypersensitive. Keep container closed when not in use.

PACKAGING, HANDLING & STORAGE

Shelf Life	24 months at 24°C
Storage Temperature & Humidity	4°-43°C 0-95% Relative Humidity Do NOT freeze!
Flash Point (Setaflash)	>93°C
Shipping Weight (Approximate)	4 US gallons (15.1 litres) 12 kg
Storage	Store indoors (Keep from freezing)

WARRANTY

Manufactured and / or distributed in Australia & New Zealand by Altex Coatings under license to Carboline Company. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Altex Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ALTEX COATINGS OR CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. Altex Terms and Conditions of Trade, available at www.altexcoatings.com, apply in respect of all coating products and materials supplied, including samples.