

## SELECTION & SPECIFICATION DATA

|                                   |  |
|-----------------------------------|--|
| <b>Generic Type</b>               | Solvent-free aromatic polyurethane, ASTM D16 Type V  |
| <b>Description</b>                | Polyclad 777 PL is a high performance 100% solids structural polyurethane designed to provide superior corrosion protection for steel, ductile iron and concrete pipe. Tenacious adhesion and high impact resistance allow its use in the harshest environments. It forms a dense, long-term impermeable barrier that is ready for service moments after application through a fast-set cure mechanism. No primer is required.   |
| <b>Features</b>                   | <ul style="list-style-type: none"> <li>• Rapid curing to increase plant throughput</li> <li>• Excellent abrasion resistance for use as a rock shield, slip bore and in directional drill applications</li> <li>• Superior wetting properties for outstanding adhesion</li> <li>• Mix ratio of 1:1 with easy application properties</li> <li>• Can be topcoated by Carbothane series of products</li> <li>• Unlimited film-build with single or multi-pass coats</li> </ul> |
| <b>Typical Uses</b>               | Steel pipeline exteriors, steel valves & fittings, steel pilings, steel poles (above & below ground), buried tank exteriors, penstocks. Also other applications requiring high abrasion resistance, rapid cure and superior corrosion protection for steel.  |
| <b>Colour</b>                     | Standard colors are: Yellow (0600) and Medium Blue (0100)  |
| <b>Finish</b>                     | Gloss  |
| <b>Primer</b>                     | No primer needed- direct to steel  |
| <b>Dry Film Thickness</b>         | 635 - 1016 microns (25 - 40 mils) For most applications on steel.<br>635 - 3175 microns (25 - 125 mils) For other applications on steel, depending on service conditions.  |
| <b>Solids Content</b>             | By Volume 100% +/- 0%  |
| <b>Theoretical Coverage Rates</b> |  |
| <b>Theoretical Coverage Rate</b>  | 39.4 m <sup>2</sup> at 25 microns (1604 ft <sup>2</sup> at 1.0 mils)<br>1.6 m <sup>2</sup> at 625 microns (64 ft <sup>2</sup> at 25.0 mils)<br>0.3 m <sup>2</sup> at 3125 microns (13 ft <sup>2</sup> at 125.0 mils)<br>Allow for loss in mixing and application.  |
| <b>VOC Values</b>                 | <b>As Supplied</b> : 0.00 lbs/gal  |
| <b>Approvals</b>                  | Meets requirements of AWWA C222-08   |
| <b>Limitations</b>                | Due to its aromatic composition Polyclad 777 PL will tend to yellow or darken in exterior UV exposure. This will not affect performance.   |
| <b>Topcoats</b>                   | Carbothane Acrylic Polyurethanes (Optional)<br>Contact Carboline Technical Service for more information.   |

## SUBSTRATES & SURFACE PREPARATION

|                |  |
|----------------|--|
| <b>General</b> | Prepare surface as noted below. Ensure dust/smut from blasting operation does not interfere with adhesion. Recommend using ISO 8502-3 to confirm low surface dust with a preferred rating of "1" or "2". Apply coating prior to any flash rusting or contamination fall-out. |
|----------------|--|

# Polyclad 777 PL

## PRODUCT DATA SHEET



### SUBSTRATES & SURFACE PREPARATION

**Steel** | Remove all contaminants in accordance with SSPC-SP 1. Near White Metal Blast clean in accordance with NACE No. 2/SSPC-SP 10 and create 3 to 5 mils, (75 to 125 microns), of dense angular anchor profile.

**Ductile or Cast Iron** | Remove all contaminants in accordance with SSPC-SP 1. Abrasive blast clean in accordance with National Association of Pipe Fabricators, Inc., NAPF 500-03-04.

### PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

| Test Method                    | System                 | Results                 |
|--------------------------------|------------------------|-------------------------|
| Abrasion Resistance ASTM D4060 | 1 Coat Polyclad 777 PL | 27 mg loss              |
| Adhesion to Steel ASTM D4541   | 1 Coat Polyclad 777 PL | Minimum 1500 psi        |
| Cathodic Disbondment ASTM G-95 | 1 Coat Polyclad 777 PL | 4 mm                    |
| Chemical Resistance ATSM D543  | 1 Coat Polyclad 777 PL | Pass 30 day immersion   |
| Dielectric Strength D149       | 1 Coat Polyclad 777 PL | > 500 V/mil             |
| Flexibility ASTM D522          | 1 Coat Polyclad 777 PL | Pass 3 inch 180 degrees |
| Hardness: ASTM D2240 Shore D   | 1 Coat Polyclad 777 PL | 77 + Shore D            |
| Impact Resistance ASTM G14     | 1 Coat Polyclad 777 PL | 101 in-lbs              |
| Tensile Strength ASTM D412     | 1 Coat Polyclad 777 PL | > 4000 psi              |
| Water Absorption ASTM D570     | 1 Coat Polyclad 777 PL | < 1.6%                  |

### MIXING & THINNING

**Mixing** | Power mix part B until the pigments are dispersed into a homogeneous liquid. Do not batch mix parts A & B. Do not thin.

### APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

**General** | Applicators must be trained and familiar with the application of 100% solids fast set high build coatings. Carboline Technical Service must review the project specifications and approve of the applicator prior to the start of the project. Applicators must follow the proper safety guidelines, operation and maintenance of the spray equipment.

**Airless Spray** | Use only heated plural component airless equipment with 1:1 mix ratio. The plural airless pump must have a minimum capability of 1.25 gallons per minute with a fluid pressure of up to 3,000 psi. The recommended spray system is a Graco Reactor or WIWA PU 460 plural component system utilizing typical transfer pumps to supply both the resin and catalyst to the spray system, in-line heaters capable of heating the material up to 160 degrees F as needed, heated hose bundle, and a Graco Fusion Plural Component Gun. Other equipment of equal capabilities may suffice. Contact Carboline Technical Service Department for alternate spray equipment recommendations. We recommend that the applicator perform a mock up prior to and after mobilizing to the jobsite to be sure all equipment is performing properly.

## APPLICATION CONDITIONS

| Condition | Material     | Surface      | Ambient      | Humidity |
|-----------|--------------|--------------|--------------|----------|
| Minimum   | 52°C (125°F) | -18°C (-0°F) | 2°C (35°F)   | 0%       |
| Maximum   | 71°C (160°F) | 49°C (120°F) | 49°C (120°F) | 85%      |
| Optimum   | 63°C (145°F) | 21°C (70°F)  | 21°C (70°F)  | 35%      |

Industry standards are for substrate temperatures to be 5 F(3 C) above the dew point. Caution: this product in the liquid stage is moisture sensitive and needs to be protected from high humidity, dew and direct moisture contact until cured to a firm state. Application and/or curing in humidity above maximum, or exposure to moisture from rain or dew may result in a loss of gloss, micro bubbling and/or blistering of the product.

Note: for applications on concrete please contact your Carboline representative for proper application procedures.

## CURING SCHEDULE

| Surface Temp. | Cure for Service | Dry to Handle | Dry to Touch |
|---------------|------------------|---------------|--------------|
| 24°C (75°F)   | 1 Hour           | 9 Minutes     | 90 Seconds   |

Lower metal temperatures will slow the dry time and higher metal temperatures will speed up dry time. Polyclad 777 PL is ready for holiday testing as soon as it reaches its dry-to-handle state. It is ready for service when the hardness reaches Shore D 70 (typically 1 hour)

For added UV resistance, Polyclad 777 PL may be topcoated with Carbothane aliphatic polyurethanes as soon as it is dry to touch. Maximum recoat time with Carbothane series is 28 days. To topcoat past the maximum recoat time the surface must be abraded and cleaned.

Maximum recoat with itself is two hours.

## CLEANUP & SAFETY

|                |   |
|----------------|---|
| <b>Cleanup</b> | Use Thinner 2 or 76. To clean lines, use Thinner 76 followed by Carboline's Polyclad Line Stabilizer for long term storage. Contact Carboline Technical Service for cleaning recommendations. In case of spills, absorb and dispose of in accordance with local applicable regulations.   |
| <b>Safety</b>  | Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions. Workers should wear proper personal protection equipment.  |
| <b>Caution</b> | This product does not contain flammable solvents, however, clean-up solvents that may be used do contain flammable solvents. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workers should be required to use non-ferrous tools and wear conductive and non-sparking shoes. |

## PACKAGING, HANDLING & STORAGE

|   |   |
|---|---|
| <b>Packaging</b>                          | 10 gallon, 110 gal, 528 gal and dual cartridge kits   |
| <b>Shelf Life</b>                         | Part A: Min. 12 months at 75°F (24°C)<br>Part B: Min. 24 months at 75°F (24°C)<br><br>*When kept at recommended storage conditions and in original unopened containers. |
| <b>Storage Temperature &amp; Humidity</b> | 60° - 90°F (16°-32°C)<br>0-100% Relative Humidity   |

# Polyclad 777 PL

## PRODUCT DATA SHEET



### PACKAGING, HANDLING & STORAGE

|                                      |   |
|--------------------------------------|---|
| <b>Flash Point (Setaflash)</b>       | Part A =390°F (199°C)<br>Part B >200°F (93°C)   |
| <b>Shipping Weight (Approximate)</b> | 9.8 lbs per kit gal (4.4 kg per gal)  |
| <b>Storage</b>                       | Store indoors and keep dry. Blanket all partial drums with nitrogen gas to prevent moisture contamination. Do not allow Part A to freeze. Do not open until ready to use. |

### WARRANTY

Manufactured and / or distributed in Australia & New Zealand by Altex Coatings under license to Carboline Company. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Altex Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ALTEX COATINGS OR CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. Altex Terms and Conditions of Trade, available at [www.altexcoatings.com](http://www.altexcoatings.com), apply in respect of all coating products and materials supplied, including samples.