

SELECTION & SPECIFICATION DATA

Generic Type	Single package, water-based, flexible mastic fire protective coating for cables and cable trays.
Description	A water based mastic that can be applied to electrical cables to retard fire propagation. Once applied, it meets code and insurance requirements for interior and exterior use. It provides a hard and flexible surface that will not dust, flake, or spall.
Features	<ul style="list-style-type: none"> • Flexible • Hard, dust free surface • Allows easy replacement of cables • Water-based product, low odour • Asbestos-Free – complies with EPA and OSHA regulations • Factory Mutual – tested and approved • Does not de-rate cables • Weathering – approved for exterior use • Quality Manufactured – under strict Carboline quality standards • Provides protection at 1.6mm Dry Film Thickness
Colour	Grey
Finish	Textured Textured finish varies depending on the method of application.
Primer	Primer is not required.
Fireproofing Wet Film Thickness	3mm
Fireproofing Dry Film Thickness	1.6 mm
Solids Content	By Volume 53% +/- 2%
VOC Values	As Supplied : 29 g/l Calculated per EPA Method 24: 56 g/l (Calculated minus water and exempt solvents)
Limitations	Not recommended for long-term surface temperatures over 91°C in continuous use, 104°C in non-continuous use.
Topcoats	Topcoats are generally not required. In severely corrosive atmospheres, contact Carboline Technical Service for a topcoat recommendation most suitable for the operating environment.

SUBSTRATES & SURFACE PREPARATION

General	Before applying Thermo-Lag 270 to electrical cables, the cables must be dry and free of all oil, grease, condensation or any other contamination.
----------------	---

Thermo-Lag 270

PRODUCT DATA SHEET



PERFORMANCE DATA

Test Method	Results
ASTM D2240 Hardness	Shore D - 30-40
ASTM E84 Surface Burning	Class A
DEFSTAN 02-711-2 Smoke Index	Class A
EPS 96202 Ampacity	No de-rating
IEC 60331-1 Circuit Integrity	50 minutes @ 1.6 mm
IEC 60331-11 Circuit Integrity	90 minutes @ 3 mm
IEC 60332-3-22 Flame Propagation	2 hours @ 1.6 mm
IEC 60754 Halogen Gas Content	Pass (<5.0 mg/g HCL)

*All values derived under controlled laboratory conditions.

*Test reports and additional information available upon written request.

TYPICAL CHEMICAL RESISTANCE

Exposure	Fumes	Splashes & Spills
Acids	Very Good	Fair
Alkalies	Very Good	Fair
Salt	Excellent	Very Good
Solvents	Good	Good

MIXING & THINNING

Mixer | Use 1/2" electric or air driven drill with a slotted paddle mixer (300 rpm under load).

Mixing | Thermo-Lag 270 must be mixed using a 1/2" electric or air driven drill with a slotted paddle or Jiffy mixer blade. Mix material for a minimum of 5 minutes to achieve the necessary texture required before spraying.

Thinning | Thermo-Lag 270 may be thinned with clean potable water up to 5% by volume.

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Airless Spray	Use 45:1 airless (minimum) with Dura Flow lower cylinder (3/4" outlet) / 3.3 gal. per minute to provide an operating pressure of 3,000psi (210 kg/cm ²). *Remove filters and surge tanks. Set bottom ball to greatest travel. Hopper feed optional. Teflon packings are recommended.
Pump	Graco® Xtreme XL Heavy Fluid Package WIWA® Herkules 75:1 or Carboline approved equivalent Contact the equipment manufacturers for specific models. Contact Carboline Fireproofing Technical Service for details.
Spray Gun	WIWA® 500 PFP, Binks 1M Mastic or equivalent Must be non-wetted spring assembly.
Gun Swivel	5,000 psi (34.4 MPa) 12.7 mm - 9.5 mm (1/2" - 3/8")

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

Spray Tips	0.059" - 0.063" (Use Graco heavy duty RAC non diffuser tips and housing)
Fan Size	152 mm - 254 mm (6" - 10") depending on area being sprayed
Material Hose	Use 15m (50 ft) of high pressure spray line with a minimum I.D. of 19mm (3/4")
Whip Hose	6m (20 ft) of 12.7 mm (1/2") I.D. minimum
Compressor	Be certain that the air supply is a minimum of 185 cfm @ 100 psi (690 kPa). Air volume and pressure required will depend on equipment used.

APPLICATION PROCEDURES

General	Thermo-Lag 270 may be applied by spray, trowel or hand application. When spray applying, Thermo-Lag 270 must be thinned 5% by volume (1 quart or 945ml water per 5 gallons maximum). A single coat built up with a number of quick passes allows greater control over quantities, thickness and finish. In most conditions, it is advantageous to apply two thin coats rather than one thick coat.
Application Rates	At an ambient temperature of 21°C, apply 3mm per coat (wet)
Wet Film Thickness	Frequent thickness measurements with a wet film gauge are recommended during the application process to ensure uniform thickness.
Palming	Hand application of Thermo-Lag 270 may be more economical when cables are "ganged" or for protecting individual strands. Rubber gloves are recommended
Trowel	A standard plasterer's hawk and trowel may be used for suitable applications. Selection of instruments is left to the discretion of the applicator.

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	10°C (50°F)	4°C (39°F)	4°C (39°F)	0%
Maximum	43°C (109°F)	35°C (95°F)	35°C (95°F)	90%

*Air and substrate temperature must be at least 4.4°C and rising. Surface temperature should be a minimum of 3°C above the dew point. The maximum humidity is 90%. Area must be protected from rain or running water during application until material is cured. Minimum ambient temperatures must be maintained for 24 hours after application.

CURING SCHEDULE

Surface Temp.	Dry to Touch	Final Cure Time
21°C (70°F)	24 Hours	15 Days

*Curing times are dependent on thickness, humidity and temperature. Normal dry times are based on a wet thickness of 3.2 mm (1/8").

Thermo-Lag 270

PRODUCT DATA SHEET



CLEANUP & SAFETY

Cleanup	Pump, gun, tips and hoses should be cleaned with clean, potable water at least once every 4 hours at 21°C and more often at higher temperatures.
Safety	Follow all safety precautions on the Thermo-Lag 270 Safety Data Sheet. It is recommended that personal protective equipment be worn including spray suits, gloves, eye protection and respirators when applying Thermo-Lag 270.
Overspray	All adjacent and finished surfaces shall be protected from damage and overspray. Wet overspray may be cleaned with soapy or clean potable water. Cured overspray may require chipping or scraping to remove.
Ventilation	In enclosed areas, ventilation shall not be less than 4 complete air exchanges per hour until the material is dry.
Caution	Thermo-Lag 270, like most water based coatings, is electrically conductive until it is dry. Extreme caution should be exercised when the material is applied to energised cables and equipment. The material should never be applied without the supervision of plant safety personnel.

TESTING / CERTIFICATION / LISTING

Intertek	Thermo-Lag 270 has been successfully tested at Intertek laboratories to the following international test standards: IEC 60331-1 - Circuit Integrity IEC 60332-3-22 - Flame Propagation IEC 60754-1 - Halogen Gas Content DEFSTAN 02-711-2 - Smoke Index
FM Global	Thermo-Lag 270 has been tested and approved by Factory Mutual Research Corporation at 1.6 mm (1/16") dry thickness, and evaluated by Sandia Laboratories in tests sponsored by the U.S. Nuclear Regulatory Commission using both propane and diesel fueled fires. Copies of both the Factory Mutual and Sandia Laboratories' test reports are available upon request. Ampacity tests run by Factory Mutual show "No electrical derating necessary when a cable is coated (and cured properly) with Thermo-Lag 270." The temperature attained was well below the maximum temperature rating of the cable insulation. Heat transfer calculations should be used to calculate derating requirements of large groups of conductors. <u>Factory Mutual Research Corp.</u> <u>Sandia Labs</u> <ul style="list-style-type: none">• Diesel (Cable Tray)• Propane (Cable Tray) <u>Electrical Power System</u> <ul style="list-style-type: none">• Ampacity - No derating of cables required• Report EPS 96202 Fire Retardant coating for Electrical Power and Control Cables at 1.6mm (1/16") dry film thickness.

PACKAGING, HANDLING & STORAGE

Packaging	5 gallon
Shelf Life	12 Months *Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers.
Flash Point (Setaflash)	>148°C

PACKAGING, HANDLING & STORAGE

**Shipping Weight
(Approximate)** | 11 lbs. per gallon

Storage | Store indoors in a dry environment between 4.4°C - 37.7°C. Keep from freezing.

WARRANTY

Manufactured and / or distributed in Australia & New Zealand by Altex Coatings under license to Carboline Company. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Altex Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ALTEX COATINGS OR CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. Altex Terms and Conditions of Trade, available at www.altexcoatings.com, apply in respect of all coating products and materials supplied, including samples.