

## SELECTION & SPECIFICATION DATA

<b>Generic Type</b>	Epoxy Phenalkamine
<b>Description</b>	An all-purpose epoxy that has a variety of attributes including low-temperature cure, surface tolerance, fast recoat times, moisture tolerance during application and cure, and excellent corrosion protection. Carboguard 635 HAR can be used direct to metal as a corrosion resistant primer or as an intermediate coating over other primers. It is suitable for both maintenance and new construction projects due to its excellent surface wetting characteristics and quick cure for handling. It may also be used for immersion in fresh or salt water (marine) exposures and exhibits exceptional abrasion resistance & toughness.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Low temperature cure -7°C (20°F)</li> <li>• Excellent corrosion protection</li> <li>• High abrasion resistance</li> <li>• Excellent flexibility</li> <li>• Excellent application characteristics</li> <li>• Fast recoat times</li> <li>• Moisture tolerance during application</li> <li>• Extended re-coat window for atmospheric exposures up to 6 months self re-coat</li> <li>• Approved for use in food &amp; dairy processing plants (refer to "Approvals NZ/AU" section)</li> </ul>
<b>Colour</b>	Light Grey
<b>Gloss</b>	Satin
<b>Primer</b>	Self-Priming
<b>Dry Film Thickness</b>	102 - 152 microns (4 - 6 mils) per coat  Note: <i>Thicknesses above this range may result in higher gloss appearance which can interfere with topcoat adhesion. Follow Curing Schedule notes to mitigate possible adhesion issues.</i>
<b>Solids Content</b>	By Volume 65% +/- 2%
<b>Theoretical Coverage Rate</b>	25.6 m <sup>2</sup> at 25 microns (1043 ft <sup>2</sup> at 1.0 mils) 6.4 m <sup>2</sup> at 100 microns (261 ft <sup>2</sup> at 4.0 mils) 4.3 m <sup>2</sup> at 150 microns (174 ft <sup>2</sup> at 6.0 mils) Allow for loss in mixing and application.
<b>VOC Values</b>	<b>As Supplied</b> : 296 g/l mixed  These are nominal values and may vary with color.
<b>Dry Temp. Resistance</b>	Continuous: 82°C (180°F) Non-Continuous: 104°C (220°F)
<b>Limitations</b>	Epoxies lose gloss, discolour and eventually chalk in sunlight exposure.
<b>Abrasion Resistance</b>	55-65 mg loss (Tabor Abrasion Test using 1 kg weight, CS17 wheel and 1000 cycles)
<b>Topcoats</b>	May be coated with Acrylics, Epoxies, Alkyds, Polyurethanes or Polysiloxanes depending on exposure and need.

# Carboguard 635 HAR

## PRODUCT DATA SHEET



### SUBSTRATES & SURFACE PREPARATION

<b>General</b>	Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants as described in SSPC-SP 1 (AS 1627.1).  <b>Concrete:</b> Do not apply coating unless concrete has cured at least 28 days @ 21°C and 50% RH or equivalent.
<b>Steel</b>	<u>Immersion Service &amp; Atmospheric exposures:</u> <ul style="list-style-type: none"><li>• For optimal performance, Abrasive blast to SSPC-SP 10 (AS 1627.4 Sa 2½) and achieve a uniform jagged blast profile of between 35µm (minimum) and up to 75µm.</li><li>• For commercial performance abrasive blast to a minimum of SSPC-SP 6, (AS 1627.4 Sa 2) with a 40-75 micron blast profile.</li></ul> Higher film builds and increased abrasion necessitate the need to increase the profile achieved. <ul style="list-style-type: none"><li>• For minor repairs, hand tool or power tool clean in accordance with SSPC-SP 2 or 3 / AS 1627.2 St 2 or St 3 to produce a rust-scale free surface.</li></ul>
<b>Concrete or CMU</b>	Remove all loose, unsound concrete. Remove all oils or other non-compatible sealers or treatments. Surfaces shall be clean, sound, and be abraded to remove laitance, rendering the surface to a coarse profile similar in texture to 80 grit sandpaper. Seal surfaces with Carboguard 1340, or similar penetrating sealer prior to applying Carboguard 635 HAR. Consult Carboline Technical Service for more specific recommendations.

### MIXING & THINNING

<b>Mixing</b>	Mix separately, then combine and mix in the correct 4:1 v/v ratio
<b>Thinning</b>	For spray application thin up to 8% by volume with Thinner #76. For brush application thin up to 8% by volume with Thinner #25.
<b>Pot Life</b>	3 hours at 24°C and less at higher temperatures. Pot life ends when coating becomes too viscous to use.

### APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

<b>Spray Application (General)</b>	Hold gun 300-350 mm from the surface and at a right angle to the surface.
<b>Conventional Spray</b>	Pressure pot equipped with dual regulators, 9.5 mm (3/8") I.D. minimum material hose, 1.8 mm (.070") I.D. fluid tip and appropriate air cap.
<b>Airless Spray</b>	Pump Ratio: 30:1 min. Output: 9.5 l/minute min. Material Hose: 9.5 mm (3/8") I.D. min. Tip Size: 0.43-0.53mm (0.017-0.021") Pressure: 140-175kg/cm <sup>2</sup> (2000-2500 psi) The following spray equipment has been found suitable and is available from manufacturer. <b>Mfg. &amp; Gun</b> Graco 207-300 <b>Pump</b> : Graco Bulldog 45:1 *Teflon packings are recommended and available from pump manufacturer.

## APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

<b>Brush &amp; Roller (General)</b>	For applications over damp surfaces, brush and roller is the preferred method. Multiple coats may be required to obtain desired appearance, recommended dry film thickness, and adequate hiding. Avoid excessive re-brushing or re-rolling. For best results, tie-in within 10 minutes at 24°C. Use a short-nap synthetic roller cover with phenolic core.
---	--

## APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	7°C (45°F)	-7°C (20°F)	-7°C (20°F)	0%
Maximum	32°C (90°F)	49°C (120°F)	38°C (100°F)	95%

Industry standards are for substrate temperatures to be above the dew point. Carboguard 635 HAR is unique in that it can tolerate damp substrates. See Brush or Roller above. Special thinning and application techniques may be required above or below normal conditions.

## CURING SCHEDULE

Surface Temp.	Dry to Handle	Dry to Topcoat Minimum	Dry to Topcoat Maximum
-7°C (19°F)	24 Hours	24 Hours	180 Days
2°C (36°F)	16 Hours	2 Hours	180 Days
10°C (50°F)	10 Hours	1 Hour	180 Days
24°C (75°F)	3 Hours	45 Minutes	180 Days
32°C (90°F)	90 Minutes	30 Minutes	90 Days

**Marine Use** : Refer to the next Curing Schedule below.

**These times are to be used as a guideline.**

The listed times in the chart above are based on a 100-150 microns dry film thickness per coat. Deviation from those thicknesses may compromise the performance and adhesive properties of the film. Higher film thickness, insufficient ventilation or cooler temperatures could result in solvent entrapment and premature failure. Excessive humidity or condensation on the surface during curing will not affect performance but may cause discoloration and result in a surface haze. Any haze or blush must be removed by water washing before recoating. If the maximum recoat times have been exceeded, the surface must be abraded by sweep blasting or sanding prior to the application of additional coats. For force curing, contact Carboline Technical Service for specific requirements. Do not apply to substrates with ice or ice crystal formation. Dehumidify or raise the temperature to eliminate ice on the substrate. This product will tolerate drops in temperature to -17°C during its cure and will continue to cure when the temperature rises. Follow "Cure for Service" guideline listed above to determine when the product is fully cured.

**Topcoating with Polyurethane Finishes:** Many high performance polyurethanes have a limited time to topcoat maximum, some as low as 5 days at 20°C; before proceeding applicators are advised to refer to the relevant Coating Specification or contact Carboline Technical Service for specific information.

**Maximum Topcoat Time for Atmospheric Use will depend on topcoat selected:** contact Carboline Technical Service for specific information.

# Carboguard 635 HAR

## PRODUCT DATA SHEET



### CURING SCHEDULE (MARINE / ANTIFOULING)

Surface Temp.	Dry to Topcoat w/ Antifouling (Min.)	Dry to Topcoat w/ Antifouling (Max.)	Dry to Topcoat with Itself (Max.)
-7°C (19°F)	24 Hours	36 Hours	30 Days
2°C (36°F)	2 Hours	16 Hours	30 Days
10°C (50°F)	1 Hour	8 Hours	30 Days
24°C (75°F)	45 Minutes	4 Hours	30 Days
32°C (90°F)	30 Minutes	3 Hours	30 Days

**The curing schedule above references curing times for immersion service when an antifouling topcoat is used.**

The optimum time to topcoat with an antifouling is when the film is "touch-tacky". If the touch-tacky time has been exceeded, or if the film is "glossy", you can generally re-prime/refresh the applied coat with a fresh coat of itself. High temps and/or sunlight exposure may shorten this recoat schedule.

**Marine Use** : Undocking time of 24 hours @ 24°C

### APPROVALS

<b>Approvals NZ/AU</b>	<b>Food Processing - New Zealand</b> AsureQuality® assessed for food/beverage industry including dairy factory and dairy farm non-incident contact (assessment reference number: h3106b).
------------------------	--

### CLEANUP & SAFETY

<b>Cleanup</b>	Use Thinner #2 or Acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations.
<b>Safety</b>	Read and follow all caution statements on this product data sheet and on the SDS for this product. Employ normal workmanlike safety precautions. Hypersensitive persons should wear protective clothing, gloves and use protective cream on face, hands and all exposed areas.
<b>Ventilation</b>	When used as a tank lining or in enclosed areas, thorough air circulation must be used during and after application until the coating is cured. The ventilation system should be capable of preventing the solvent vapor concentration from reaching the lower explosion limit for the solvents used. User should test and monitor exposure levels to insure all personnel are below guidelines. If not sure or if not able to monitor levels, use suitable approved supplied air respirator.
<b>Caution</b>	This product contains flammable solvents. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the local electrical code. In areas where explosion hazards exist, workers should be required to use non-ferrous tools and wear conductive and non-sparking shoes.

### PACKAGING, HANDLING & STORAGE

<b>Shelf Life</b>	Part A: 48 months at 48°C Part B: 24 months at 24°C  Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers. For products/components exceeding the stated shelf life, contact Technical Services for further advice.
<b>Storage Temperature &amp; Humidity</b>	4°C-38°C 0-95% Relative Humidity

## PACKAGING, HANDLING & STORAGE

<b>Flash Point (Setaflash)</b>	<ul style="list-style-type: none"><li>• Part A: 7°C</li><li>• Part B: 27°C</li><li>• Mixed: 31°C</li></ul>
<b>Shipping Weight (Approximate)</b>	5 Litre Kit - 8.6 kg
<b>Storage</b>	Store indoors and KEEP DRY

## WARRANTY

Manufactured and / or distributed in Australia & New Zealand by Altex Coatings under license to Carboline Company. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Altex Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ALTEX COATINGS OR CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. Altex Terms and Conditions of Trade, available at [www.altexcoatings.com](http://www.altexcoatings.com), apply in respect of all coating products and materials supplied, including samples.