

SELECTION & SPECIFICATION DATA

Generic Type	Vinyl Co-Polymer
Description	V-766E Vinyl Primer Intermediate is a single pack primer for use under V-102E Vinyl Finish Aluminium and is specifically formulated to protect metal or concrete surfaces in hydraulic structures or exposed to weather, water, and many chemicals.
Features	<ul style="list-style-type: none"> • Conforms to US Army Corps of Engineers formulation requirements • Excellent adhesion to metal / concrete when used in conjunction with V-102E Vinyl Finish Aluminium • Good recoatability, even after weathering • Excellent resistance to mineral oils, grease, dilute aqueous acids, and alkalis. • Fast drying • Excellent flexibility & impact resistance • Good abrasion resistance • Excellent water immersion resistance
Colour	White, & Grey
Finish	Semi-Gloss
Film Build	35 - 40 microns dry per coat Dry film thickness in excess of 50 microns per coat is not recommended
Solid(s) Content	20% ± 1%
Theoretical Coverage Rates	5.4 m ² /litre at 37 microns dry Allow for loss in mixing and application
Limitations	Not recommended for solvent immersion or splash.
Topcoats	<p>V-102E Vinyl Finish Aluminium. V-766E Vinyl Primer Intermediate is normally used as a primer and/or intermediate coats under V-102E Finish Aluminium in a multi-coat system sequence as described below: <i>US Army Corps of Engineers - System #3</i></p> <ul style="list-style-type: none"> • Coat 1 - V-766E White at 37 microns • Coat 2 - V-766E Grey at 37 microns • Coat 3 - V-102E at 37 microns • Coat 4 - V-102E at 37 microns

SUBSTRATES & SURFACE PREPARATION

General	All surfaces must be sound and free of oil or grease prior to preparation. Clean and/or degrease with either a suitable non-ionic detergent (such as Altex P40 Cleaner), or solvent wipe with Altex C50 Surface Cleaner prior to abrading or sandblasting.
Steel	For optimum results abrasive blast to Near White Metal equivalent to AS 1627.4 Sa 2½. For non-immersion or light service satisfactory results will be obtained by abrasive blasting to AS 1627.4 Sa 2.
Aluminium	Typically surfaces should be lightly abraded with either a Scotchbrite® pad or P220-320 sandpaper. <i>Scotchbrite® is a registered trademark of the 3M Company</i>

V-766E Vinyl Primer Intermediate

PRODUCT DATA SHEET



MIXING & THINNING

Mixing	Stir thoroughly to ensure a homogeneous condition. This product is supplied at application consistency however some thinning may be required depending upon the type of surface to be painted and the prevailing ambient conditions.
Thinning	Thinning is not normally required; however up to 10% Altex Thinning Solvent #2 may be added without adverse affect on the coating.
Pot Life	N/A - single component

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

General	The preferred method of application for this product is by conventional spray. Airless spray is not recommended.
Conventional Spray	Pressure pot equipped with dual regulators, 9.5 mm (3/8") I.D. minimum material hose, 1.8 mm to 2.5mm I.D. fluid tip and appropriate air cap.
Airless Spray	Not recommended
Brush & Roller (General)	Small areas may be brushed or rolled if conditions are suitable; however care must be taken to ensure the correct film build is applied.

CURING SCHEDULE

Surface Temp.	Dry to Touch	Dry to Handle	Dry to Recoat	Dry to Topcoat
25°C (77°F)	30 Minutes	1 Hour	2 Hours	2 Hours

Curing schedule based on 37 microns DFT.

Dry to Topcoat times refers to topcoating V-766E Vinyl Primer Intermediate with V-102E Finish Aluminium.

CLEANUP & SAFETY

Cleanup	Use Thinner #2 or toluene
Ventilation	It is very important for the safety of the applicator and the proper performance of the applied coating that good ventilation be provided to all portions of the enclosed area. It is equally important to bring into the enclosed area dry fresh air to remove all solvent vapours. Since solvent vapours are heavier than air, ventilation ducts should reach to the lowest portions of the enclosed areas as well as into any structural pockets. Ventilation should be provided throughout the cure period to ensure all of the solvents are removed from the coating.
Caution	For industrial use only: Read and follow all the caution statements on this Product Data Sheet, the product label and the Safety Data Sheet (SDS) for health and safety information prior to use. This product is flammable. Keep away from heat, sparks and open flame. Use with adequate ventilation. May cause eye and skin irritation. Do not breathe vapour or spray. Wear suitable protective clothing such as gloves and eye and face protection.

PACKAGING, HANDLING & STORAGE

Packaging	20 litre
------------------	----------

PACKAGING, HANDLING & STORAGE

Shelf Life | 24 months at 24°C

**Storage Temperature &
Humidity** | 0-40°C
0-90%

Flash Point (Setaflash) | 4°C Setaflash

Storage | Store indoors under cool (10-24°C) dry conditions

WARRANTY

Manufactured and / or distributed in Australia & New Zealand by Altex Coatings under license to Carboline Company. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Altex Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ALTEX COATINGS OR CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. Altex Terms and Conditions of Trade, available at www.altexcoatings.com, apply in respect of all coating products and materials supplied, including samples.