

SELECTION & SPECIFICATION DATA

Generic Type	Modified polyurea
Description	Reactamine Joint Seal is a 2-component 100% solids, polyurea-based joint sealant that is self-leveling and cures in approximately 60 minutes. It works equally well with asphalt and concrete and protects interior horizontal concrete expansion and control joints from spalling, chipping and breakdown. This product can be applied at temperatures ranging from 0° to 150°F (-18° to 65°C) and possess excellent chemical resistance, water resistance and thermal stability at both high and low temperatures.
Features	• 100% solids; zero VOC • Fast cure times • USDA compliant for non-direct food contact • Has a functional temperature range of 0° to 250°F (-18°C to 121°C) • Excellent water resistance, chemical resistance, and thermal stability at high & low temperatures • Works well with asphalt or concrete
Color	Standard colors: Unpigmented (0000) and Grey (0700)
Recommended Thickness	This product is a self-leveling joint seal to fill joints from 1/8" to 1" wide and up to 3" in depth. A typical joint of 1/2" wide by 1/2" deep will fill 77 lineal feet per gallon.
Solids Content	By Volume 100%
VOC Values	As Supplied : 0.00 (Calculated)
Topcoats	Acrylics, Epoxies, Polyureas

SUBSTRATES & SURFACE PREPARATION

General	The product adheres well to sound concrete substrates. All surfaces should be free of moisture, loose particles, and debris. Products may be applied using plural component spray equipment, hand mixing, or plural component cartridges. When hand mixing care must be taken to mix and pour quickly as product is designed to gel quickly.
Concrete	New Concrete: Saw cut concrete at least one inch deep and vacuum joint for any loose dust and debris. Backer rods may be used to prevent excessive material loss through "sinks". Aged Concrete: Remove old or existing joint materials and make fresh saw cuts to freshly opened concrete to receive joint seal material. Then follow procedures as for new concrete.

Reactamine Joint Seal

PRODUCT DATA SHEET



PERFORMANCE DATA

All test data was generated under laboratory conditions. Field testing results may vary.

Test Method	System	Results
Abrasion (ASTM D4060) CS17 wheel; 1000 gm weight; 1000 cycles	Reactamine Joint Seal	40 mg
Adhesion over Concrete (ASTM D4541)	Reactamine Joint Seal	400 psi (concrete failure)
Elongation ((ASTM D412)	Reactamine Joint Seal	400%
Flexibility (ASTM 1737)	Reactamine Joint Seal	Pass (1/8" Mandrel)
Hardness (ASTM D2240)	Reactamine Joint Seal	Shore A: 85
Tear Strength (ASTM D624)	Reactamine Joint Seal	450 pli
Tensile Strength (ASTM D412)	Reactamine Joint Seal	1500 psi

MIXING & THINNING

Gel Time | 4-5 minutes

Mixing | Thoroughly mix in a 1:1 ratio by volume.

APPLICATION PROCEDURES

General | Apply mixed material into joint to the full depth and slightly overfill. Allow to cure for a minimum of 15 minutes before shaving level with concrete.

APPLICATION CONDITIONS

Condition	Material	Surface	Ambient	Humidity
Minimum	10°C (50°F)	-18°C (-0°F)	-18°C (-0°F)	0%
Maximum	77°C (170°F)	66°C (150°F)	49°C (120°F)	85%

Industry standards are for substrate temperatures to be 5°F (3°C) above the dew point. Caution: This product is moisture sensitive and needs to be protected from high humidity, dew and direct moisture contact until cured. Application and/or curing in humidity above maximum, or exposure to moisture from rain or dew may result in a loss of gloss, micro bubbling, and/or blistering of the product.

CURING SCHEDULE

Surface Temp.	Dry to Receive Light Traffic
2°C (35°F)	3 Hours
10°C (50°F)	1.5 Hours
24°C (75°F)	1 Hour

CLEANUP & SAFETY

Cleanup | Contact Carboline Technical Service for cleaning recommendations. In case of spillage, absorb and dispose in accordance with local applicable regulations.

Safety | Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Persons should wear proper personnel protection equipment.

CLEANUP & SAFETY

Caution	This product does not contain flammable solvents; however, clean-up solvents that may be used do contain flammable solvents. Keep away from sparks and open flames. All electrical equipment and installations should be made and grounded in accordance with the National Electric Code. In areas where explosion hazards exist, workmen should be required to use non-ferrous tools and wear conductive and non-sparking shoes.
----------------	---

PACKAGING, HANDLING & STORAGE

Packaging	9.5 gal and 106 gal kits Dual-cartridge packs are also available (12 dual sets per carton)
Shipping Weight (Approximate)	9.3 lbs/gal (4.2 kg/gal)
Flash Point (Setaflash)	Part A: 400°F (204°C) Part B: >200°F (>93°C)

WARRANTY

To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Carboline to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Carboline warrants our products to be free of manufacturing defects in accord with applicable Carboline quality control procedures. THIS WARRANTY IS NOT VALID WHEN THE PRODUCT IS NOT: (1) APPLIED IN ACCORDANCE WITH CARBOLINE'S SPECIFICATIONS, AND/OR (2) PROPERLY STORED, CURED, AND USED UNDER NORMAL OPERATING CONDITIONS. Carboline assumes no responsibility for coverage, performance, injuries, or damages resulting from use of the product. If this product is found not to perform as specified upon inspection by a Carboline representative during the warranty period, Carboline's sole obligation, if any, is to replace the Carboline product(s) proven to be defective or refund the purchase price thereof, at Carboline's sole option. Carboline shall not be liable for any other losses or damages. This warranty excludes (1) labor and costs of labor for the application or removal of any product, and (2) any incidental or consequential damages, whether based on breach of express or implied warranty, negligence, strict liability or any other legal theory. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. The whole text of this Product Data Sheet, as well as the documents derived from it, have been written in English, and for legal purposes the English version shall prevail.